



جامعة الملك عبد الله
للعلوم والتقنية
King Abdullah University of
Science and Technology

Materials and membrane technologies for water and energy sustainability

Item Type	Article
Authors	Le, Ngoc Lieu; Nunes, Suzana Pereira
Citation	Materials and membrane technologies for water and energy sustainability 2016 Sustainable Materials and Technologies
Eprint version	Post-print
DOI	10.1016/j.susmat.2016.02.001
Publisher	Elsevier BV
Journal	Sustainable Materials and Technologies
Rights	Archived with thanks to Sustainable Materials and Technologies. Under a Creative Commons license, http://creativecommons.org/licenses/by-nc-nd/4.0/
Download date	25/08/2019 06:07:11
Link to Item	http://hdl.handle.net/10754/601315

Materials and membrane technologies for water and energy sustainability

Abstract

Water and energy have always been crucial for the world's social and economic growth. Their supply and use must be sustainable. This review discusses opportunities for membrane technologies in water and energy sustainability by analyzing their potential applications and current status; providing emerging technologies and scrutinizing research and development challenges for membrane materials in this field.

Keywords: water sustainability, energy sustainability, membrane materials, membrane technologies

Table of content

1. Introduction.....	5
2. Membrane technology in water sustainability	6
2.1. Desalination	7
2.1.1. Produced water.....	7
2.1.2. Desalinated water for agriculture.....	10
2.1.3. Desalination in mining.....	12
2.1.4. Removal/recovery of heavy metals and rare earth elements (REEs).....	14
2.2. Wastewater reclamation and reuse.....	16
2.2.1. Municipal wastewater	16
2.2.2. Industrial wastewater	18
2.3. Membrane materials for water sustainability and their challenges.....	22
2.3.1. Microfiltration (MF) and ultrafiltration (UF)	22
2.3.2. Nanofiltration (NF)	24
2.3.3. Reverse osmosis (RO).....	25
2.3.4. Forward osmosis (FO)	28
2.3.5. Membrane distillation (MD)	32
2.3.6. Challenges in membrane materials to prevent fouling	34
3. Membrane technology in energy sustainability	37
3.1. Salinity-gradient energy.....	37
3.1.1. Pressured-retarded osmosis (PRO)	38
3.1.1.1. Fundamental of PRO.....	38
3.1.1.2. PRO membrane development and challenges.....	38

3.1.1.3. Economical analyses	39
3.1.2. Reverse electrodialysis (RED)	41
3.1.2.1. Fundamental of RED	41
3.1.2.2. RED membrane development and challenges	42
3.1.2.3. Economical analyses	44
3.2. Batteries and fuel cells	45
3.2.1. Lithium ion batteries (LIBs)	46
3.2.1.1. Current status	46
3.2.1.2. Membrane separator: properties and materials	47
3.2.2. Polymer electrolyte membrane fuel cells (PEMFCs)	51
3.2.2.1. Applications and current status	51
3.2.2.2. Polymer electrolyte membranes (PEMs)	52
3.3. Biofuel production and purification.....	55
3.3.1. Current status	55
3.3.2. Membrane technology in biofuel production and purification	56
3.3.2.1. Biodiesel	56
3.3.2.2. Bioethanol	59
3.3.2.3. Biogas	63
4. Prospects and conclusion	64

1. Introduction

Water and energy are fundamental resources used for economic, social and cultural development. These resources have been long presupposed as abundant. With the increase of population and the developments brought by the industrial revolution, their demand increased and scarcity is now an undeniable result.

Figure 1 illustrates the total global stock of water for human use [1]. From the global water reserve, only 2.5 % is fresh water and the rest is saline. From the 2.5 % the largest part is frozen in polar regions and 30 % are also in remote aquifers of difficult access. As a result only 0.007 % of the total global water is directly accessible for use. Unfortunately part of this water is polluted by industrial plants, mining, oil or gas exploration, fertilizer and pesticide residue used in agriculture. In addition, the uneven distribution of water over the globe causes even more severe water scarcity in some regions. Desalination and water reclamation are of paramount importance in water security, where desalination happens to be one of the main life supports in many arid regions.




Fig. 1. The total global stock of fresh water for human use

The current global energy problem originates not only from limited fossil energy supplies, but also its environmental impacts for its entire energy lifecycle, from mining and processing to emissions, waste disposal and recycling. The indicators of energy sustainability include its price, environmental impacts and greenhouse gas emissions, availability of renewable energy sources, land requirements, water consumption and social impacts [2]. One solution to achieve energy sustainability is to develop sustainable technologies to gradually replace non-renewable fossil fuels. These include energy conversion from renewable and/or natural resources (e.g. biomass, wind, solar and water) into usable energy (e.g. electricity) and energy storage systems for long-term or remote usage.

Membrane technologies play a significant role in water and energy sustainability. Some of them are already applied in industries at scale. Examples include desalination by reverse osmosis (RO), wastewater treatment by membrane reactors (MBR), lithium-ion batteries and membrane-based fuel cells. Besides addressing water and energy scarcity, membrane technologies meet sustainability criteria in terms of environmental impacts, land usage, ease of use, flexibility and adaptability. On the other hand, they still need to be improved in terms of cost and affordability, energy consumption and expertise. To achieve these improvements, advances in membrane materials are needed. This article aims to analyze opportunities for membrane technologies and the revolution and advancement of membrane materials to tackle water and energy sustainability. This review may provide membrane researchers with greater clarity in membrane criteria targets, provide industrial end-users with emerging membrane technologies and reinforce the engagement between research and application aspects.

2. Membrane technology in water sustainability

2.1. Desalination

Desalination plays an important role in water sustainability for many countries around the world, particularly in the Middle East. For instance the water supply for domestic and industrial use in Qatar and Kuwait is 100% provided by desalination [3]. Desaldata [4] reported that 63.7% of the total capacity of global desalted water is produced by membrane processes, validating the importance of membrane technologies in this application. Regarding water sources for desalination, seawater contributes for 58.9%, brackish groundwater 21.2%, surface water and wastewater for the remaining of 19.9% [4]. Application of membrane desalination to produce drinking water from seawater has been comprehensively reviewed [5-15]. Therefore, in this review, we focus on desalination for other applications. Examples are desalination of produced water, desalted water for agriculture, desalination in mining, and removal/recovery of heavy metals and rare earth elements (REEs) from saline wastewater.

2.1.1. Produced water

Produced water is the largest waste generated in oil and gas industries. The global amount of wastewater co-produced in oil and gas exploration is about 210 million barrels/day, three times higher than the produced oil [16]. Its production increases in an attempt to exhaustively recover oil from matured fields with significant environmental consequences. Produced water management is one of the most challenging issues facing the oil and gas industries and protecting human health and the environment. Treatment of produced water for reuse and recycling is an effective option for its handling, which has the potential to be a harmless and valuable product rather than a waste for disposal.

Produced water is difficult to treat because of its complicated physicochemical composition, which may change over the lifetime and well-to-well. Produced water consists of dissolved and suspended organics and solids. Membrane technology plays an increasingly important role in

produced water treatment to remove all above components. Depending on the reuse purpose of produced water, the quality of reused water may vary and the applied membrane techniques may be different. External reuse applications, other than for reinjection, require much higher water quality. Microfiltration (MF) and ultrafiltration (UF) standalone processes or their hybrid integration have been efficiently used to separate suspended particles, macromolecules and oil as a pretreatment step while the combination of ultra-low-pressure nanofiltration (NF) and reverse osmosis (RO) has been applied to treat produced water for higher water quality standards which are potable and for irrigation [17-29]. However, in this review, we focus more on advanced membrane technologies for high-salinity produced water sources, such as produced water from shale gas wells [30, 31], where the concentration of total dissolved solids (TDS) varies from 8,000 to 360,000 mg/L [32]. The high value of TDS concentration restricts the choices of appropriate desalination technologies. RO, which is commercially employed to desalinate seawater (TDS $\approx$ 35,000 mg/L), is not a good choice because of its high hydraulic pressure (high energy) required to overcome the osmotic pressure of high-salinity produced water, making the process unfeasible. This hydraulic pressure may exceed the allowable pressure of the membrane modules and other process equipment, making impractical this application.

On the other hand, emerging technologies such as membrane distillation (MD) and forward osmosis (FO), can be potentially used to treat high-salinity water with low energy consumption. In addition, as compared to RO, both MD and FO are expected to have lower fouling propensity due to the absence of an applied hydraulic pressure. MD is a membrane-based desalination technology which utilizes low-grade heat to drive separation. In MD, a hydrophobic and microporous membrane is employed to separate the aqueous feed stream and the permeate. The transport of liquid feed water across the membrane pores is hindered by the hydrophobic nature

of the membrane. The vapor pressure difference, provided by temperature differences in both sides of the membrane, drives the transport of water vapor through the pores to the permeate side. Different configurations to promote the vapor pressure gradient in MD, such as direct contact, air gap, sweeping gas, and vacuum, have been proposed [33-37]. The process has the advantage of energy efficiency because it requires only minor auxiliary energy to circulate the solutions. However, the complexity in produced water composition is challenging for MD, where small organic components and dissolved gases could pass through the membranes with water and contaminate the permeate stream; or certain feed compounds such as alcohols and surfactants could reduce the feed surface tension and cause membrane wetting, which enables the feed solution to penetrate the pores and compromise the permeate quality. Therefore, to address the produced water quality, pretreatment to remove these above components or post-treatment to remove permeated volatile compounds and gases may be required [35, 38]. In addition, periodic membrane cleaning could be essential to preserve the MD productivity [35, 38].

In the FO process the water transport is driven by an osmotic pressure difference between the feed solution and a concentrated draw solution, which has higher osmotic pressure than the feed. The water flow across the membrane dilutes the draw solution and lower the osmotic pressure gradient. Consequently, a supplemental draw solution regeneration step is essential to recover the draw solute and collect the produced water [39, 40]. Draw solution selection is crucial for FO, especially for desalination of high-salinity water, because it must provide a higher osmotic pressure than the feed and should be easily recyclable. Draw solutes generating insufficiently high osmotic pressures such as magnetic nanoparticles [41], stimuli-responsive hydrogels [42] and polyelectrolytes [43], are normally not satisfactory for FO desalination of high-salinity produced water. Although dissolved salts can provide high osmotic pressures, the need of RO for

their regeneration make them inapplicable for produced water treatment [44-46]. Thermolytic salts, which can vaporize via a change in solution temperature, may be the most suitable draw solute candidate for this application. Thermal energy such as distillation can be utilized for its regeneration. Among thermolytic salts, ammonia–carbon dioxide is the most popular thermolytic draw solute studied for FO [47-49]. It was first discovered as a draw solution for water desalination in 1964 by Neff [50]. Its solution can produce osmotic pressures greater than 200 atm and can be regenerated at 60 °C [49]. Besides ammonia–carbon dioxide, other thermolytic draw solute such as trimethylamine–carbon dioxide [51] or switchable polarity solvents [52, 53] may also be promising for the FO desalination of produced water. However, they are still at early stages of investigation and the presence of ammonia even in low concentration can be a problem for some applications.

2.1.2. Desalinated water for agriculture

In the past, direct sources of fresh water were cheap, not justifying the use of more costly desalinated water in agriculture [54]. However, desalinated water is becoming more competitive because its cost is decreasing, while the costs of surface water and groundwater are elevating. It is now clear that the use of groundwater is not sustainable and new regulations are expected to mitigate their use compared to desalinated water. In spite of this evolution, the cost of desalinated water is still too high for its full usage in irrigation. However, it might be affordable for intensive horticulture with high-value crops such as vegetables and flowers grown in greenhouse or coastal areas (where safe disposal of brines is easier than in inland areas) [54, 55]. Moreover, the high quality of desalinated water can cause less negative impact on soils and crops as compared to the direct use of brackish water [56]. Other advantages of desalinated water for agricultural use are additional and sustainable water resource not depending on the weather

(especially important for drought countries), enhancement in productivity and quality of agriculture products, less water consumption and recovery of salty soils [56, 57]. Furthermore drinking water quality is not needed for agriculture. Partial desalination could be enough in many cases, particularly by choosing salt-resistant crops [58].

According to Desaldata [59], there is an increasing use of desalinated water in agriculture around the world. Spain contributes to the highest proportion of desalinated water use in agriculture, where the current desalination capacity is 1.4 million m³/day and 22% is utilized for agriculture. Most of Spanish desalination plants for agriculture employ brackish water as the feed and are located in coastal areas or within 60 km of the sea. The next country applying high percentage of desalinated water for agriculture is Kuwait (13%). Saudi Arabia, despite its highest production of desalinated water in the world, uses only 0.5% of its desalination capacity for agriculture. Other countries such as Chile, China and Australia are also evaluating the feasibility of desalination technologies to support agricultural water supply.

For agricultural uses, RO is the preferred desalination technology because of its maturity and its reduced cost [57] compared to thermal desalination. Both sea and brackish water are used as the feed. Seawater has salinity of 35,000 mg/L equivalent with the osmotic pressure of 2800 kPa while brackish water has low salinity of 1600 mg/L equivalent with the osmotic pressure of 140 kPa [57]. Such data imply a significantly higher hydraulic pressure and hence higher energy consumption required for RO when applying seawater as the water resource. RO desalinated water has reduced amount of calcium and other essential minerals, as well as a slightly acid pH, which could damage soil structure [56]. Consequently, this water requires a re-mineralization step to adjust the mineral ratios. However, the cost of this post-treatment is virtually negligible as compared to the desalination cost [56]. The use of nanofiltration for partial desalination is also

under consideration with the advantage of lower hydraulic pressure, delivering water with higher mineral content than RO. Another concern of desalinated water for agriculture is its boron concentration because boron is toxic to different crops even with its low content of 0.3-4 mg/L [60] and it has high permeability across membranes [56]. To reduce boron content to an acceptable value, additional treatments such as the use of ion exchange resin might be required [56], which increases the capital cost and operational expense of the desalination plants. In addition, disposal of the RO retentate stream is challenging for inland desalination plants, which adds a supplemental cost to water product.

2.1.3. Desalination in mining

Water plays an important role in the mining industry. It is used for flotation, heap leaching of copper or gold ores, dust suppression, equipment cooling, slurry transport and human needs at mine sites [61]. There are two main water concerns in mining. Firstly, mining requires a sustainable supply of water because mines are often located in remote and arid areas [61]. Secondly, the contamination of the spent mine water with explosive residues, salts, and acids requires treatment before it can be recycled or disposed [62].

The main water resource for remote and arid mines are groundwater and seawater, both of which have high salinity [61]. The salinity of groundwater in mine sites may exceed 100,000 ppm TDS or even higher, such as the mines in Western Australia [61]. These water resources alone or blended with mine water runoff from stockpile, waste or mine dewatering can be directly used for some processing steps in mining such as copper leaching, flotation or cooling [63-66]. However, to alleviate negative impacts on local aquifers, protect the health of miners and to minimize corrosion of underground equipment in underground mines, desalinated water

produced from seawater and groundwater are preferred [67, 68]. RO is the key desalination technology used to treat groundwater in many mines to provide potable and fresh water [61].

On the other hand, spent mine water also requires the desalination process before recirculation or prior to discharge. Mine waters are classified into two groups, according to their tendency to form calcium sulfate scale [62]. The conventional membrane-based desalination processes such as tubular reverse osmosis (TRO) and electrodialysis reversal (EDR) have been demonstrated for their technical viability in desalinating non-scaling mine water in the early 90's decade [62, 69]. TRO uses a tubular membrane module. This is the only practical mode for desalination of feed solutions with high suspended solids concentrations, such as mine water [69]. EDR is the desalination membrane process where an electric current is used to migrate dissolved salt ions through an electrodialysis stack consisting of alternating layers of cationic and anionic ion exchange membranes. The advantages of EDR over RO are its lower sensitivity to effluent temperature or pH and lower capital cost [70]. An EDR pilot plant at Beatrix gold mine in South Africa achieved 80% salt recovery and recycled 84% water [71]. Recently, advanced membrane technology such as vacuum membrane distillation has been studied for mine water desalination [72], using a hollow-fiber membrane to remove up to 99.9% of TDS from Appin (New South Wales) mine water. However, its long-term operation has been not investigated.

For scaling mine water, modified RO processes including seeded RO (SRO) and the slurry precipitation and recycle reverse osmosis (SPARRO) technology have been proposed [62, 68, 73, 74]. In SRO, calcium sulfate is removed prior to membrane treatment to reducing the scaling. This CaSO_4 removal involves a suspension of seed crystals added into the feed via recycling of waste slurry. Although SRO provided high salt rejection and water recovery, its high energy consumption and poor control of CaSO_4 seeds constrained its development. Based on SRO

mechanism, SPARRO was developed and patented by the Chamber of Mines Research Organization (COMRO) from 1989 to 1993 [74]. The schematic representation of the SPARRO pilot plant is shown in Figure 2 and its operational principle can be found elsewhere [74]. It is capable to produce a high quality produced water at water recovery of around 95 %. However, the fouling of quartzitic suspended materials declines the flux. The capital cost for a 4 ML/d SPARRO plant was US\$ 1 million, with an estimated operating cost of US\$ 0.09 /m³ of produced water.




Fig. 2. The schematic representation of the SPARRO pilot plant

2.1.4. Removal/recovery of heavy metals and rare earth elements (REEs)

Removal/recovery of heavy metals and REEs from wastewaters contribute to water sustainability in two ways. First, removal of toxic metals makes wastewater safe for disposal or reuse [75]. Second, recovery of expensive metals and especially REEs can save the cost of wastewater treatment through metal reuse or sale [76]. Table 1 lists the prices of some heavy metals and REE oxides [77, 78]. REE prices have strongly oscillated in the last decade, depending on

demand mining restrictions. In wastewater, the metals exist in their ions and dissolved salt form. Conventional treatment technologies for such salts include chemical precipitation, coagulation, flocculation, floatation, ion exchange, adsorption and electrochemical processes [79]. Compared to these conventional technologies, membrane processes such as ultrafiltration, nanofiltration and reverse osmosis have proven their competitiveness in removal/recovery of metals from wastewater because of their low energy requirement, small volume of retentate, high selectivity, possibility of achieving zero discharge, continuous operation and minimal labor requirement [80-82].

Ultrafiltration (UF) uses a permeable membrane to separate macromolecules based on its pore size (5-20 nm) and their molecular weight (1000 – 100,000 Da) at low transmembrane pressures. Since the pore size of UF membranes is much larger than that of dissolved metal ions in its hydrated ion form or low molecular weight complexes, the metal ions have to bind with large molecules of surfactants [83-85] or complex with water-soluble polymers [86-90] to increase their size before the treatment. The former succeeded to remove 99 % of Cd(II), Cu(II), Ni(II), Pb(II) and Zn(II) from synthetic wastewater while the latter was able to remove 100 % Ni(II), 94 % Cu(II) and 100 % Cr(III). Although their recovery is high, a post treatment is essential to recover metal ions and reuse surfactants and water-soluble polymers.

Table 1. Prices of some metals and rare earth oxides [77, 78]

Metal	Price^a (US\$/kg)	Rare earth oxides	Prices (US\$/kg)^b	
			2011	2015
Sodium	0.13	Lanthanum oxide	20.1	0.6
Magnesium	2.80	Cerium oxide	50.0	1.4
Potassium	0.15	Neodymium oxide	11.6	10.0
Rubidium	79,700	Terbium oxide	48.2	0.9
Caesium	63,000	Dysprosium oxide	4.7	0.5
Germanium	1700	Yttrium oxide	1.8	0.1

^a Estimated selling price in 2005 if extracted from RO brine;

^bSource: Arafura Resources Limited (2011 and 2015)

Reverse osmosis (RO) has also commonly been studied for metal recovery. It provided high recovery of > 99% for Cu(II), Ni(II), Zn(II) and As(V) [91-94]. However, it has yet to be widely applied, mainly because of its high-pressure operation, tendency for fouling and high energy consumption. Nanofiltration (NF) is the intermediate membrane process between UF and RO. Its pore size is equivalent with the molecular weight of 200 –1000 Da and it operates at pressures of 150 – 500 psi (10 – 34 bar) (lower than that of RO). It allows partial permeation of monovalent salts such as sodium chloride but rejects bivalent salts. Since all heavy metals or REEs are bivalent or higher, NF is an effective process to remove/recover them. NF is now a promising technology to reject heavy metal ions such as nickel [95], chromium [96, 97], cadmium [98], lead [99], copper [100, 101] and arsenic [102, 103] from wastewater. It has benefits from high efficiency of metal removal, ease of operation, reliability and comparatively low energy

consumption as compared to RO [104]. Membranes with capacity to better separate specific metals and salts would be an important achievement.

2.2. Wastewater reclamation and reuse

2.2.1. Municipal wastewater

Municipal wastewater refers to sewage, the main wastewater produced in human daily life's activities, including kitchen sink, shower, laundry, etc., and flush toilets sewage. Most municipal wastewater contain biodegradable compounds and limited chemicals, which can be treated using activated sludge systems. The membrane bioreactor (MBR), which integrates either a microfiltration (MF) or UF membrane into conventional activated sludge (CAS) reactor to perform the sludge separation. The MBR process has been introduced in 1960s and enabled to remove high amount of BOD (Biochemical Oxygen Demand), TOC (Total Organic Compound) and completely eliminate TSS (Total Suspended Solid) [105]. Compared to CAS, its product effluent has auxiliary advantage of low turbidity and SDI value (Silt Density Index, an index to characterize the fouling potential of suspended solids on membrane surfaces), which makes it available as the feed water to an RO system. Lozier et al [106] reported moderate success of a pilot-scale study using MBR effluent as feed water for RO. MBR is advancing rapidly both in R&D and commercial application on around the world. An example of successful MBR plants was commissioned by The Public Utilities Board (PUB) of Singapore in December 2006 [107], which provides valuable information on design and operation of the MBR systems under tropical environment. The plant consumed an energy of about 0.55 kwh/m³ and needed no intensive chemical cleaning since the start-up for about 7 months. Currently, over 1,500 MBRs are in operation around the world in Japan, Europe and North America [108]. Table 2 summarizes their configuration and size of operation [109-114].

Table 2. MBR applications in domestic and municipal wastewater treatment

Country	Size of operation	Membrane configuration	Ref.
Japan	Full-scale ~ 125 m ³ /d	Plate and frame external	[114]
USA	Full-scale 9000 m ³ /d	Hollow fiber submerged	[113]
The Netherlands	Pilot-scale 360-840 m ³ /d	Tubular external	[112]
France	Pilot-scale 2.4-4.8 m ³ /d	Tubular external	[111]
Korea	Pilot-scale 48 m ³ /d	Cartridge-disc external	[110]
Germany	Pilot-scale 6-9 m ³ /d	Hollow fiber submerged	[109]

Since 2011, Cranfield University (UK) has been developing waterless hygienic toilet (the Nano Membrane Toilet, NMT), supported by Bill & Melinda Gates Foundation for the Water, Sanitation & Hygiene program [115, 116]. This NMT design is an innovative sanitation solution which can turn human waste into pathogen-free water and encapsulated briquettes for irrigation and fertilizer, respectively. It works without external energy or water. Figure 3 shows its schematic representation. In this toilet, membrane technology plays a key role. A bundle of hollow-fiber membranes is used to separate loosely bound water (mostly from urine) through the mechanism of membrane distillation, where water penetrates through the membrane in the vapor state. A sweep gas is pumped through the permeate side of the membrane to produce the vapor pressure difference between the feed and permeate to drive the water transport [116]. The nanostructure of the fibers reject pathogens. Nano-coated beads are subsequently used as a “condenser” to recover the permeate water with the efficiency of 90 %. Since the condensed water has certain amount of volatile organic compounds (VOCs), it can not be stored. Instead, it must be used in the home daily for washing or irrigation. More details on its operation can be found elsewhere [115]. A prototype for it is expected to be ready for field testing in January 2016.




Fig.3. The schematic representation of the Nano Membrane Toilet

2.2.2. Industrial wastewater

Industrial wastewater originates from many sources, including the iron and steel, mining food, pulp and paper, textile, pharmaceuticals chemical industries. Most industrial wastewater can be efficiently treated by MBR (Table 3) [114, 117-121], which is similar for municipal wastewater treatment. However, along with the rapid development of industrialization and urbanization or due to the particularity of some industries, many industrial wastewater and municipal wastewater sources contain toxic chemicals such as heavy metals and trace organic contaminants (TrOCs). These cannot be removed easily by conventional water treatment technologies or MBR alone. Removal/recovery of heavy metals from wastewater was reviewed in the section 2.1.4, hence we will review membrane-based technologies for TrOC removal in this section.

Table 3. MBR applications in industrial wastewater treatment

Source	Country	Size of operation	Efficiency	Ref.
Wool scouring	Japan	Pilot-scale ~ 10 m ³ /d	TOD removal > 89%	[117]
Pulp mill	Japan	Pilot-scale ~ 10 m ³ /d	TOC removal > 85%	[118]
Automotive industry	USA	Full-scale 113 m ³ /d	COD removal > 94%	[119]
Metal transforming	Canada	Pilot-scale 0.2 m ³ /d	COD removal > 90%	[120]
Cosmetic industry	France	Full-scale	COD removal > 98%	[114]
Maize/egg processing	South Africa	Full-scale 500 m ³ /d	COD removal > 97%	[121]

TrOCs are a diverse group of compounds including persistent organic compounds (POPs), pesticides, pharmaceutically active compounds (PhACs) and endocrine disrupting chemicals (EDCs) [122]. TrOC concentration ranges from 100 ng/L to 100 µg/L in raw wastewater. Even if their content in wastewater is very small, many are biologically active and can cause acute and chronic toxicity to aquatic organisms and possible harmful effects on human health. Intensive membrane-based technologies have been studied to remove TrOCs, such as MBR, single membrane processes (NF, RO, FO), dual membrane processes (UF + RO, FO + RO) and hybrid processes (MBR or BR (bioreactor) + NF, RO, FO, MD) [123].

All the standalone processes have certain inherent advantages and disadvantages and their commercial application of TrOC removal is yet to be developed. Previous studies reported from virtually complete removal for some TrOCs to almost no removal for some others by MBR [123]. Their removal mechanism is governed by the adsorption of the TrOCs on the sludge retained by a membrane and subsequent degradation by the biomass in the reactor. As a result, the TrOC removal efficiency depends on their intrinsic biodegradability and other physicochemical properties affecting their biosorption on the sludge such as hydrophobic interaction, molecular

weight, functional groups and electron withdrawing/donating groups [124-128]. Operating conditions (temperature [129-131], pH [132-135], hydraulic retention time [136], sludge retention time [137-139], dissolved oxygen concentration [140-143]) also have various effects depending on the physicochemical properties of TrOCs. For single membrane separation processes (NF, RO, FO) [144-160], the separation is accomplished by size exclusion, charge repulsion, or sorption diffusion mechanism [122]. Removal efficiency of > 90 % can be achieved but it also largely depends on physicochemical properties of TrOCs. In addition, TrOCs cannot be degraded in these processes, only concentrated and hence further treatment is required to recover or neutralize them. Some dual membrane processes have also studied for TrOCs removal, where one membrane process is supplemental to the other. For example, UF was used to reduce the foulant concentration for the RO process [161] or RO was employed to recover water from the diluted draw solution of the FO process [162-164].

The complete removal of a broad range of TrOCs by a single process is however hardly feasible. Therefore integrated/hybrid processes including MBR and other membrane separation technologies are under consideration to efficiently remove TrOCs [152, 165-172]. For example, the combination of MBR with NF or RO can improve the removal of both hydrophobic and hydrophilic TrOCs. The hydrophobic compounds, which may absorb and subsequently pass through NF or RO membranes, can be first retained into the MBR sludge. The hydrophilic compounds, which have less interaction with the sludge, can be efficiently removed by the following NF or RO. In addition, MBR can retain bulk organic or colloidal compounds to reduce the fouling issue for the NF and RO. Nguyen et al [170] reported that this model can remove 90 % to 100 % of 22 diverse TrOCs from the synthetic wastewater. Similarly, Sahar et al [171] achieved > 99 % removal efficiency of 11 TrOCs from wastewater by a MBR-RO system.

The integration of MBR with FO in an osmotic membrane bioreactor has been demonstrated with promising results [39, 162, 173-178]. Figure 4 illustrates this hybrid process, which takes the advantages of both technologies. It has low fouling propensities, inheriting from the osmotic-pressure-difference-driven nature of FO instead of hydraulic pressure. In addition, the FO process can keep small and persistent TrOCs in the reactor, increasing their retention time and hence improving their biodegradation. Alturki et al [174] reported that this combination obtained high removal efficiency of 25 out of 50 TrOCs while Lay et al [178] found that it efficiently removed four pharmaceuticals to produce excellent water quality. However, the build-up of salinity in the reactor as the result of the FO operation may be toxic to the bioreactor and reduce its effectiveness in degrading TrOCs. In addition, FO-related challenges such as water recovery from the draw solution, draw solution regeneration and reverse solute leakage need to be targeted.




Fig. 4. FO set-up for water/wastewater treatment

More recently, Phattaranawik et al [179] integrated an MD unit into a bioreactor. The bioreactor can first digest the organic matters such as carbohydrates or proteins before they may wet the MD membrane pores and deteriorate its performance [180]. On the other hand, the need to

operate MD at 30 – 80 °C suggests the use of thermophilic microorganisms for the bioreactor may lead to an enhanced biodegradation of organics [181]. Even the salinity was still built up in the reactor, Wijekoon et al [182, 183] found that the high overall removal of > 95 % can be achieved for all 25 studied TrOCs.

2.3. Membrane materials for water sustainability and their challenges

2.3.1. Microfiltration (MF) and ultrafiltration (UF)

In MBR, several types of membranes are used based on the size of contaminants, such as MF for suspended particles (100–1000 nm), UF for bacteria and virus (5–100 nm) and NF for dissolved particles (1–5 nm). MF and UF are technically popular than NF regarding the fouling and cost factors [184-187]. Both ceramic and polymer materials can be used to fabricate MF and UF membranes. Ceramics have advantages of high chemical stability and mechanical strength, ease of cleaning, long and reliable lifetime [188-190]. However, it is expensive and difficult to fabricate in large scale due to its brittleness [189]. Sealing when integrating in modules can be an issue. Polymeric membranes have therefore dominated the market for decades. Common commercial polymers used for MF and UF membranes are poly(ether sulfone) (PES), poly(vinylidene fluoride) (PVDF), polyethylene (PE), polypropylene (PP) and polytetrafluorethylene (PTFE). Except for PES, all the mentioned polymers are very hydrophobic. PE, PP and PTFE are insoluble in organic solvents at room temperature, making the manufacture by solution processes difficult. Porous membranes based on PP and PTFE are produced by mechanical stretching of extruded films. Thermal induced phase separation (TIPS) of polymer solutions is commonly used for the manufacture of porous polyolefin membranes. However, the most widely used method for membrane preparation, applied for PES and PVDF membranes, is the non-solvent induced phase separation (NIPS). This involves solution casting

and immersion in a coagulating water bath. Asymmetric membranes with gradient pore size are obtained in this case. Table 4 lists examples of MF and UF membrane types and configurations used in MBR systems [191-197].

Table 4. Examples of MF and UF membrane types and configurations used in MBR systems

Types	Configuration	Supplier	Pore size	Wastewater	Ref.
MF ceramic	Tubular	Adams Hydraulics	0.2 μm	Food waste	[191]
MF ceramic	Tubular	Kerasep	0.1 μm	Municipal	[192]
MF ceramic	Tubular	-	0.2 μm	Municipal	[193]
MF alumina	Tubular	SCT	0.2 μm	Municipal	[194]
UF	Plate and frame	DDS Lab	20 kDa	Alcohol distillery	[195]
UF Zircon	Tubular	SCT	0.05 μm	Municipal	[194]
UF	Tubular	Zenon Environmental	75 kDa	Sanitary and industrial	[196]
UF	Tubular	-	15 kDa	Synthetic (fuel oil)	[197]

Fouling is one of the biggest challenges for MF and NF membranes because most of them are hydrophobic. The most commonly used strategy to combat fouling is to make membranes hydrophilic by 1) hydrophilically modifying membrane polymers before fabrication, 2) blending with hydrophilic agents; and 3) grafting or coating hydrophilic polymers on the membrane surface. Although fouling can be minimized, undesirable effects such as narrowing the pore size or even blocking the pores of the MF and UF microporous membrane surfaces [198]. In other cases, the pore size enlarges, reducing the salt rejection [199, 200]. In addition, many coating layers have inadequate mechanical and chemical properties and do not sustain long-term

operations [198]. Material challenges to prevent fouling will be further discussed in the section 2.3.6.

2.3.2. Nanofiltration (NF)

Advanced membrane formation technologies have been applied to produce NF membranes with high flux and rejection and low fouling tendency. The basic manufacturing method is NIPS. This produces an integrated porous asymmetric membrane with a selective layer on the top or a non-selective porous structure, which can be used as substrate for multilayered membrane preparation. Typical polymeric materials for this purpose are PES, PVDF and polyacrylonitrile (PAN). The deposition of a selective layer constituted by another polymer, which can be crosslinked or not, can be performed by dip-coating [201, 202] or interfacial polymerization [203-216]. Additional surface modification by nanoparticle incorporation [217-226] and grafting polymerization [226-242] can be performed to control selectivity or reduce fouling. Interfacial polymerization technique refers to the polycondensation of water-soluble and organic-soluble monomers on a porous support to produce thin-film composite (TFC) membranes. The technique is simple, easy to apply, and capable of creating a very thin selective layer of < 100 nm, mainly based on polyamide. This thin layer determines the overall efficiency of the membranes. Efforts to improve NF performance include influencing the selective layer by changing monomers [207, 208, 212, 213, 216], adding additives into the aqueous or organic solutions [204-206] or modifying the surface of the formed polyamide layer [203, 209, 210, 214, 215]. The incorporation of nanoparticles into the selective layer during the polymerization has been studied to form thin-film nanocomposite (TFN) [224]. TFC membranes are considered the benchmark in the field of NF for aqueous separations. On the other hand, grafting polymerization via UV/photo-grafting [243-246], electron beam irradiation [227-229], plasma treatment [230-232]

and layer-by-layer (LbL) [226, 233-236] technique have been also extensively studied to produce NF membranes with high hydrophilicity and low fouling propensity. These techniques are well developed in the laboratory scale but their application in the large scale is still limited.

Although membranes with high permeance and selectivity to salt are available, membranes with tailored selectivity, able to distinguish solutes of similar size are needed. Furthermore the use of NF membranes is also growing for applications other than water purification. This is the case of chemical and pharmaceutical applications, requiring operation in the presence of organic solvents. For this purpose a new class of resistant porous substrates and selective layers is being developed. Materials under consideration are polyetherketone, crosslinked polyimide and polyazoles [247-251].

2.3.3. Reverse osmosis (RO)

The application of membranes for seawater desalination substantially reduced the cost and increased the availability of drinking water. Late in 1980's, the costs were recorded as about US\$2.10/m³ [252]. Since then, the desalination market has been increasingly expanded with improved technologies to reduce the cost. It was remarked in the last decades that large-scale SWRO plants reached US\$0.5/m³ for water price [253]. This price depends on many parameters such as plant location, feed water quality, plant capacity, local energy and labor costs, political and environmental policies and others. The recent capital costs range between US\$900 and 1200/m³/d for a large scale SWRO desalination plant, and can reach about US\$2500/m³/d for a smaller one [6]. Besides the major costs from capital recovery (41 %) and energy consumption (19 %), membrane replacement (16 %) contributes a significant component of the total water cost [254]. Other cost components are operation and maintenance (14 %), chemicals for cleaning (6 %) and spares (4 %).

Polymeric membranes dominate the market for desalination by RO, because of their low-cost fabrication, ease of handling, and excellent performance in terms of selectivity and permeability. A key breakthrough in RO membrane manufacturing and application in different fields was the NIPS process proposed by Loeb-Sourirajan [255]. This allowed production of asymmetric membranes (1960s), initially based on cellulose derivatives, and the fully crosslinked TFC membranes (1970s to 1980s) prepared by interfacial polymerization. The mostly used TFC membranes are constituted by a porous polysulfone substrate and a thin polyamide layer. Thin cellulose acetate hollow fibers and TFC membranes in the spiral module configuration share the market for RO desalination plants. Table 5 provides commercial RO membrane modules in seawater desalination [256-259]. Despite of their success, TFC membranes have a key limitation – the degradation by chlorine, one of the common disinfectants used in wastewater treatment. RO membrane development should focus on chlorine-resistant membranes to eliminate the need of de-chlorination for the RO feed and re-chlorination for the RO permeate, reducing the overall cost of the system [260-263]. In addition, high-boron rejection membranes should be addressed when increasingly stringent water quality standards for which lower boron concentrations are required [264-270]. This will help to reduce the number of RO pass in the RO plants to achieve the required water quality [271, 272]. In terms of water permeance and salt selectivity, the current RO membranes are well advanced and successful in large-scale seawater desalination operation. The future RO development should focus on other regulated and emerging trace contaminants such as persistent organic compounds (POPs), pesticides, pharmaceutically active compounds (PhACs) and endocrine disrupting chemicals (EDCs).

Table 5. Examples of commercial RO membrane modules in seawater desalination

Brand name	Membrane	Module	Operation condition	Flux (m ³ /day)	Salt rejection (%)	Location	Ref.
DOW FILMTECT M 8-in. SW30HRLE	TFC crosslinked membrane	Spiral wound	32 g/L NaCl, 55 bar, 25 °C, pH 8, 8 % recovery	28.0	99.60-99.75	Perth, Australia	[257]
Hydranautics 8-in. SWC4+	TFC crosslinked membrane	Spiral wound	32 g/L NaCl, 55 bar, 25 °C, pH 7, 10 % recovery	24.6	99.70-99.80	Lobregat, Spain	[256]
Toray 8-in. TM820C	TFC crosslinked membrane	Spiral wound	32 g/L NaCl, 55 bar, 25 °C, pH 8, 8 % recovery	19.7-24.6	99.50-99.75	Singapore	[259]
Toyobo 16-in. HB10255	Asymmetric cellulose tri-acetate	Hollow fiber	35 g/L NaCl, 54 bar, 25 °C, 30 % recovery	60.0-67.0	99.40-99.60	Fukuoka, Japan	[258]

The evolutionary development of polymeric RO membranes is mostly mature. Membranes with high salt rejection are available with high water permeance. Even higher permeances would reduce the needed membrane area, but would not considerably save energy for RO operation [47]. However membranes with higher fouling resistance and higher resistance to chlorine are needed. RO membranes continue to be developed using nanoparticles [206, 273-277]. Two major practical challenges need to be overcome before they can move to the next stage of development. The first aspect is cost. The second is the difficulty to scale up. In addition, health and safety aspects particularly in the case of added nanoparticles need to be estimated, especially for drinking water desalination.

There is currently intense interest in biomimetic membranes based on embedded Aquaporin due to the expectation of superior permeability and almost absolute salt rejection [278-280].

However, the fabrication of Aquaporin membranes with high packing density would be hardly feasible at the large scale, being a complex and expensive technique. Moreover, these bio-materials are relatively unstable and hence the durability of the membranes is questionable at least for mass applications like desalination of seawater for drinking purposes.

2.3.4. Forward osmosis (FO)

There are two evolutionary development routes of FO membranes. The first is to modify available commercial NF or RO membranes and the second involves the development of new membranes with specific design for FO applications. Fabrication of FO membranes from existing NF or RO membranes is considered simple, effective to some extent and cost-efficient. Despite the similarity in performance criteria such as high salt retention and high water flux, the difference between NF/RO and FO membranes is the balanced relation between high-pressure tolerance (or mechanical strength) and low internal concentration polarization (ICP) of the support layer. In FO processes, pressure tolerance is not critical (almost no or low hydraulic pressure is applied) while low ICP is important to maintain high water flux and low salt leakage. To achieve it, therefore, the mechanical strength of the membranes is reduced to some extent to increase porosity and reduce tortuosity. For example, when McCutcheon and Elimelech [281] removed the backing fabric support layer (thickness of 80 – 120 μm) of the commercial RO membranes (overall thickness of 200 μm) and the FO water flux of the modified membranes was improved by a factor of 5. Another difference between RO and FO membranes is the importance of pore wettability. For the FO process, pore wettability must be improved, because the presence of un-wetted pore regions may block the water flux and significantly exacerbate ICP. Coating with a highly hydrophilic polymer like polydopamine (PDA) has been demonstrated as an effective technique to improve wettability, flux, and fouling resistance [282-286]. The water flux

can be increased ten folds after PDA coating. Table 6 provides examples of commercial membranes used for FO tests [287-292]. Despite the improvement after modification, the efficiency of the modified FO membranes is still limited and restricted by the inherent properties of their parent NF/RO membranes. Thus, many membrane scientists turn their research scope to develop new FO membranes.

Table 6. Examples of commercial membranes for FO tests

Material	Type	Supplier	Water permeability $\times 10^{-12}$ (m/s.Pa)	Draw solute	Rejection (%)	Ref.
CA-3000	flat-sheet	Toray	3.75	NaCl	98	[292]
CA	flat-sheet	HTI	5.69	(NH ₄) ₂ CO ₃	> 95	[291]
CTA	flat-sheet	HTI	7.10	NaCl	> 92	[290]
TFC (NF)	TS80	TriSep	20.0	MgSO ₄	100	[290]
TFC (RO)	DS-11-AG	General Electric	11.91	-	99.5	[289]
TFC (RO)	SW30XLE-400i	Dow	3.80	NaCl	-	[288]
TFC (RO)	SWC1	Hydranautics	5.60	-	100	[290]
TFC (RO)	SW30-HR	Dow	4.39	NaCl	98	[287]

A desirable FO membrane should have (1) highly hydrophilic, greatly porous but adequately strong support layer to minimize ICP effects, and (2) ultrathin defect-free highly selective layer to achieve high water flux, high salt rejection and minimize reverse solute diffusion [293]. These two layers are either integrated by the same materials (asymmetric membranes) or prepared separately from different materials in a thin-film-composite (TFC) membrane structure. The latter has the advantage over the former in its possibility to optimize support and selective layers

separately. The development strategy of FO membranes in terms of materials is similar to that of RO membranes. Rather than membrane materials, the development for FO also focuses on membrane morphologies.

The ideal support morphology for FO membranes is still under debate. Some studies reported that the support with straight finger-like macrovoids is more efficient in mitigating ICP effects due to its low pore tortuosity (leading to low structural parameter) that facilitates the transport of both water and salt [294]. On the other hand, finger-like structures were considered not essential by other authors [257] to achieve low overall structural parameter. For example, Li et al [295] and Widjojo et al [296] concluded that even though the support exhibits a sponge-like structure, its structural parameter can also be remarkably reduced due to its high hydrophilic characteristics. In addition, the significantly low structural parameter (80–100 microns) can be obtained by using electro-spun fibers as the support [217, 297, 298]. Although the water flux of the resultant TFC membrane is high, however, the mechanical stability of the thin selective layer deposited directly on the electro-spun nanofiber support is still questionable.

Besides membrane materials, the exploration of suitable draw solute materials is of great importance in FO process. The key criteria of draw solute selection are (1) high osmotic pressure, (2) low reverse diffusion (leakage through the membrane into the feed), (3) easy and economical regeneration, (4) non-toxicity and (5) reasonable price. In addition, the draw solution should not degrade the membranes or cause membrane scaling/fouling. Numerous draw solutes have been proposed, including inorganic [40, 290, 292, 299, 300], thermolytic/volatile [49, 291, 301-305], organic [173, 306-308], magnetic and polymer-based solutes [309-313]. Table 7 [40] summarizes their examples, recovery methods and drawbacks, which implies that there has been

no perfect draw solutes so far. Different FO objectives and available solute recovery technologies determine different draw solutions.

Despite extensive investigation of FO in the past decade and significant advancement in its understanding, questions and challenges of its energy sufficiency remains. Several recent FO analyses have disproved the common misguided view that FO is a low energy process and a potential alternative of RO in seawater desalination [314-316]. In fact, FO cannot be a single separation process, where water spontaneously permeates through a semi-permeable membrane (i.e. low energy process), but has to be combined with a subsequent separation of the diluted draw solution to recover water (i.e. require further energy). Based on the thermodynamic theories and practical kinetic analyses, the theoretical minimal energy of this hybrid process is unlikely to compete with that of the standalone RO process [315, 316]. However, FO is still potentially promising to desalinate the high salinity feed stream with osmotic pressure exceeding the tolerant pressure of RO (as discussed in section 2.1.1) or treat the waste stream with high fouling tendency (as discussed in section 2.2.2) [316]. In the former application, the hybrid FO systems employing thermolytic draw solutions may be favorable because only relatively small amount of the thermolytic draw solute (higher vapor pressure than water) must be vaporised as compared to large volume of water having to be recovered in conventional distillation. In addition, the draw solutes with high vapor pressures requires less total energy for recovery. Using low-cost thermal energy sources (e.g. solar energy, geothermal energy and industrial waste heat) for draw solution recovery would reduce the energy cost of the whole FO process. In the second application, FO may be advantageous in the integration with MBR because of its low fouling propensity and high reversibility of fouling. Fouling is undesirable because it reduces process performance and

increases operation costs. Development of membrane materials with improved fouling properties continue to be active areas of research, which will be discussed in the section 2.3.6.

Table 7. Draw solutes, their recovery methods and drawbacks

Group	Example	Recovery method	Drawback
Inorganic	Al ₂ SO ₄	Precipitation by doping Ca(OH) ₂	Toxic by-products
	MgCl ₂	None	Not pure water
Thermolytic/ volatile	SO ₂	Heating or air stripping	Energy intensive, toxic
	NH ₄ HCO ₃	Moderate heating	High reverse draw solute flux, insufficient removal of ammonia
	Ethanol	Pervaporation-based separations	High reverse draw solute flux and low water flux
Organic	Glucose–Fructose	None	Not pure water
	Sucrose	NF	Relatively low water flux
	Dendrimers	Adjusting pH or UF	Not feasible
	Albumin	Denatured and solidified by heating	Not feasible
	2-Methyl imidazole based solutes	MD	Materials costly
	Fertilizers	None	Only applicable in agriculture
	Organic salts	RO	Low water flux, energy intensive
Magnetic	Magnetic particles	Captured by a canister Separator	Poor performance, agglomeration
Polymer-based	Hydrogels	Deswelling of the polymer	Energy intensive, poor water flux
	Fatty acid-polyethylene glycol	Thermal method	Poor water flux
	Polyelectrolytes	UF	Relatively high viscosity
	Hexavalent phosphazene salts	Not studied	Not economical and practical

2.3.5. Membrane distillation (MD)

In general, a MD membrane should (1) exhibit high hydrophobicity to prevent pore wettability on the feed side (membrane liquid entry pressure of water ranges from 48 to 368 kPa for common commercial flat-sheet MD membranes [317]); (2) be thin to achieve high permeation flux (the optimum thickness lies between 30 – 60 μm [318], but when composite hydrophobic/hydrophilic membranes are used, the hydrophobic layer can be as thin as 5 μm [319]); (3) have reasonably small pore size (in the range of 0.1 to 0.6 μm [320]) to prevent liquid intrusion but not too small to contribute for mass transfer resistance; (4) have high porosity 60 – 80 % [321]) and low tortuosity (a value of 2 has been commonly assumed [322] but 3.9 was also reported [323]) to favor the water vapor transport; (5) have high heat transfer resistance (the thermal conductivity ranges from 0.11 to 0.27 $\text{Wm}^{-1}\text{K}^{-1}$ at 23 °C for three common MD polymers PVDF, PTFE and PP [324]) but low mass transfer resistance (the reported membrane coefficient ranges 3 – 15 $\times 10^{-7}$ $\text{kg/m}^2\text{pa.s}$ for commercial MD membranes in the direct contact operation mode [36]); (6) have adequate chemical and thermal resistances, strong mechanical properties and long-term stability; and (7) be cheaply available. Early development stages of MD membranes focused on hydrophobic commercial polymers such as PVDF, PTFE and PP, analogously to those used for micro- and ultrafiltration. Some commercial membranes used for MD are listed in Table 8 [325]. The main advantage of these materials is their commercial availability. However, they cannot meet all above requirements of an excellent MD membrane. Hence, research on designing and synthesizing new membrane materials for MD processes is essential to attain a fully commercial status of MD.

Novel MD hydrophobic membranes can be fabricated either by newly synthesized hydrophobic polymers or by surface modification of hydrophilic membranes. An example of the former is

synthesis of copolymers between PVDF with hexafluoropropylene (HFP) or tetrafluoroethylene (TFE) [326-330]. Although MD membranes prepared from these materials had lower flux than PVDF membranes due to lower porosity, they exhibited excellent mechanical properties with 100% salt rejection. On the other hand, various surface modifications have been investigated for MD, such as surface segregation [319, 331], impregnation and cross-linking [331], co-extrusion [332], coating [333], grafting [334], and plasma polymerization [335].

A promising MD membrane fabrication is the composite hydrophobic/hydrophilic membranes in the multilayered structure [37, 319, 335-340]. The advantage of such structure is that high mass transport can be achieved by tailoring the thickness of the hydrophobic layer as thin as possible while low heat transfer and adequate mechanical properties can still be maintained by controlling the thickness of the hydrophilic layer. Other attempts on MD membrane development are use of nanofiber membranes prepared by the electrospinning method to achieve high and controlled void volume [341]; incorporation of carbon nanotubes [342-346] to increase vapor permeation and prevent pore wettability; and adding clay particles to enhance the mechanical strength and long-term stability of the membrane [347]. Finally the synthesis of new hydrophobic polymers and their manufacture into flat-sheet and hollow fiber membranes for MD has been successfully demonstrated [348, 349].

Table 8. Several commercial membranes studied for MD

Polymer	Trade name	Company	Mean pore size (μm)
PTFE	TF200	Gelman	0.2
	FGLP14250	Millipore	0.25
	M05E0020	GVS	0.2
	Desal K150	Millipore	0.1
	Fluoropore	Millipore	0.2
PVDF	GVHP	Millipore	0.11
	Microza	Ashi Chem	0.2
	M09G0020	GVS	0.2
	Durapore	Millipore	0.2
	GVHP22	Millipore	0.16
PP	Accurel PP	Microdyne	0.22
	Liqui-cel	Celgard	0.04
	MD020TP2 N	Enka	0.2

2.3.6. Challenges in membrane materials to prevent fouling

Membrane fouling is an important and inevitable challenge in all membrane processes. Lower membrane fouling allows higher water productivity, less cleaning and longer membrane life, and reduced capital and operational costs. Membrane fouling can be categorized by the type of foulant: inorganic (scaling), organic and biofouling. Table 9 provides their definition and common foulants [350, 351], being more severe in pressure-driven membrane processes such as RO and NF where high hydraulic pressures are employed.

Table 9. Category of fouling

Category	Definition	Foulants
Colloidal fouling	Fouling occurs due to the accumulation of particles on the membrane surface and inside the membrane pores, forming a cake layer	Suspended solids and particles such as silicate, ferric oxide, iron oxide and aluminum oxide
Inorganic fouling	Fouling occurs through precipitation deposits resulting in bulk and membrane crystallization	Inorganic salts such as calcium carbonate, calcium sulfate, calcium phosphate and sodium chloride
Organic fouling	Fouling occurs due to adsorption of natural organic compounds on membrane, causing gel formation	Natural organic matters such as fulvic acid, protein, polysaccharides, and polyacrylic polymer
Biofouling	Fouling occurs when biofilm forms on the membrane	Aquatic organisms, such as fungi, algae, yeast and bacteria

Classical solutions to membrane fouling are the use of pretreatment technologies, operation optimization and periodic membrane cleaning. Table 10 presents their effects, affecting parameters and challenges [350]. On the other hand, membrane modification is potentially the most sustainable solution to prevent fouling. The characteristics and properties of membranes that affect fouling formation are their chemical structure (functional groups, charge and hydrophilicity) and morphology (pore size, surface roughness or surface pattern). Generally, high hydrophilicity, negative surface charge and low surface roughness are desirable for low fouling propensity.

To achieve above properties, many membrane modifications have been extensively studied such as surface coating [352-354], surface grafting [355-359], incorporation of hydrophilic monomers/inorganic particles [360-364] and zwitterionic modification [365]. Although membrane modifications can effectively enhance anti-fouling capacity, they often affect flux. In addition, many of them are costly, complicated or only at the laboratory scale. Furthermore most

approaches successfully delay the early stages of fouling, but are not able to hinder it in long term. Therefore there is still a need for new membrane materials able to overcome the trade-off between anti-fouling capacity and permeability, as well as advanced methods of membrane modification, which are cost-effective and simple.

Table 10. Classical solutions to membrane fouling

Solution	Methods	Effects	Affecting factors	Challenges
Pre-treatment	Coagulation, precipitation, media filtration, sonication, boiling, membrane filtration, pH changes and chlorination	Alter the physicochemical and/or biological properties of the feed water, and reduce the foulant concentration	Agent, temperature, dosing point, solution and foulant properties, and the characteristics of the membrane	Ineffective pretreatment can lead to high rates of membrane fouling
Operation optimization	Gas bubbling	Increase shear rate at the surface to intermittently remove fouling layers	Size of bubbles, gas flow rate	Mainly effective in addressing external membrane fouling
	Temperature and flow reversal	Inhibit the homogeneous precipitation of salts and disrupt the nucleation of salt crystals	Temperature, flow rate	No in-depth explanation on the nucleation kinetics and scale formation
Chemical cleaning	Rinse with acid or base	Rinsing with acid is particularly effective in removing inorganic scaling while rinsing with base is relatively effective in reducing organic fouling	Type, amount of agents	May cause membrane structural damage

3. Membrane technology in energy sustainability

Renewable energy sources are increasingly becoming a greater part of the global energy picture, particularly for power generation. They contributed approximately 58.5% of additions to the world's power generation capacity in 2014 with significant growth in all regions [366]. Membrane technology has a great potential to take advantages of renewables to produce energy. This review covers several examples including conversion of seawater or wastewater into electricity (pressure-retarded osmosis and reverse electrodialysis), energy storage for renewable energy sources such as solar, wind or biofuels (fuel cells and batteries) or direct participation into energy production processes (biofuels). Other applications in natural gas separations, solvent recovery, various refinery and power plant processes (e.g. CO₂ capture) are beyond the scope of this review.

3.1. Salinity-gradient energy

Salinity gradient energy is the power generated by the difference in osmotic pressure between aqueous solutions of different salinities, e.g. fresh and salt water. The chemical potential difference in this case can be equivalent to the power of a 270-m high waterfall to be converted into electrical energy [367-369]. The concept of harvesting such energy was first proposed by Pattle [368], and then reconsidered in 1970s by Loeb [370, 371], when the global energy crisis urged the need of exploring new alternative energy sources. Salinity gradient energy is estimated to be the second largest marine energy source with total estimated global power potential of 1650 TWh/y [372, 373], equivalent to about half the annual hydropower of 3551 TWh/y [374]. This energy is considered clear and sustainable, with no production of CO₂ or other emissions and no interference with the global climate. Its high potential is supported by the inherent abundance of river and seawater. The two promising technologies of capturing salinity gradient energy are

pressured-retarded osmosis (PRO) and reverse electrodialysis (RED). Both of them are membrane-based technologies and they are used in different salinity conditions. PRO is more efficient if using concentrated brines, whereas RED is more favorable with seawater [375].

3.1.1. Pressured-retarded osmosis (PRO)

3.1.1.1. Fundamentals of PRO

The principle of PRO was first reported by Loeb in 1976 [371, 376]. However, its research slowed down in the 80s and 90s due to the lack of membranes with the required performance and acceptable cost. Its investigation was resumed in the late 2000s by Skilhagen et al [377], Gerstandt et al [378] and Thorsen and Holt [373], bringing the membrane development forward enough to allow the implementation of the technology. With further optimization, Statkraft (Norway) opened the first PRO power plant prototype in 2009 to prove its concept in generating electricity. Figure 5 depicts an idealized arrangement of a PRO plant. On one side of the membrane seawater or brine is pumped keeping a constant hydraulic pressure. Concurrently, the compartment on the other side of the membrane is fed by fresh or waste water. Water permeates through the membrane from the fresh water to the seawater side, moving a turbine to generate electricity [370, 379].




Fig. 5. Idealized continuous PRO system

3.1.1.2. PRO membrane development and challenges

A membrane is the important component of a PRO set-up, separating the solutions with different salinity and maintaining the chemical potential difference, which will lead to the electricity generation. The membrane performance in PRO is characterized by the membrane power density, i.e. the power output per area unit, which it would be able to provide. This power density is critical because it directly affects the cost of the generated power. The starting membranes for PRO were practically those used for RO [380-384]. However it has been recognized that concentration polarization [302, 304, 385] greatly impacts osmotically driven processes. The requirements for PRO membranes are quite different from those for RO. The thick, dense and highly resistant support layer of RO membranes, which is essential to tolerate high pressures, causes severe concentration polarization in PRO [39, 292]. Therefore membranes developed exclusively for FO or PRO have a thinner and less dense support layer [385-388].

To achieve high membrane power density, the PRO membrane should have high water flux and pressure tolerance, corresponding to an optimum combination of the membrane properties: A (water permeability), B (salt permeability) and S (structural factor). Most PRO studies have not focused on exploration of new materials but on the discovery of suitable membrane morphology with large A and low B for the active layer and low S for the support.

3.1.1.3. Economical analyses

At the present, it is difficult to obtain a cost estimation for osmotic power due to the lack of their large scale plants to validate current cost assumption. The world's only pilot-scale plant was commissioned by Statkraft in Norway under "The Osmotic Power Project" funded by the European Union [389]. It was reported by Statkraft to have a membrane with the output density of 1 W/m^2 , which is below the target of 5 W/m^2 . This value is estimated a minimum power

density for a PRO business viability [378]. The project was then discontinued in 2014 due to the commercial absence of high-performance and cheap PRO membranes.

Among PRO cost components, according to Loeb's report [390], capital cost contributes a large fraction of more than 60 % while operation and maintenance costs would be a small fraction. If the membrane power density is low, a high capital cost is expected because it would require not only a large membrane area to overcome the low power density, but also high membrane installation cost for the large membrane area. A current study reported the range of installed membrane cost for desalination plant from US\$20 to US\$40/m² [391]. If the lowest value is assumed, the capital cost of the 20-MW capacity power plant with the power density of 1 W/m² is estimated US\$20,000/kW [392], which is still above those associated with wind power (US\$1700 - US\$2450/kW) [393] and solar (US\$6800 - US\$7700/kW) [394]. To compete with solar power, a minimum power density of 5 W/m² and a maximum installed membrane cost of US\$35/m² would be required [392]. Other than wind and solar, the osmotic power seems to be cost-similar or cost-competitive with other ocean energy sources and bio-power sources [392]. However, these cost analyses did not consider the costs related to the intake and outfall systems and pretreatment of feeding streams which depend on plant location and water sources. With inclusion of these cost components, Kleiterp [395] predicted higher capital costs of US\$32,000/kW and US\$29,200/kW for a 25 MW and 200 MW PRO plants, respectively; with an assumed power density of 2.4 W/m². The responsive unit energy costs were estimated \$1.21 kWh⁻¹ and \$1.0 kWh⁻¹ for a 25 MW and 200 MW PRO plants, respectively. These unit costs could potentially reduce to \$0.12 kWh⁻¹ and \$0.07 kWh⁻¹ for a 25 MW and 200 MW PRO plants, respectively if developments in membrane technology achieve increased membrane power density, reduced membrane price and other capital costs. Similarly, Skilhagen [396] predicted

the unit energy cost of US\$0.16 kWh⁻¹ for a demonstrated 25 MW osmotic power plant when cost reductions are gained from technology advancement and economical scale-up. This value is higher than the reported value of wind power (US\$0.07 to US\$0.14 kWh⁻¹) [393] but comparable or more economical than that of solar power (US\$0.11 to US\$0.86 kWh⁻¹) [394, 397, 398].

In summary, membrane elements are the main fraction of the capital cost of an osmotic power plant. Commercially available membranes with high power density and low susceptibility to fouling are required to reduce the capital, operation and maintenance costs. With the expectation that the PRO membranes would be commercialized and their price abruptly reduced in the similar trend observed for RO membranes in last decades, the unit energy cost of PRO could be in the range of US\$0.065 - US\$0.13 kWh⁻¹ by 2030 [399]. PRO is a renewable energy source with high environmental advantages. If it receives government subsidy or incentives the cost could drop to US\$0.05-US\$0.06 kWh⁻¹ [400], which is potentially more cost-effective than wind and solar power in the future. Cost is however only one of the aspects to be considered for PRO implementation. This technology depends much more on geographical requirements than most other water-based processes. Special salinity conditions need to be available as prerequisite.

3.1.2. Reverse electrodialysis (RED)

3.1.2.1. Fundamentals of RED

The principle of RED was first applied in the early of 1950s by Pattle [368] and further developed during the late 1970s. RED operates with the reverse principle of electrodialysis (ED), using the similar stack design and membrane. In contrast to ED where a voltage is applied to induce ion flow, in RED electrochemical potential gradient is produced from the concentration difference between the feed streams. A full-scale RED system comprises multiple cell pairs, each of which is composed of dilute (e.g. river water) and concentrated (e.g. seawater) feed channels,

and anion/cation exchange membranes disposed alternatively. This membrane stack has electrodes at its two ends to convert the ionic flow into an electric current through oxidation-reduction reactions (Figure 6).




Fig. 6. Schematic drawing of a RED cell

Unlike PRO processes that use pressurized water to spin the turbine for electricity production, the RED process can convert ionic flow directly into electricity. The produced power is determined by the electro-chemical potential drop across the membrane and the external load resistance. The potential across the membrane depends on the concentration difference and membrane perm-selectivity.

3.1.2.2. RED membrane development and challenges

Daniilidis et al [401] emphasized the importance of affordable membrane cost and power performance to the success in RED commercialization. Ion exchange membranes (IEMs) are essential for RED and are currently 2-3 times more expensive than RO membranes [47, 369]. Most commercial IEMs are not specifically designed for RED, but for other applications such as

ED, diffusion dialysis, electro-deionization and fuel cells [402]. Table 13 presents commercially available IEMs studied for RED [367]. In these studies, rather than the development of membranes, the efforts have been made on system design and operation such as stack, cell configuration, spacers and electrodes. Although some commercial IEMs exhibit properties desirable for RED (e.g. high permeability), they may not meet other RED requirements (e.g. physical and electrochemical properties). In addition, the high prices of these membranes also disfavor the implementation of power generation by RED.

IEM membranes are known for high thermal, chemical and mechanical stability. However, these properties are not crucial for RED membranes[392, 403-405]. Lower stability than that required for fuel cells could be acceptable, especially if it results in lower membrane cost. On the other hand, more critical for RED are the membrane swelling degree, ion exchange capacity (IEC) and fixed charge density (FCD), i.e. the ratio of IEC and water uptake. Different from other applications, where swelling is an adverse effect because it might decrease the membrane permselectivity, it can be advantageous for RED to reduce the membrane resistance [406-408]. Good RED membranes should have the ideal balance between high permselectivity and low membrane resistance to optimize its power generation [407].

Table 13. Several commercial IEMs studied for RED

IEM	Power density (W/m²)
Anion exchange membrane	
Neosepta AFN	1.23-1.30
Selemion APS	1.23-1.30
Fumasep FAD	1.16-1.24
Neosepta AMX	1.02-1.22
Ralex AMH-PES	0.73-1.12
Cation exchange membrane	
Neosepta CM-1	1.12-1.30
Fumasep FKD	0.99-1.19
Neosepta CMX	1.02-1.30
Ralex CMH-PES	0.73-1.23

Easy functionalization is expected to increase IEC and hence permselectivity, whereas easy processability enables possibility of fabricating low-resistant (thin) membranes with adequate mechanical strength. The most considered polymers for RED membranes are polyvinyl alcohol (PVA) [409-416], poly(2,6-dimethyl-1,4-phenylene oxide) (PPO) [411, 416-419] and polyvinylchloride (PVC) [401, 420-424]. These materials have advantages of good chemical resistance, good membrane processability and low cost, but the absence of charged groups in their pure chemical structure leads to poor conductivity. Thus, modification of these polymers or membranes is required to produce charged groups. Options include introducing negatively charged sulfonic groups by crosslinking with sulfosuccinic acid (SSA) or functionalizing with sulfonic acid [414, 416, 417], blending with quaternized cationic polymers [413, 422] and incorporating with inorganic particles [409-412, 420, 423]. Many efforts have also focused on synthesizing new membrane materials for RED membrane. For example, Guler et al [405] synthesized anion exchange membranes (AEMs) from polyepichlorohydrin (PECH) and 1,4-

diazabicyclo-2,2,2-octane (DABCO). The resultant membranes has high IEC, but blending with polyacrylonitrile (PAN) is required to increase mechanical strength. Guler's group [425] also synthesized negatively charged coating layers of 2-acryloylamido-2-methylpropanesulfonic acid (AMPS) and N,N-methylenebis(acrylamide). Although many studies have reported good power density of RED membranes, none of them have been commercialized. Fouling propensity is also critical when using seawater and rivers as feed solutions. However, very few fouling studies have been conducted so far for RED membranes. Thus, optimization of well-balanced permselectivity and membrane resistance and low fouling propensity should be the heart of membrane material development and modification for RED application.

3.1.2.3. Economical analyses

Similar to PRO, the economic analyses of RED is only at the modelling stage because there is no RED plants so far. Membranes are also the major components of the capital, which contributes to about 80 % [426] because they are the heart of a RED stack. Membrane related cost parameters such as power density, membrane price, membrane lifetime and its annual loss of power density remain the decisive factors for the unit energy cost while labor and construction costs have small effects [401]. Currently, the maximal power density reported in the literature is about 2.2 W/m² at 35 % of energy efficiency when using seawater (~0.5 M NaCl) and river water (~0.01 M NaCl) [427]. A higher power density of 4 W/m² can be obtained if the intermembrane distance is reduced and flow rates increase [427]. Including the power required for pumps, a gross power density of 2.7 W/m² can be theoretically achieved in the near future [401]. The current high membrane prices (~ US\$55/m²) for comparably performing membranes and cheap heterogeneous membranes (< US\$4.4 /m²) not associated with a high power density suggest that all of RED applications are not economically viable at the current. However, future membrane

advancement in this technology is expected to develop more affordable ion-exchange membranes ($< \text{US\$}4.4/\text{m}^2$) with the current performance (a power density of $2.7 \text{ W}/\text{m}^2$). If such condition can be achieved, the levelized cost of energy can be reduced to $\text{US\$ } 0.17 / \text{kWh}^{-1}$ [401] making RED competitive with conventional and established renewable energy sources. In 2014, a RED pilot plant with a capacity of 50 kW was installed in The Netherlands [428]. Its performance report is expected to offer more relevant data for cost analyses and further development of RED technology.

3.2. Batteries and fuel cells

With unprecedented evolution of clean technologies for electricity generation, energy storage devices are expected to play an important role in electricity networks. Among many energy storage devices, batteries and fuel cells have received great attention because of their high energy density [429]. A common feature is their use of a chemical reaction to produce electricity. Batteries store chemical energy internally. Thus, when this energy is exhausted, the batteries must be recharged. Fuel cells generate electricity through reactants stored externally and hence will live as long as fuel is supplied. Polymer electrolyte membrane fuel cells (PEMFCs) are under consideration for transportation and automotive applications because of their rapid start-up and shutdown, capability of operating even when they have not reached their operating temperature, no thermal shock and no high temperature corrosion [430]. The strongest competitors of fuel cells for transportation are currently batteries. Lithium ion batteries (LIBs) have been widely used also in portable electronic devices such as mobile phones, laptops, and medical microelectronic devices with advantages of long cycle life and low self-discharging [431]. Membranes are critical components both in LIBs and PEMFCs and their performance essentially depends on their chemical composition and morphology. Their primary role is to

physically separate the anode and cathode, preventing electrical shorting, while serving as electrolyte reservoir for ionic transport.

3.2.1. Lithium ion batteries (LIBs)

3.2.1.1. Current status

Lithium ion batteries were first introduced in 1991 [432] and since then they have grown into a US\$ 4.64 billion market in 2013 [433] charging portable electric devices such as laptops, cell phones and digital cameras [432]. More recently, their application has been extended to power tools, electric bicycles and hybrid electric vehicles (HEVs) [432, 434]. Moreover, LIBs are considered as energy storage for renewable energy sources such as solar or wind. Global sales of such energy storage systems are expected to be approximate US\$ 2 billion in 2015 and to increase to US\$ 6 billion by 2020 [435]. Along with the growth of LIB market, that of their membrane separator is expected to increase. Its market is estimated to exceed US\$ 3 billion by 2020 and its production is estimated to be > 1000 billion m² in 2013 [435]. Japan-based Asahi Kasei, USA-based Celgard, South Korea-based SKI and Japan-based Toray Tonen have occupied major market share of battery separators (Table 12).

Table 12. Battery separator market share

Separator manufacturers	Market share*	Brand name
Asahi	26 %	Hipore TM
Toray	23 %	Setela TM
Celgard	19 %	Celgard [®]
SKI	13 %	—
UBE	7 %	Upore [®]
Entek	3 %	Entek
Sumitomo	1 %	Pervio TM
Others	8 %	—

*: data in 2012

3.2.1.2. Membrane separator: properties and materials

A typical LIB comprises an anode, a cathode and electrolyte (Figure 7). During discharging, lithium ions move from the anode to the cathode across the electrolyte to produce the current. During charging period, an external electrical power is applied to drive the current in the reverse direction and make lithium ions re-migrate on the anode. The separator is a must to separate two electrodes to prevent short circuit.




Fig. 7. Schematic drawing of a typical lithium-ion battery

A LIB separator should have (1) chemical and electrochemical stability to prevent degradation and/or loss of mechanical strength during cell reaction or dissolution of electrolyte [436, 437], (2) quick wettability for absorption and retention of the electrolyte to smoothen the lithium ion transport and to facilitate the process of electrolyte filling during the battery assembly [431, 436-438], (3) strong mechanical strength to withstand the stress of physical forces or the tension of the winding process during battery assembly [431], (4) strong puncture strength to withstand the penetration of electrolyte [431, 437, 439], (5) proper thickness to offers both low internal resistance and safety [431, 436-438], (6) uniformity of the thickness for stable and long cycle life of the batteries [431], (7) small pore size to restrict the permeation of electrode material particles and dendritic lithium metal [431, 437], (8) uniform pore size distribution to avoid performance loss resulted from uneven current distribution [431], (9) appropriate porosity to keep adequate liquid electrolyte inside for sufficient ionic conductivity, low internal resistance, high safety and good shutdown capability [431, 437, 439], (10) high porosity and low tortuosity [431], (11) high

dimensional stability to keep the separators flat and not curled up when immersed into the electrolyte and not shrunk during storage and operation [437], (12) good thermal stability to keep the battery safe during the drying process of battery assembly [431] and (13) shutdown capability when overheating or short circuit occurs [436, 437]. Table 13 provides target number for certain properties of LIB membrane separators.

Table 13. Target properties of a LIB membrane separator [431]

Characteristic	Target number
Mechanical strength	< 2% offset at 6.9 MPa
Puncture strength	> 300 g/25.4 μm
Thickness	20-25 μm
Pore size	< 1 μm
Porosity	40-60 %
Thermal stability	> 90 $^{\circ}\text{C}$

Based on the characteristic requirements of membrane separators, the most commonly used materials for membrane separators are PE and PP or their blends with other polymers such as polystyrene (PS) and poly(ethylene terephthalate) (PET) [431, 440-447]. However, their poor thermal stability, low wettability and poor electrolyte retention limit the battery performance. Thus, other polymers such as PVDF [448-455], PAN [456-460], poly(methyl methacrylate) (PMMA) [456, 461-463] have also been used for preparing microporous membranes. Microporous PDVF membranes have good physicochemical and electrochemical stability, high mechanical strength and great wettability. A disadvantage is the potential formation of LiF during operation through reaction between lithium ions and the fluorine atoms in PDVF [452]. Microporous PAN membranes are an alternative, exhibiting good processability, high electrolyte

uptake, high thermal and electrochemical stability with the transport of lithium ions being facilitated by interaction with the $C\equiv N$ groups. However, PAN membranes face the problem of electrolyte leakage during long-term storage [464]. Like PDVF and PAN, PMMA is also used for fabricating microporous membrane separators because of its high affinity towards electrolytes. PMMA membranes display high conductivity, good thermal and electrochemical stability. However, they have poor mechanical strength due to their amorphous structure [465]. Other problems linked to PDVF and PAN are their high crystallinity, which is one of major obstacle for high ionic conductivity [437, 459, 461, 466, 467]. To overcome this problem, many of their copolymers [467-472] and blend polymers [473-487] have been developed for LIB membrane separators.

Optimal mechanical strength, thermal resistance, shutdown capability and electrochemical performance are requirements for a good battery membrane, but this is hard to achieve by using a monolayer. To tackle this issue, multilayer membranes have been proposed [488-495]. Typical examples are multilayer membranes of PE and PP [494, 495]. They combine the advantages of PE melting at high temperatures to block the pathway of ions, hence providing safety assurance, and the benefit of strong mechanical properties and dimensional stability of PP for the overall structure. Many patents for bi-layer or tri-layer membranes of PE and PP have been filed [494, 495]. Several multilayer membrane separators, such as Celgard® tri-layer separators, have been successfully used in commercial LIBs [431]. However, attempts are still essential to improve them in terms of thickness, wettability and ionic conductivity. Important approaches to simultaneously enhance multi-properties of membrane separators such as physical and chemical properties, thermal stability, wettability and ionic conductivity are grafting [496-499], coating [496, 500-506] and filling with nanoparticles [507-523].

All microporous membranes discussed above need to be filled with electrolyte to transport lithium ions. Electrolyte membranes, on the other hand, have inherent ion conductivity property and hence can act as both separator and electrolyte. In the aspect of materials, these electrolyte membranes are made of similar polymer materials with non-electrolyte membranes, but they are incorporated with ionically conductive components, e.g. lithium salts to form solid polymer electrolytes [524-527] or liquid lithium-based electrolyte such as lithium hexafluorophosphate and lithium polyvinyl alcohol oxalate borate to form gel polymer electrolytes [528-536]. Recently, ion exchange membranes with lithiated perfluorinated sulfonic groups, swollen with organic solvents, have been investigated [537-539], demonstrating high thermal and mechanical stability and good interfacial compatibility with the electrodes. High safety standards have been achieved. In most cases ionic conductivity and mechanical properties still have to be improved.

3.2.2. Polymer electrolyte membrane fuel cells (PEMFCs)

3.2.2.1. Applications and current status

PEMFCs have been applied in three main areas of transportation, portable and stationary power generation. PEMFCs are used in transportation to replace internal-combustion engines (ICEs) because of their potentials of obtaining higher efficiency and lower emission of greenhouse gases [540]. The typical power of transportation including passenger cars, utility vehicles and buses ranges from 20 kW to 250 kW [541]. Many light-weight vehicles using PEMFCs have been developed and demonstrated, such as GM Hydrogen 1, Ford Demo IIa (Focus), DaimlerChrysler NeCar4a, Honda FCX-V3, Toyota FCHV, Nissan XTERRA FCV, VW Bora HyMotion, and Hyundai Santa Fe FCV [540]. Car manufacturers such as Toyota, Honda, Hyundai, Daimler, and General Motors (GM) have announced plans of commercializing their PEMFC vehicles by 2015 [542]. Besides light-weight vehicles, PEMFC buses have been commercialized and their

procurement plans have been announced under government funding such as US National Fuel Cell Bus Program and Europe's Fuel Cell and Hydrogen Joint Technology Initiative [543].

PEMFC's advantages for portable electronic devices are their high energy power capability and short charging time. The global production of portable PEMFC devices grew from approximately 2000 units in 2005 to about 10,000 units in 2009 [544]. The typical power of portable electronic devices ranges from 5 to 50 W, but the power of < 5 W for micro power application or 100-500W has also been considered [541, 545]. Besides mobile phones and laptops, portable PEMFCs can also be used for electric toys and utilities such as radio-control cars, boats, robot and emergency lights. Several portal PEMFC companies are CMR, Viaspace, Jadoo, Horizon MTI micro, Neah, Samsung DSI, SFC, Sony and Toshiba [544].

Stationary PEMFC power systems can be used for residential applications, where the waste heat of fuel cells can be used for household usage [546]. Further significant enhancement in fuel cell cost and lifetime is required for this application. However, the cost is already justifiable for applications such as back-up power for banks and telecommunication companies, since an eventual power breakdown [540] would have extremely expensive consequences. Several units like Plug Power GenSys® and Ballard FCgen™ 1020 ACS PEMFC systems have been developed in many locations. Several companies working on the stationary PEMFC application are Altergy, ClearEdge, Ebara Ballard, Eneos Celltech, Hydrogenics, IdaTech, Matsushita, P21, Plug Power and Toshiba FCP [547].

3.2.2.2. Polymer electrolyte membranes (PEMs)

Current research of PEMs have focused on two types of PEMFCs, which are hydrogen/air (H_2/O_2) fuel cells and direct methanol fuel cells (DMFCs). Figure 8 depicts the schematic drawing of a typical PEM H_2/O_2 fuel cell. The latter is more applicable for portable power

applications because its fuel (methanol) is more easily portable. Properties of PEMs determine the efficiency of PEMFCs. Desirable PEMs should have (1) high proton conductivity, (2) low electronic conductivity, (3) low fuel and oxidant permeability (4) adequate electrochemical and chemical stability, (5) high thermal and hydrolytic stability, (6) good dimensional and morphological stability, (7) adequate water transport, (8) high mechanical properties, (9) long lifetime and (10) low cost. Table 14 provides target numbers of certain properties for PEMs. Generally, based on the respective materials, PEMs can be categorized as perfluorinated polymer-based membranes and non-perfluorinated polymer-based membranes. Nafion® membranes (perfluorinated polymer) for DMFCs typically have a price in the range of US\$600-1200/m² depending on the thickness, while the sulfonated poly(ether ether ketone) membranes (sPEEK) have a lower price of US\$375/m² [548].

Table 13. Target properties of PEMs

Characteristic	Target numbers
Proton conductivity	> 80 mS/cm [549]
Electronic conductivity	negligible or zero [550]
Fuel and oxidant permeability	< 10 ⁻⁶ molmin ⁻¹ cm ⁻¹ for methanol [549] < 2 mAcm ⁻² for hydrogen/oxygen crossover at 1 atm [551]
Electrochemical and chemical stability	at > 80 °C [552]
Long lifetime	> 5000 h for transport use [553] > 40,000 h for stationary use [553]
Cost	< US\$10/kW [554]




Fig. 8. Schematic drawing of a PEM fuel cell

The perfluorinated polymer Nafion[®] is currently the benchmark of PEMs in fuel cell industry. This material has high proton conductivity (50-200 mS/cm), moderate water uptake (30-55%), excellent chemical resistance at moderate conditions, and high operation temperature range up to 190 °C [555, 556]. However, Nafion still has several serious drawbacks such as (1) polymer chain decomposition by alien cations [557, 558], (2) declined conductivity and water uptake if the cell is contaminated with multi-charged ions [559-561], (3) poor chemical and mechanical stabilities at high temperatures [562-565], (4) severe degradation in multiple thermal and hydration/dehydration cycles [566-568], (5) insufficient resistance to methanol permeation when applied for direct alcohol fuel cells [569, 570] and (6) high cost due to its complex processability. To explore cheaper alternatives to Nafion[®], many non-perfluorinated polymers have been studied, including polystyrene, sulfonated polyimide, sulfonated aromatic main-chain polymers (e.g. polyphosphazene, poly(arylene ether), polysulfone, poly(sulfone ether), polyphenylsulfone) and natural polymers (e.g. pectin, chitin phosphosphate, gelatin, agar, alginic acid and uracil) [571-575].

However the requirements of high oxidation stability and high proton conductivity can be hardly achieved at low cost to compete with Nafion[®] in hydrogen fuel cells at least in temperatures up to 80°C.

Operation at temperatures higher than 100°C would be more attractive for different reasons. It provides less catalyst poisoning with CO (impurity in H₂ fuel), faster electrode kinetics and hence higher cell efficiency, and simplified water management due to the absence of biphasic water (vapor and liquid) [551]. Operation above 100°C is however challenging for Nafion[®] due to natural dehydration and loss of conductivity. The search for better polymeric materials able to keep high proton conductivity at high temperature and low humidity levels has motivated intense activities in the field. Polybenzimidazole (PBI) is the most investigated polymer for this purpose. Other functionalized polyazoles have been synthesized and investigated in the laboratory [571, 572, 574, 575]. The inspiration of using PBI as PEMs originates from the design of phosphoric acid (H₃PO₄) fuel cells (PAFCs), where phosphoric acid is employed as an ion conductor. In PAFCs, thin silicon carbide ceramic is used as the matrix to carry H₃PO₄ [576, 577]. Later on, the polymers with ability of chemical interactions with H₃PO₄ to form acid-base poly salt systems are considered as a new class of proton conducting PEMs. Among many polymers tested for such ability [578-582], PBI is the most promising candidate because of its high mechanical and thermal stabilities [579, 583, 584]. Several PBI/ H₃PO₄ membranes are commercialized by BASF such as CeltecL, CeltecP, and CeltecV [585]. BASF also reported their long-time stability such as more than 20000 h for CeltecP1100 and 6000 h for CeltecP2100 for H₂/O₂ fuel cells at 160 °C [586]. However, these data are still lower than the lifetime requirement for commercially viable stationary fuel cells, which should be higher than 40000 h [551].

3.3. Biofuel production and purification

The use of liquid (mainly bioalcohols and biodiesel) or gaseous (i.e. biogas) fuels produced from biomass for transportation is already an established technology, at least in countries like Brazil and Sweden. Biofuels have advantages over fossil fuels such as (1) easy availability from common biomass sources, (2) lower carbon dioxide emission, when considering the whole life cycle (3) environmental friendliness, and (4) biodegradability and sustainability [587]. The basic problems of biofuel are large areas needed for feedstock cultivation and competition with food production.

3.3.1. Current status

Although biofuels are growing fast and acquiring global production significance, statistics for 2008 reported that they represented only about 1.5% of the global transport fuel consumption [588]. USA and Brazil are two large bioethanol producers and account for 80 % of its global supply with the capacities up to more than 500 million litres per year (2007) [588]. The global bioethanol market is predicted to attain approximately 20 % increment from 2015 to 2020 [589]. Bioethanol is the most common alcohol used for internal combustion engines because of its technical and economical suitability [590]. In Brazil bioethanol is used pure (100%) or blended with gasoline in different ratios with comparable performance in cars equipped with “flex” motors [591].

Different from bioethanol, the large biodiesel producers are from Europe, which accounts for 87% of the global supply [588]. Among them, Germany and France are the largest producers. However, the total global production of biodiesel is small compared to that of ethanol, approximately 4.1 Mtoe in 2006. The global biodiesel market is predicted to increase about 35 %

from 2015 to 2020. Biodiesel can be used as a diesel substitute in the blend with conventional diesel (up to 5%). Higher biodiesel fuel blends are used for fleet vehicles (e.g. trucks and buses). The global biogas production shows an exceptionally rapid increase from 292 PJ in 2000 to 1.1 EJ in 2011 [592]. In 2011, 90 % of global biogas production and consumption is attributed to European Union, China and USA. Two-thirds, one quarter and approximately one-tenth of biogas production in Europe are originated from agricultural factories, waste disposal sites and sewage treatment plants, respectively. Biogas typically comprises approximately 60% methane, 40% carbon dioxide and some trace gases. It can be used for diverse end-use applications such as heating or combined heat and power (CHP) generation. If biogas is purified and upgraded to biomethane, it can be used as natural gas or transportation fuel. Bauer et al [593] reported that by the end of 2012, there are 221 biogas upgrading plants in the world.

3.3.2. Membrane technology in biofuel production and purification

3.3.2.1. Biodiesel

Biodiesel, which is as known as fatty acid methyl ester (FAME), is produced from transesterification of renewable lipid (vegetable oil or animal fat) by methanol. In this process, the membrane plays an important role to remove the byproduct glycerol from the product stream (biodiesel) [594] or to retain the unreacted lipid within the membrane [595]. There are two basic separation principles of membrane-based biodiesel production, based on oil droplet size (or membrane pore size) or perm-selectivity of the membrane.

In the system based on oil droplet size, a microporous membrane, which is typically a ceramic membrane or carbon membrane, is used because its high resistance to degradation and corrosion in the harsh environment of biodiesel production, where acid or base is used as a catalyst [595-597]. Due to the differences in polarity, methanol and lipids are immiscible. Their mixture exists

as a two-phase system, where the lipid/oil micelles or droplets are dispersed in the continuous phase of methanol. These droplets have much higher diameter than the product biodiesel, byproduct glycerol, reactant methanol and catalyst (acid or base) and can be filtered by a membrane. Further water-washing is required to purify the biodiesel from other components in the permeate.

In the system based on membrane selectivity, a non-porous dense hydrophilic polymeric membrane (e.g. poly(vinyl alcohol)) is used [594, 597, 598]. The separation is based on the interaction between the target components and the membrane. Generally, glycerol and methanol have strong interaction with –OH groups of PVA via hydrogen bonding and hence penetrate through the membrane. As the result, they are continuously removed from the mixture during the reaction whereas the unreacted lipid and the product biodiesel, of which chemical structures are different with that of the membrane, are retained in the system. In such separation mechanism, the system can be operated under atmospheric pressure. To restrict the permeation of catalysts through the membrane, activated carbon is used to carry them during the reaction [595]. By this approach, Baroutian et al [595] reported that the oil to FAME conversion reached 93.5 % and high-quality biodiesel can be produced without washing or purification steps.

To combine reaction and separation in a single step, the catalytically active membranes, which is the product of catalyst immobilization into the membrane matrix, have been developed. The acidic catalyst membranes are fabricated by esterifying the –OH groups of PVA with 5-sulphosalicylic acid to achieve sulfonic groups in the polymeric matrix [599] or by blending with poly(styrene sulfonic acid) containing strong acidic groups [600]. In addition, the heterogeneous catalysts, e.g. hydrotalcite $\text{Mg}_6\text{Al}_2(\text{OH})_{16}(\text{CO}_3^{2-}) \cdot 4\text{H}_2\text{O}$ [601] or amino-functionalized carbon nanotubes (CNTs) [602], can be embedded into the polymeric matrix to form catalyst

membranes by dispersing them in the polymer solution. In the case of CNTs, these particles can also increase the mechanical strength of the membrane when an appropriate content is used. Besides PVA, the polymer polyacrylonitrile (PAN) is also used for biodiesel production. To date, however, only one paper reported its membrane for purifying biodiesel by removing glycerol [603].

Similar to other membrane processes, fouling is one of the major challenges. In biodiesel production, the fouling is caused by the agglomeration of glycerol – which is favored by the presence of excess alcohol, soap (salt of fatty acids) and catalysts – to block the pores of the membrane in the system based on the oil droplet size. However, in the typical biodiesel production, fouling is not serious because the alcohol concentration in the reaction mixture is low. For the system using selective membranes, unfortunately, fouling has been not studied so far. In addition, the mechanical properties and surface morphology of the membranes have not been fully studied. Therefore, these problems should be addressed before applying in practical biodiesel industry.

3.3.2.2. Bioethanol

Among bioalcohols, bioethanol is the most practical because of its high content produced from the fermentation process. Bioethanol can be divided into three generations based on the origin of biomass used as depicted in Table 14 [588]. Higher generation bioethanol requires more steps in its production procedure. An overview of third generation bioethanol production with potential membrane applications is described in Figure 10 [604], where MF/UF process is applied to harvest microalgae as the biomass/substrate for fermentation, MD/NF/RO process is employed to concentrate the pre-hydrolyzates and remove microorganism-inhibitors before fermentation, UF/NF is used after fermentation to remove some by-products and retain microorganism and

MD/pervaporation is integrated to recover and purify the product bioethanol in the final step [604].

Table 14. Bioethanol - definitions and development status

Generation	Biomass source	Current status	Challenges
1 st	Sugar and starch crops	- Technically mature - Commercially available	- The profitability heavily depends on the prices of both fossil oil and the commodity feedstock. - Compete with food prices - The greenhouse gas benefits depend on the feedstock and process used
2 nd	Lignocellulosic biomass such as agricultural wastes (e.g. straw) and energy crops (e.g. Miscanthus, poplar)	- Advanced stage of development and deployment - Demonstration stage	- Cost reduction - Availability of comparatively low-cost and sustainable feedstock
3 rd	Algae	- Earlier stage of research and development	- Cost reduction - Technical challenges

Algal biomass harvesting is challenging because of their small size (3-30 μm), similar density to that of water and large volumes of water that must be removed to recover algal cells. Compared to conventional techniques such as coagulation/flocculation, flotation, gravity sedimentation, centrifugation, membrane filtration (MF/UF) is more advantageous in terms of energy consumption, recovery efficiency and non-toxicity. Petrushevski et al [543] reported a biomass recovery of 70-89 % when concentrating algae from large reservoirs by membrane filtration. Although membrane filtration has many advantages over other techniques, membrane fouling – a serious problem – is still under investigation.




Fig. 10. Application of membrane processes for 3rd – generation bioethanol production

Membrane processes can be applied prior to the fermentation process in the production of the 2nd or 3rd generation bioethanol to concentrate sugar concentration (it is low due to different pretreatment processes and hydrolysis efficiency) and to remove fermentation-inhibitors produced during the pretreatment process. The main advantage of membrane processes over conventional techniques (e.g. evaporation, solvent extraction, overliming, activated charcoal adsorption and ion exchange) is the capability of concentrating sugar and removing inhibitors simultaneously [605, 606]. Moreover, the capital investment and operation cost of membrane processes are lower than those of the evaporation process [607]. The present membrane processes applied in this aspect include MD, NF and RO, depending on the target inhibitors and sugar concentration. On the other hand, ultrafiltration can be integrated into this stage to recycle valued enzymes (e.g. cellulase) used to hydrolyze the biomass into sugar in the previous step. By this way, economic viability of the enzymatic hydrolysis of biomass is improved.

Subsequent to the fermentation process, a MD/pervaporation (PV) process is integrated to continuously recover bioethanol from the fermentation broth. Generally, the final ethanol concentration of the corn-to-ethanol fermentation (1st generation) is more than 10 wt% while the microorganisms used for fermentation can tolerate a maximum ethanol concentration of 10 wt%. Therefore, ethanol must be removed constantly to prevent the activity loss of microorganisms. On the other hand, cellulosic biomass-based fermentation (2nd generation) produces lower ethanol concentrations (< 5 wt%). To save energy and costs of the refining process, the ethanol should be pre-concentrated. The conventional technique to concentrate fermentation broths is distillation. However, this technique has several main drawbacks [608]: (1) the energy consumption is remarkably higher to concentrate low ethanol concentration than to concentrate high concentration, (2) the mixture of ethanol and water forms an azeotrope at 95.6 % ethanol, which cannot be separated by the conventional distillation, and (3) it is technically difficult to integrate the distillation into the fermentation to remove ethanol continuously due to that fact that high-temperature operation of distillation is lethal to microorganisms. Membrane technologies (MD/PV) are therefore more useful to remove ethanol from dilute aqueous fermentation broths. By adding membrane systems to the fermentation, productivity and production rate, as well as the substrate uptake rate can be improved.

Ethanol recovery by MD is based on the higher partial pressure of ethanol than that of water, which implies ethanol vapor can preferentially transfer through the membrane pores. Both direct contact air gap MD are common configurations coupled with fermentation for ethanol production. Udriot et al [609] reported that 87 % increase in ethanol productivity was achieved. Although this integrated fermentation-MD system can overcome the drawbacks of the conventional batch production, its studies have been limited to the lab scale. Larger scale operations need to be

investigated. Moreover, the membrane selectivity of current MD materials (PTFE, PVDF and PP) is low [604] and hence higher performance MD membranes are needed. However alcohol and biological surfactants which might be present in the fermentation reduces the surface tension and promote liquid intrusion in the membrane pores, making MD application challenging.

Pervaporation (PV) is the most studied membrane technique for ethanol recovery from dilute fermentation broths. The separation of this process is based on the chemical potential difference generated by either vacuum or a sweep gas on the permeate side of the membrane. The separation mechanism predominantly relies on the preferential sorption (solubility) and diffusion (diffusivity) of the target component across the membrane. To recover ethanol, the membrane should be hydrophobic to possess higher affinity (solubility) towards ethanol that allows ethanol to preferentially pass through. Polydimethylsiloxane (PDMS) is the dominant polymeric material used to recover ethanol from water because of its superior performance as compared with other polymeric materials [610]. From the aspect of energy consumption, the separation factor of pervaporation membranes must be larger than 20 to compete with distillation [611]. This is the one of the main challenges to restrict the industrialization of polymeric membranes in this application. Although inorganic membranes (e.g. zeolite and 1-silicalite) produce the separation factor of over 20, they pose problems in processability of large-sized membranes and they are often expensive. In addition, performance degradation in practical separation system is another issue needed to be solved before the system can be industrialized [612]. This degradation is mainly due to the complex compositions in the fermentation broth. Even with very small concentration, the present of by-products in the fermentation broth can significantly reduce membrane performance. Thus, exploring higher performance and reliable membrane materials are critical for pervaporation applications in ethanol recovery.

3.3.2.3. Biogas

Biohydrogen is generated in fermentation processes while biomethane is produced during anaerobic digestion of biological waste [613]. Anaerobic membrane bioreactors (AnMBRs) have an advantage in producing both biohydrogen and biomethane in a single membrane system because in anaerobic digestion, the hydrogen production phase occurs prior to the methanogenic phase [614]. Besides biogas, many other gases and volatiles exist in the system in trace amounts (ppm) such as nitrogen, oxygen, carbon dioxide, hydro sulfide and volatile siloxanes [615]. They must be removed to upgrade biogas because their presence not only reduces the calorific value of biogas, but also causes corrosion to the transport and distribution system and reduces the possibilities of compression [613].

Membrane technology are also gaining importance in biogas [613]. Also for this application polymeric membranes have clear advantages over ceramic for operation in temperatures below 150°C. Several companies are currently developing gas separation membranes on commercial scale such as Membrane Technology Research, Air Products, UOP, Air Liquide, Praxair, Cynara, UBE and GKSS Licensees [616]. Continuous attempts have still been made to improve the performance of these polymeric membranes. The two commonly used effective approaches are (1) chemical modifications, especially introduction of bulky functional groups such as $-\text{Si}(\text{CH}_3)_3$, $-\text{C}(\text{CF}_3)_2$ or bromine groups [617, 618]; which increase permeability without sacrifice of selectivity and (2) crosslinking to improve selectivity of highly permeable membranes [619]. Although polymeric membranes have high potential for gas separation, they (especially glassy polymers) usually pose problems with densification, ageing or plasticization. Plasticization occurs when gas molecules are dissolved into micro-voids of the polymeric matrix, leading swelling or permanent damage to the matrix and hence drastic increase in gas diffusion and

reduced selectivity [620]. To overcome plasticization, considerable attempts have focused on membrane modification by heat treatment [621, 622], chemical modification [623] and polymer blending [624, 625].

Also, mixed matrix membranes (MMMs) are promising candidate for gas separation by synergistic combination of easy processability from polymeric membranes and high selectivity and permeability from inorganic membranes. The attractive inorganic materials for gas transport are zeolites, carbon molecular sieves (CMS), carbon nanotubes (CNTs), metal-organic frameworks (MOFs) and covalent organic frameworks (COFs). To achieve the improvement of MMMs, the problems in their fabrication must be conquered, which are particle sedimentation, agglomeration and interfacial voids. Sedimentation causes inhomogeneous filler and polymer phase whereas agglomeration and interfacial voids lead to non-selective voids decreasing selectivity. These problems are possibly solved by [613] (1) preparing polymer solutions at high concentrations to increase viscosity and lessen the particle sedimentation, (2) quickly solidifying membranes to offer the fillers less chance to settle, (3) matching the polarity of polymer chains and filler structures, (4) subsequently thermally annealing MMMs, (5) developing a priming protocol of MMM preparation (e.g. coating an ultrathin layer of the matrix polymer on the particle surface) and (6) using melt extrusion technique.

4. Prospects and conclusion

Membranes have been long used as sustainable solution for seawater desalination by reverse osmosis. The successful use of membrane technology in other applications requires new materials and tailored separation characteristics. Although high flux and rejection of salt and small neutral molecules can be achieved by commercial membranes, membranes with specific functionalities, better defined pores or functionalized transport channels could provide

breakthroughs in the separation and recovery of valuable products for instance in mining industry, heavy metals and rare elements, as well as in the biotech industry. Membranes could supply partial desalinated water and play a more important role for agriculture providing the needed water in arid regions. For situations in which drinking water quality is not a requirement and alternatives to RO can be used, new membranes with higher flux but lower salt rejection may be an option. Providing the right composition of nutrients or selectivity for ions, preferentially for crop growth, would require membranes with tailored pore size and functionality and is still an open challenge. Industrial effluents treatment will offer more opportunities for membrane technology in the future. Membrane materials with good thermal and chemical stability would allow their application in chemical processes, which are so far not extensively explored with membranes. This is the case of recovery of valuable products such as catalysts from reaction medium containing organic solvents. Membrane materials with better resistance to harsh cleaning treatments (chlorine, acid and alkali treatments) would increase the membrane life time in chemical separation and also in regular wastewater treatment, for which fouling is a serious problem. This would also facilitate the use of membranes for a separation task of growing importance, the treatment of produced water in the oil and gas industry.

In the energy sector, membranes already play a role in the production of biofuels. They are also the key components in different energy conversion or storage technologies, whose performance and competition with other technologies depend on the availability of better materials. For fuel cells proton conductivity even above 100°C and low humidity aligned to high chemical and oxidative resistance are important specifications to achieve. There has been important achievement and innovative approaches in this area in the last decade. More incremental improvements in membranes for fuel have been reported in recent years. The technology as a

whole has progressed becoming more mature for market penetration. A combination of other characteristics is needed for battery separators, a sector which has grown faster than fuel cell. Longer term options, such as osmotic power, are also on the horizon. However, osmotic power requires significant advances in the membrane technology, while maintaining cost and competitiveness. In summary there is a large number of open challenges and opportunities for new materials in membrane technology. With the advent of better materials in this area, new sustainable technologies and separation processes will be implemented, a task for the current and new generation of material scientists.

Abbreviations

AEM	: anion exchange membrane
AMPS	: 2-acryloylamido-2-methylpropanesulfonic acid
AnMBR	: anaerobic membrane bioreactors
BOD	: biochemical oxygen demand
CAS	: conventional activated sludge
CHP	: combined heat and power
CMS	: carbon molecular sieve
CNT	: carbon nanotube
COF	: covalent organic framework
DABCO	: 1,4-diazabicyclo-2,2,2-octane
DMFC	: direct methanol fuel cell
ED	: electrodialysis
EDC	: endocrine disrupting chemical
EDR	: electrodialysis reversal

FAME	: fatty acid methyl ester
FCD	: fixed charge density
FO	: forward osmosis
HEV	: hybrid electric vehicle
HFP	: hexafluoropropylene
ICD	: ionic complexation degree
ICP	: internal concentration polarization
IEC	: ion exchange capacity
IEM	: ion exchange membrane
LbL	: layer-by-layer
LIB	: lithium ion batteries
MBR	: membrane reactor
MD	: membrane distillation
MMM	: mixed matrix membrane
MOF	: metal-organic framework
NF	: nanofiltration
NIPS	: non-solvent induced phase separation
PEMFC	: polymer electrolyte membrane fuel cell
RED	: reverse electrodialysis
REE	: rare earth element
RO	: reverse osmosis
PAFC	: phosphoric acid fuel cell
PAN	: polyacrylonitrile

PBI	: polybenzimidazole
PDA	: polydopamine
PDMS	: polydimethylsiloxane
PE	: polyethylene
PECH	: polyepichlorohydrin
PEM	: polymer electrolyte membrane
PES	: poly(ether sulfone)
PET	: poly(ethylene terephthalate)
PhAC	: pharmaceutically active compound
PMMA	: poly(methyl methacrylate)
POP	: persistent organic compound
PP	: polypropylene
PPO	: poly(2,6-dimethyl-1,4-phenylene oxide)
PRO	: pressure-retarded osmosis
PS	: polystyrene
PTFE	: polytetrafluorethylene
PV	: pervaporation
PVA	: polyvinyl alcohol
PVC	: polyvinylchloride
PVDF	: poly(vinylidene fluoride)
SDI	: silt density index
SPARRO	: slurry precipitation and recycle reverse osmosis
SRO	: seeded reverse osmosis

SSA	: sulfosuccinic acid
TDS	: total dissolved solid
TFC	: thin-film composite
TFE	: tetrafluoroethylene
TFN	: thin-film nanocomposite
TIPS	: thermal induced phase separation
TOC	: total organic compound
TrOC	: trace organic contaminant
TRO	: tubular reverse osmosis
TSS	: total suspended solid
UF	: ultrafiltration
VOC	: volatile organic compound

References

- [1] N.H. Afgan, Sustainability concept for energy, water and environment systems, in: Sustainable energy technologies, Springer, 2008, pp. 25-49.
- [2] A. Evans, V. Strezov, T.J. Evans, Assessment of sustainability indicators for renewable energy technologies, Renewable and sustainable energy reviews, 13 (2009) 1082-1088.
- [3] N. Ghaffour, The challenge of capacity-building strategies and perspectives for desalination for sustainable water use in MENA, Desalination and Water Treatment, 5 (2009) 48-53.
- [4] G.W.I.G.I. DesalData), Market profile and desalination markets, 2009–2012 yearbooks and GWI website, <http://www.desaldata.com/>, in.
- [5] A. El-Ghonemy, RETRACTED: Future sustainable water desalination technologies for the Saudi Arabia: A review, Renewable and Sustainable Energy Reviews, 16 (2012) 6566-6597.
- [6] N. Ghaffour, T.M. Missimer, G.L. Amy, Technical review and evaluation of the economics of water desalination: current and future challenges for better water supply sustainability, Desalination, 309 (2013) 197-207.
- [7] P.S. Goh, A.F. Ismail, Review: is interplay between nanomaterial and membrane technology the way forward for desalination?, Journal of Chemical Technology and Biotechnology, (2014).
- [8] I.C. Karagiannis, P.G. Soldatos, Water desalination cost literature: review and assessment, Desalination, 223 (2008) 448-456.
- [9] K.P. Lee, T.C. Arnot, D. Mattia, A review of reverse osmosis membrane materials for desalination—Development to date and future potential, Journal of Membrane Science, 370 (2011) 1-22.
- [10] D.S. Likhachev, F.-C. Li, Large-scale water desalination methods: a review and new perspectives, Desalination and Water Treatment, 51 (2013) 2836-2849.

- [11] T. Matsuura, Progress in membrane science and technology for seawater desalination—a review, *Desalination*, 134 (2001) 47-54.
- [12] J.E. Miller, Review of water resources and desalination technologies, Sandia National Labs Unlimited Release Report SAND-2003-0800, (2003).
- [13] M. Nair, D. Kumar, Water desalination and challenges: The Middle East perspective: a review, *Desalination and Water Treatment*, 51 (2013) 2030-2040.
- [14] B.L. Pangarkar, M.G. Sane, M. Guddad, Reverse osmosis and membrane distillation for desalination of groundwater: a review, *International Scholarly Research Notices*, 2011 (2011).
- [15] L. Weinrich, C.N. Haas, M.W. LeChevallier, Recent advances in measuring and modeling reverse osmosis membrane fouling in seawater desalination: a review, *Journal of Water Reuse and Desalination*, 3 (2013) 85-101.
- [16] Z. Khatib, P. Verbeek, Water to value-produced water management for sustainable field development of mature and green fields, in: SPE International Conference on Health Safety and Environment in Oil and Gas Exploration and Production, Society of Petroleum Engineers, 2002.
- [17] M. Çakmakce, N. Kayaalp, I. Koyuncu, Desalination of produced water from oil production fields by membrane processes, *Desalination*, 222 (2008) 176-186.
- [18] C.H. Webb, L. Nagghappan, G. Smart, J. Hoblitzell, R. Franks, Desalination of oilfield-produced water at the San Ardo water reclamation facility, CA, in: SPE Western Regional Meeting, Society of Petroleum Engineers, 2009.
- [19] Y. He, Z.-W. Jiang, Technology review: treating oilfield wastewater, *Filtration & Separation*, 45 (2008) 14-16.
- [20] N. Liu, J. Lu, L. Li, R. Lee, Factors determining the reverse osmosis performance of zeolite membranes on produced water purification, in: SPE International Symposium on Oilfield Chemistry, Houston, Texas, USA, 2007.
- [21] A. Zaidi, K. Simms, S. Kok, The use of micro/ultrafiltration for the removal of oil and suspended solids from oilfield brines, *Water Science & Technology*, 25 (1992) 163-176.
- [22] P. Xu, J.E. Drewes, D. Heil, Beneficial use of co-produced water through membrane treatment: technical-economic assessment, *Desalination*, 225 (2008) 139-155.
- [23] D.B. Burnett, Potential for beneficial use of oil and gas produced water, Global Petroleum Institute, Texas Water Resources Institute, (2004) 1-11.
- [24] A. Chen, J. Flynn, R. Cook, A. Casaday, Removal of oil, grease, and suspended solids from produced water with ceramic crossflow microfiltration, *SPE Production Engineering*, 6 (1991) 131-136.
- [25] K.S. Ashaghi, M. Ebrahimi, P. Czermak, Ceramic ultra-and nanofiltration membranes for oilfield produced water treatment: a mini review, *The Open Environmental Journal*, (2007).
- [26] M. Bader, Seawater versus produced water in oil-fields water injection operations, *Desalination*, 208 (2007) 159-168.
- [27] J.M. Lee, T.C. Frankiewicz, Treatment of produced water with an ultrafiltration (UF) membrane—a field trial, in: SPE Annual Technical Conference and Exhibition, Society of Petroleum Engineers, 2005.
- [28] T. Bilstad, E. Espedal, Membrane separation of produced water, *Water Science and Technology*, 34 (1996) 239-246.
- [29] Y.S. Li, L. Yan, C.B. Xiang, L.J. Hong, Treatment of oily wastewater by organic–inorganic composite tubular ultrafiltration (UF) membranes, *Desalination*, 196 (2006) 76-83.
- [30] K.L. Hickenbottom, N.T. Hancock, N.R. Hutchings, E.W. Appleton, E.G. Beaudry, P. Xu, T.Y. Cath, Forward osmosis treatment of drilling mud and fracturing wastewater from oil and gas operations, *Desalination*, 312 (2013) 60-66.
- [31] D.L. Shaffer, L.H. Arias Chavez, M. Ben-Sasson, S. Romero-Vargas Castrillón, N.Y. Yip, M. Elimelech, Desalination and reuse of high-salinity shale gas produced water: drivers, technologies, and future directions, *Environmental science & technology*, 47 (2013) 9569-9583.

- [32] G. Breit, J. Otton, Produced waters database, Database]. United States Geological Survey. Available: <http://energy.cr.usgs.gov/prov/prodwat/data2.htm> [2002, June 12], (2002).
- [33] A. Alklaibi, N. Lior, Membrane-distillation desalination: status and potential, *Desalination*, 171 (2005) 111-131.
- [34] E. Curcio, E. Drioli, Membrane distillation and related operations—a review, *Separation and Purification Reviews*, 34 (2005) 35-86.
- [35] M.K. Souhaimi, T. Matsuura, *Membrane Distillation: Principles and Applications*, Elsevier, 2011.
- [36] A. Alkudhiri, N. Darwish, N. Hilal, Membrane distillation: A comprehensive review, *Desalination*, 287 (2012) 2-18.
- [37] P. Wang, T.-S. Chung, Recent advances in membrane distillation processes: Membrane development, configuration design and application exploring, *Journal of Membrane Science*, 474 (2015) 39-56.
- [38] S. Al-Obaidani, E. Curcio, F. Macedonio, G. Di Profio, H. Al-Hinai, E. Drioli, Potential of membrane distillation in seawater desalination: thermal efficiency, sensitivity study and cost estimation, *Journal of Membrane Science*, 323 (2008) 85-98.
- [39] T.Y. Cath, A.E. Childress, M. Elimelech, Forward osmosis: principles, applications, and recent developments, *Journal of membrane science*, 281 (2006) 70-87.
- [40] Q. Ge, M. Ling, T.-S. Chung, Draw solutions for forward osmosis processes: developments, challenges, and prospects for the future, *Journal of Membrane Science*, 442 (2013) 225-237.
- [41] M. MingáLing, Facile synthesis of thermosensitive magnetic nanoparticles as “smart” draw solutes in forward osmosis, *Chemical communications*, 47 (2011) 10788-10790.
- [42] D. Li, X. Zhang, G.P. Simon, H. Wang, Forward osmosis desalination using polymer hydrogels as a draw agent: Influence of draw agent, feed solution and membrane on process performance, *Water research*, 47 (2013) 209-215.
- [43] Q. Ge, J. Su, G.L. Amy, T.-S. Chung, Exploration of polyelectrolytes as draw solutes in forward osmosis processes, *Water research*, 46 (2012) 1318-1326.
- [44] D.L. Shaffer, N.Y. Yip, J. Gilron, M. Elimelech, Seawater desalination for agriculture by integrated forward and reverse osmosis: Improved product water quality for potentially less energy, *Journal of membrane science*, 415 (2012) 1-8.
- [45] R.W. Holloway, A.E. Childress, K.E. Dennett, T.Y. Cath, Forward osmosis for concentration of anaerobic digester centrate, *Water Research*, 41 (2007) 4005-4014.
- [46] C.R. Martinetti, A.E. Childress, T.Y. Cath, High recovery of concentrated RO brines using forward osmosis and membrane distillation, *Journal of Membrane Science*, 331 (2009) 31-39.
- [47] M. Elimelech, W.A. Phillip, The future of seawater desalination: energy, technology, and the environment, *Science*, 333 (2011) 712-717.
- [48] Y.C. Kim, S.-J. Park, Experimental study of a 4040 spiral-wound forward-osmosis membrane module, *Environmental science & technology*, 45 (2011) 7737-7745.
- [49] J.R. McCutcheon, R.L. McGinnis, M. Elimelech, A novel ammonia—carbon dioxide forward (direct) osmosis desalination process, *Desalination*, 174 (2005) 1-11.
- [50] R.A. Neff, Solvent extractor, in, Google Patents, 1964.
- [51] C. Boo, Y.F. Khalil, M. Elimelech, Performance evaluation of trimethylamine—carbon dioxide thermolytic draw solution for engineered osmosis, *Journal of Membrane Science*, 473 (2015) 302-309.
- [52] A.D. Wilson, F.F. Stewart, M.L. Stone, Methods and systems for treating liquids using switchable solvents, in, Google Patents, 2012.
- [53] M.L. Stone, C. Rae, F.F. Stewart, A.D. Wilson, Switchable polarity solvents as draw solutes for forward osmosis, *Desalination*, 312 (2013) 124-129.
- [54] J.M. Beltrán, S. Koo-Oshima, Water desalination for agricultural applications, *FAO Land and water discussion paper*, 5 (2006) 48.

- [55] O. Barron, R. Ali, G. Hodgson, D. Smith, E. Qureshi, D. McFarlane, E. Campos, D. Zarzo, Feasibility assessment of desalination application in Australian traditional agriculture, *Desalination*, (2014).
- [56] D. Zarzo, E. Campos, P. Terrero, Spanish experience in desalination for agriculture, *Desalination and Water Treatment*, 51 (2013) 53-66.
- [57] S. Burn, M. Hoang, D. Zarzo, F. Olewniak, E. Campos, B. Bolto, O. Barron, Desalination techniques—A review of the opportunities for desalination in agriculture, *Desalination*, 364 (2015) 2-16.
- [58] M. Tester, P. Langridge, Breeding technologies to increase crop production in a changing world, *Science*, 327 (2010) 818-822.
- [59] Desaldata, <http://www.idadesal.org/publications/desaldata-com/> 2012.
- [60] M.J.R. Guerreiro, M.d.M. de la Fuente, E.M. Camacho, Toxicidad del boro en las plantas, *Encuentros en la Biología*, (2002) 1.
- [61] R. Dunne, Water Water Everywhere and not a Drop to Drink, Nor do I Know its Whereabouts, *Water in Mineral Processing*, (2012) 1.
- [62] G. Juby, Membrane desalination of service water from gold mines, *Journal of the South African Institute of Mining and Metallurgy*, 92 (1992) 69.
- [63] L. Haig-Smillie, Sea water flotation, in: *Proceedings of the 6th Annual Meeting of Canadian Mineral Processors*, 1974, pp. 263-281.
- [64] G. Poling, D. Ellis, Importance of geochemistry: The black angel lead - zinc mine, Greenland, *Marine georesources & geotechnology*, 13 (1995) 101-118.
- [65] J. Weirtz, When best water use efficiency is not enough, what can the mining industry do?, in: *Water in Mining 2009 Conference Proceedings*, Australasian Institute of Mining and Metallurgy Perth. Carlton (Australia), 2009, pp. 15-17.
- [66] J. Chadwick, Copper Recovery, *Mining Magazine*, (2009) 23-30.
- [67] V. Lévy, R. Fabre, B. Boebel, C. Hertle, Water use in the mining industry—threats and opportunities, *Proceedings of Water in Mining*, (2006).
- [68] R. Harries, A field trial of seeded reverse osmosis for the desalination of a scaling-type mine water, *Desalination*, 56 (1985) 227-236.
- [69] G. Du Plessis, J. Swartz, Tubular Reverse Osmosis treatment of Secunda mine water: a pilot plant investigation, *Water Science & Technology*, 25 (1992) 193-201.
- [70] R. Howell, A review of sulfate removal options for mine waters, *Proceedings of Mine Water*, (2004) 75-88.
- [71] G. Juby, W. Pulles, Evaluation of Electrodialysis reversal for desalination of brackish mine water, *WRC Report*, 179 (1990) 1190.
- [72] M. Sivakumar, M. Ramezani-pour, G. O'Halloran, Mine water treatment using a vacuum membrane distillation system, *APCBEE Procedia*, 5 (2013) 157-162.
- [73] G. Juby, C. Schutte, J. Van Leeuwen, Desalination of calcium sulphate scaling mine water: Design and operation of the SPARRO process, *Water S. A.*, 22 (1996) 161-172.
- [74] W. Pulles, G. Juby, R. Busby, Development of the slurry precipitation and recycle reverse osmosis (SPARRO) technology for desalinating scaling mine waters, *Water Science & Technology*, 25 (1992) 177-192.
- [75] M. Barakat, New trends in removing heavy metals from industrial wastewater, *Arabian Journal of Chemistry*, 4 (2011) 361-377.
- [76] T. Jeppesen, L. Shu, G. Keir, V. Jegatheesan, Metal recovery from reverse osmosis concentrate, *Journal of Cleaner Production*, 17 (2009) 703-707.
- [77] J. Le Dirach, S. Nisan, C. Poletiko, Extraction of strategic materials from the concentrated brine rejected by integrated nuclear desalination systems, *Desalination*, 182 (2005) 449-460.
- [78] M.C. Achilleas Tsamis, Recovery of Rare Earths from Electronic Wastes: An Opportunity for High-Tech SMEs, in, 2015.

- [79] F. Fu, Q. Wang, Removal of heavy metal ions from wastewaters: a review, *Journal of Environmental Management*, 92 (2011) 407-418.
- [80] X. Chai, G. Chen, Y. Po-Lock, Y. Mi, Pilot scale membrane separation of electroplating waste water by reverse osmosis, *Journal of Membrane Science*, 123 (1997) 235-242.
- [81] T.A. Kurniawan, G.Y. Chan, W.-H. Lo, S. Babel, Physico-chemical treatment techniques for wastewater laden with heavy metals, *Chemical engineering journal*, 118 (2006) 83-98.
- [82] R. Abhanga, K. Wanib, V. Patilc, B. Pangarkara, S. Parjanea, Nanofiltration for Recovery of Heavy Metal Ions from Waste Water-A Review, *Liver*, 1 (2013) 0.60-65.60.
- [83] J. Landaburu-Aguirre, V. García, E. Pongrácz, R.L. Keiski, The removal of zinc from synthetic wastewaters by micellar-enhanced ultrafiltration: statistical design of experiments, *Desalination*, 240 (2009) 262-269.
- [84] X. Li, G.-M. Zeng, J.-H. Huang, C. Zhang, Y.-Y. Fang, Y.-H. Qu, F. Luo, D. Lin, H.-L. Liu, Recovery and reuse of surfactant SDS from a MEUF retentate containing Cd 2+ or Zn 2+ by ultrafiltration, *Journal of Membrane Science*, 337 (2009) 92-97.
- [85] E. Samper, M. Rodríguez, M. De la Rubia, D. Prats, Removal of metal ions at low concentration by micellar-enhanced ultrafiltration (MEUF) using sodium dodecyl sulfate (SDS) and linear alkylbenzene sulfonate (LAS), *Separation and Purification Technology*, 65 (2009) 337-342.
- [86] M.K. Aroua, F.M. Zuki, N.M. Sulaiman, Removal of chromium ions from aqueous solutions by polymer-enhanced ultrafiltration, *Journal of Hazardous Materials*, 147 (2007) 752-758.
- [87] H.-J. Kim, K. Baek, B.-K. Kim, J.-W. Yang, Humic substance-enhanced ultrafiltration for removal of cobalt, *Journal of hazardous materials*, 122 (2005) 31-36.
- [88] J. Labanda, M.S. Khaidar, J. Llorens, Feasibility study on the recovery of chromium (III) by polymer enhanced ultrafiltration, *Desalination*, 249 (2009) 577-581.
- [89] R. Molinari, T. Poerio, P. Argurio, Selective separation of copper (II) and nickel (II) from aqueous media using the complexation-ultrafiltration process, *Chemosphere*, 70 (2008) 341-348.
- [90] K. Trivunac, S. Stevanovic, Removal of heavy metal ions from water by complexation-assisted ultrafiltration, *Chemosphere*, 64 (2006) 486-491.
- [91] B. Chan, A. Dudeney, Reverse osmosis removal of arsenic residues from bioleaching of refractory gold concentrates, *Minerals Engineering*, 21 (2008) 272-278.
- [92] U. Ipek, Removal of Ni (II) and Zn (II) from an aqueous solution by reverse osmosis, *Desalination*, 174 (2005) 161-169.
- [93] M. Mohsen-Nia, P. Montazeri, H. Modarress, Removal of Cu 2+ and Ni 2+ from wastewater with a chelating agent and reverse osmosis processes, *Desalination*, 217 (2007) 276-281.
- [94] L. ZHANG, W. Yanjun, Q. Xiaoyan, L. Zhenshan, N. Jinren, Mechanism of combination membrane and electro-winning process on treatment and remediation of Cu 2+ polluted water body, *Journal of Environmental Sciences*, 21 (2009) 764-769.
- [95] Z. Murthy, L.B. Chaudhari, Application of nanofiltration for the rejection of nickel ions from aqueous solutions and estimation of membrane transport parameters, *Journal of hazardous materials*, 160 (2008) 70-77.
- [96] M. Muthukrishnan, B. Guha, Effect of pH on rejection of hexavalent chromium by nanofiltration, *Desalination*, 219 (2008) 171-178.
- [97] K.Y. Wang, T.-S. Chung, Fabrication of polybenzimidazole (PBI) nanofiltration hollow fiber membranes for removal of chromate, *Journal of Membrane Science*, 281 (2006) 307-315.
- [98] W.-P. Zhu, S.-P. Sun, J. Gao, F.-J. Fu, T.-S. Chung, Dual-layer polybenzimidazole/polyethersulfone (PBI/PES) nanofiltration (NF) hollow fiber membranes for heavy metals removal from wastewater, *Journal of Membrane Science*, 456 (2014) 117-127.
- [99] J. Gao, S.-P. Sun, W.-P. Zhu, T.-S. Chung, Polyethyleneimine (PEI) cross-linked P84 nanofiltration (NF) hollow fiber membranes for Pb 2+ removal, *Journal of Membrane Science*, 452 (2014) 300-310.

- [100] A.L. Ahmad, B.S. Ooi, A study on acid reclamation and copper recovery using low pressure nanofiltration membrane, *Chemical Engineering Journal*, 156 (2010) 257-263.
- [101] E. Cséfalvay, V. Pauer, P. Mizsey, Recovery of copper from process waters by nanofiltration and reverse osmosis, *Desalination*, 240 (2009) 132-142.
- [102] A. Figoli, A. Cassano, A. Criscuoli, M.S.I. Mozumder, M.T. Uddin, M.A. Islam, E. Drioli, Influence of operating parameters on the arsenic removal by nanofiltration, *Water research*, 44 (2010) 97-104.
- [103] C.M. Nguyen, S. Bang, J. Cho, K.-W. Kim, Performance and mechanism of arsenic removal from water by a nanofiltration membrane, *Desalination*, 245 (2009) 82-94.
- [104] P. Eriksson, Nanofiltration extends the range of membrane filtration, *Environmental Progress*, 7 (1988) 58-62.
- [105] N. Cicek, Franco, 1. P.; Suidan, MT; and Urbain, V.(1998) Using a Membrane Bioreactor To Reclaim Wastewater, *J. Am. Water Works Assoc*, 90.
- [106] J. Lozier, A. Fernandez, B. Hines, K. Carns, Using a membrane bioreactor/reverse osmosis system for indirect water reuse, in: *Proc. 2000 AWWA Water Reuse Conf.*, San Antonio, Texas, 2000.
- [107] T. Guihe, K. Kiran, V. Bala, H.O. Maung, S. Harry, Membrane bioreactor for water reclamation in Singapore, *Water Practice & Technology*, 3 (2008).
- [108] N. Cicek, A review of membrane bioreactors and their potential application in the treatment of agricultural wastewater, *Canadian Biosystems Engineering*, 45 (2003) 6.37-36.37.
- [109] S. Rosenberger, U. Krüger, R. Witzig, W. Manz, U. Szewzyk, M. Kraume, Performance of a bioreactor with submerged membranes for aerobic treatment of municipal waste water, *Water Research*, 36 (2002) 413-420.
- [110] K.-H. Ahn, H.-Y. Cha, K.-G. Song, Retrofitting municipal sewage treatment plants using an innovative membrane-bioreactor system, *Desalination*, 124 (1999) 279-286.
- [111] X.-J. Fan, V. Urbain, Y. Qian, J. Manem, Nitrification and mass balance with a membrane bioreactor for municipal wastewater treatment, *Water Science and Technology*, 34 (1996) 129-136.
- [112] E. Muller, A. Stouthamer, H.W.v. van Verseveld, D. Eikelboom, Aerobic domestic waste water treatment in a pilot plant with complete sludge retention by cross-flow filtration, *Water Research*, 29 (1995) 1179-1189.
- [113] W. Lorenz, T. Cunningham, J.P. Penny, Phosphorus removal in a membrane reactor system: A full-scale wastewater demonstration study, *Proceedings of the Water Environment Federation*, 2002 (2002) 406-414.
- [114] J. Manam, E. Sanderson, Membrane bioreactors In: *Water Treatment: Membrane Process*, Megaw Hill (Ed), (1996).
- [115] A. Parker, Membrane technology plays key role in waterless hygienic toilet, *Membrane Technology*, 2014 (2014) 8.
- [116] E. Perez Lopez, Design and testing of a novel human-powered generator device as a backup solution to power Cranfield' s Nano-Membrane Toilet, (2014).
- [117] A. Hogetsu, T. Ishikawa, M. Yoshikawa, T. Tanabe, S. Yudate, J. Sawada, High rate anaerobic digestion of wool scouring wastewater in a digester combined with membrane filter, *Water Science & Technology*, 25 (1992) 341-350.
- [118] K. Minami, A trial of high performance anaerobic treatment on wastewater from a kraft pulp mill, *Desalination*, 98 (1994) 273-283.
- [119] M. Knoblock, P. Sutton, P. Mishra, K. Gupta, A. Janson, Membrane biological reactor system for treatment of oily wastewaters, *Water Environment Research*, (1994) 133-139.
- [120] R. Zaloum, S. Lessard, D. Mourato, J. Carriere, Membrane bioreactor treatment of oily wastes from a metal transformation mill, *Water Science and Technology*, 30 (1994) 21-27.
- [121] W. Ross, J. Barnard, N. Strohwalld, C. Grobler, J. Sanetra, Practical application of the ADUF process to the full-scale treatment of a maize-processing effluent, *Water Science & Technology*, 25 (1992) 27-39.

- [122] L.D. Nghiem, A. Schäfer, Trace contaminant removal with nanofiltration, (2004).
- [123] F.I. Hai, L.N. Nguyen, L.D. Nghiem, B.-Q. Liao, I. Koyuncu, W.E. Price, Trace Organic Contaminants Removal by Combined Processes for Wastewater Reuse, (2014).
- [124] M. Cirja, P. Ivashechkin, A. Schäfer, P.F. Corvini, Factors affecting the removal of organic micropollutants from wastewater in conventional treatment plants (CTP) and membrane bioreactors (MBR), *Reviews in Environmental Science and Bio/Technology*, 7 (2008) 61-78.
- [125] O. H. Jones, N. Voulvoulis, J. Lester, Human pharmaceuticals in wastewater treatment processes, *Critical Reviews in Environmental Science and Technology*, 35 (2005) 401-427.
- [126] F.I. Hai, N. Tadkaew, J.A. McDonald, S.J. Khan, L.D. Nghiem, Is halogen content the most important factor in the removal of halogenated trace organics by MBR treatment?, *Bioresource technology*, 102 (2011) 6299-6303.
- [127] K. Kimura, H. Hara, Y. Watanabe, Removal of pharmaceutical compounds by submerged membrane bioreactors (MBRs), *Desalination*, 178 (2005) 135-140.
- [128] N. Tadkaew, F.I. Hai, J.A. McDonald, S.J. Khan, L.D. Nghiem, Removal of trace organics by MBR treatment: the role of molecular properties, *Water research*, 45 (2011) 2439-2451.
- [129] S. Castiglioni, R. Bagnati, R. Fanelli, F. Pomati, D. Calamari, E. Zuccato, Removal of pharmaceuticals in sewage treatment plants in Italy, *Environmental Science & Technology*, 40 (2006) 357-363.
- [130] F.I. Hai, K. Tessmer, L.N. Nguyen, J. Kang, W.E. Price, L.D. Nghiem, Removal of micropollutants by membrane bioreactor under temperature variation, *Journal of Membrane Science*, 383 (2011) 144-151.
- [131] N.M. Vieno, T. Tuhkanen, L. Kronberg, Seasonal variation in the occurrence of pharmaceuticals in effluents from a sewage treatment plant and in the recipient water, *Environmental science & technology*, 39 (2005) 8220-8226.
- [132] A.S. Stasinakis, S. Kotsifa, G. Gatidou, D. Mamais, Diuron biodegradation in activated sludge batch reactors under aerobic and anoxic conditions, *water research*, 43 (2009) 1471-1479.
- [133] N. Tadkaew, M. Sivakumar, S.J. Khan, J.A. McDonald, L.D. Nghiem, Effect of mixed liquor pH on the removal of trace organic contaminants in a membrane bioreactor, *Bioresource technology*, 101 (2010) 1494-1500.
- [134] T. Urase, C. Kagawa, T. Kikuta, Factors affecting removal of pharmaceutical substances and estrogens in membrane separation bioreactors, *Desalination*, 178 (2005) 107-113.
- [135] C. Zwiener, F. Frimmel, Short-term tests with a pilot sewage plant and biofilm reactors for the biological degradation of the pharmaceutical compounds clofibric acid, ibuprofen, and diclofenac, *Science of the Total Environment*, 309 (2003) 201-211.
- [136] S. Kim, P. Eichhorn, J.N. Jensen, A.S. Weber, D.S. Aga, Removal of antibiotics in wastewater: effect of hydraulic and solid retention times on the fate of tetracycline in the activated sludge process, *Environmental science & technology*, 39 (2005) 5816-5823.
- [137] M. Bernhard, J. Müller, T.P. Knepper, Biodegradation of persistent polar pollutants in wastewater: comparison of an optimised lab-scale membrane bioreactor and activated sludge treatment, *Water research*, 40 (2006) 3419-3428.
- [138] M. Clara, N. Kreuzinger, B. Strenn, O. Gans, H. Kroiss, The solids retention time—a suitable design parameter to evaluate the capacity of wastewater treatment plants to remove micropollutants, *Water research*, 39 (2005) 97-106.
- [139] N. Kreuzinger, M. Clara, B. Strenn, H. Kroiss, Relevance of the sludge retention time (SRT) as design criteria for wastewater treatment plants for the removal of endocrine disruptors and pharmaceuticals from wastewater, *Water Science & Technology*, 50 (2004) 149-156.
- [140] C. Abegglen, A. Joss, C.S. McArdell, G. Fink, M.P. Schlüsener, T.A. Ternes, H. Siegrist, The fate of selected micropollutants in a single-house MBR, *Water research*, 43 (2009) 2036-2046.

- [141] M. Clara, B. Strenn, O. Gans, E. Martinez, N. Kreuzinger, H. Kroiss, Removal of selected pharmaceuticals, fragrances and endocrine disrupting compounds in a membrane bioreactor and conventional wastewater treatment plants, *Water research*, 39 (2005) 4797-4807.
- [142] F.I. Hai, X. Li, W.E. Price, L.D. Nghiem, Removal of carbamazepine and sulfamethoxazole by MBR under anoxic and aerobic conditions, *Bioresource technology*, 102 (2011) 10386-10390.
- [143] A. Joss, H. Andersen, T. Ternes, P.R. Richle, H. Siegrist, Removal of estrogens in municipal wastewater treatment under aerobic and anaerobic conditions: consequences for plant optimization, *Environmental Science & Technology*, 38 (2004) 3047-3055.
- [144] Y. Kiso, A. Mizuno, R.A.A. binti Othman, Y.-J. Jung, A. Kumano, A. Arijji, Rejection properties of pesticides with a hollow fiber NF membrane (HNF-1), *Desalination*, 143 (2002) 147-157.
- [145] Y. Kiso, Y. Sugiura, T. Kitao, K. Nishimura, Effects of hydrophobicity and molecular size on rejection of aromatic pesticides with nanofiltration membranes, *Journal of Membrane Science*, 192 (2001) 1-10.
- [146] M. Reinhard, N.L. Goodman, P.L. McCarty, D.G. Argo, Removing trace organics by reverse osmosis using cellulose acetate and polyamide membranes, *Journal (American Water Works Association)*, (1986) 163-174.
- [147] P. Berg, G. Hagmeyer, R. Gimbel, Removal of pesticides and other micropollutants by nanofiltration, *Desalination*, 113 (1997) 205-208.
- [148] R. Boussahel, A. Montiel, M. Baudu, Effects of organic and inorganic matter on pesticide rejection by nanofiltration, *Desalination*, 145 (2002) 109-114.
- [149] B. Van der Bruggen, J. Schaep, W. Maes, D. Wilms, C. Vandecasteele, Nanofiltration as a treatment method for the removal of pesticides from ground waters, *Desalination*, 117 (1998) 139-147.
- [150] K.M. Agbekodo, B. Legube, S. Dard, Atrazine and simazine removal mechanisms by nanofiltration: influence of natural organic matter concentration, *Water Research*, 30 (1996) 2535-2542.
- [151] L. Nghiem, A. Manis, K. Soldenhoff, A. Schäfer, Estrogenic hormone removal from wastewater using NF/RO membranes, *Journal of Membrane Science*, 242 (2004) 37-45.
- [152] L.D. Nghiem, A.I. Schäfer, M. Elimelech, Removal of natural hormones by nanofiltration membranes: measurement, modeling, and mechanisms, *Environmental Science & Technology*, 38 (2004) 1888-1896.
- [153] K. Agenson, J. Oh, T. Kikuta, T. Urase, Rejection mechanisms of plastic additives and natural hormones in drinking water treated by nanofiltration, *Water Supply*, 3 (2003) 311-319.
- [154] S. Weber, M. Gallenkemper, T. Melin, W. Dott, J. Hollender, Efficiency of nanofiltration for the elimination of steroids from water, *Water Science & Technology*, 50 (2004) 9-14.
- [155] T.A. Ternes, M. Meisenheimer, D. McDowell, F. Sacher, H.-J. Brauch, B. Haist-Gulde, G. Preuss, U. Wilme, N. Zulei-Seibert, Removal of pharmaceuticals during drinking water treatment, *Environmental science & technology*, 36 (2002) 3855-3863.
- [156] E.M. Golet, A.C. Alder, W. Giger, Environmental exposure and risk assessment of fluoroquinolone antibacterial agents in wastewater and river water of the Glatt Valley Watershed, Switzerland, *Environmental Science & Technology*, 36 (2002) 3645-3651.
- [157] T.A. Ternes, R. Hirsch, Occurrence and behavior of X-ray contrast media in sewage facilities and the aquatic environment, *Environmental science & technology*, 34 (2000) 2741-2748.
- [158] S.J. Khan, J.E. Ongerth, Modelling of pharmaceutical residues in Australian sewage by quantities of use and fugacity calculations, *Chemosphere*, 54 (2004) 355-367.
- [159] K. Kimura, G. Amy, J.E. Drewes, T. Heberer, T.-U. Kim, Y. Watanabe, Rejection of organic micropollutants (disinfection by-products, endocrine disrupting compounds, and pharmaceutically active compounds) by NF/RO membranes, *Journal of Membrane Science*, 227 (2003) 113-121.
- [160] S.P. Sun, T.A. Hatton, S.Y. Chan, T.-S. Chung, Novel thin-film composite nanofiltration hollow fiber membranes with double repulsion for effective removal of emerging organic matters from water, *Journal of Membrane Science*, 401 (2012) 152-162.

- [161] R.W. Holloway, J. Regnery, L.D. Nghiem, T.Y. Cath, Removal of trace organic chemicals and performance of a novel hybrid ultrafiltration-osmotic membrane bioreactor, *Environmental science & technology*, 48 (2014) 10859-10868.
- [162] T.Y. Cath, N.T. Hancock, C.D. Lundin, C. Hoppe-Jones, J.E. Drewes, A multi-barrier osmotic dilution process for simultaneous desalination and purification of impaired water, *Journal of Membrane Science*, 362 (2010) 417-426.
- [163] N.T. Hancock, P. Xu, D.M. Heil, C. Bellona, T.Y. Cath, Comprehensive bench-and pilot-scale investigation of trace organic compounds rejection by forward osmosis, *Environmental science & technology*, 45 (2011) 8483-8490.
- [164] R.V. Linares, V. Yangali-Quintanilla, Z. Li, G. Amy, Rejection of micropollutants by clean and fouled forward osmosis membrane, *Water research*, 45 (2011) 6737-6744.
- [165] J.H. Al-Rifai, H. Khabbaz, A.I. Schäfer, Removal of pharmaceuticals and endocrine disrupting compounds in a water recycling process using reverse osmosis systems, *Separation and Purification Technology*, 77 (2011) 60-67.
- [166] A.A. Alturki, N. Tadkaew, J.A. McDonald, S.J. Khan, W.E. Price, L.D. Nghiem, Combining MBR and NF/RO membrane filtration for the removal of trace organics in indirect potable water reuse applications, *Journal of Membrane Science*, 365 (2010) 206-215.
- [167] C. Bellona, J.E. Drewes, P. Xu, G. Amy, Factors affecting the rejection of organic solutes during NF/RO treatment—a literature review, *Water research*, 38 (2004) 2795-2809.
- [168] P. Cartagena, M. El Kaddouri, V. Cases, A. Trapote, D. Prats, Reduction of emerging micropollutants, organic matter, nutrients and salinity from real wastewater by combined MBR–NF/RO treatment, *Separation and Purification Technology*, 110 (2013) 132-143.
- [169] D. Dolar, M. Gros, S. Rodriguez-Mozaz, J. Moreno, J. Comas, I. Rodriguez-Roda, D. Barceló, Removal of emerging contaminants from municipal wastewater with an integrated membrane system, MBR–RO, *Journal of hazardous materials*, 239 (2012) 64-69.
- [170] L.N. Nguyen, F.I. Hai, J. Kang, W.E. Price, L.D. Nghiem, Removal of emerging trace organic contaminants by MBR-based hybrid treatment processes, *International Biodeterioration & Biodegradation*, 85 (2013) 474-482.
- [171] E. Sahar, I. David, Y. Gelman, H. Chikurel, A. Aharoni, R. Messalem, A. Brenner, The use of RO to remove emerging micropollutants following CAS/UF or MBR treatment of municipal wastewater, *Desalination*, 273 (2011) 142-147.
- [172] F. Zavisla, P. Drogui, A. Grasmick, A. Azais, M. Héran, Nanofiltration membrane bioreactor for removing pharmaceutical compounds, *Journal of Membrane Science*, 429 (2013) 121-129.
- [173] A. Achilli, T.Y. Cath, E.A. Marchand, A.E. Childress, The forward osmosis membrane bioreactor: a low fouling alternative to MBR processes, *Desalination*, 239 (2009) 10-21.
- [174] A. Alturki, J. McDonald, S.J. Khan, F.I. Hai, W.E. Price, L.D. Nghiem, Performance of a novel osmotic membrane bioreactor (OMBR) system: flux stability and removal of trace organics, *Bioresource technology*, 113 (2012) 201-206.
- [175] A.A. Alturki, J.A. McDonald, S.J. Khan, W.E. Price, L.D. Nghiem, M. Elimelech, Removal of trace organic contaminants by the forward osmosis process, *Separation and Purification Technology*, 103 (2013) 258-266.
- [176] J.L. Cartinella, T.Y. Cath, M.T. Flynn, G.C. Miller, K.W. Hunter, A.E. Childress, Removal of natural steroid hormones from wastewater using membrane contactor processes, *Environmental science & technology*, 40 (2006) 7381-7386.
- [177] F.I. Hai, K. Yamamoto, *Membrane biological reactors*, (2011).
- [178] W.C. Lay, Q. Zhang, J. Zhang, D. McDougald, C. Tang, R. Wang, Y. Liu, A.G. Fane, Effect of pharmaceuticals on the performance of a novel osmotic membrane bioreactor (OMBR), *Separation Science and Technology*, 47 (2012) 543-554.

- [179] J. Phattaranawik, A.G. Fane, A.C. Pasquier, W. Bing, A novel membrane bioreactor based on membrane distillation, *Desalination*, 223 (2008) 386-395.
- [180] S. Goh, J. Zhang, Y. Liu, A.G. Fane, Fouling and wetting in membrane distillation (MD) and MD-bioreactor (MDBR) for wastewater reclamation, *Desalination*, 323 (2013) 39-47.
- [181] T.M. LaPara, J.E. Alleman, Thermophilic aerobic biological wastewater treatment, *Water Research*, 33 (1999) 895-908.
- [182] K.C. Wijekoon, F.I. Hai, J. Kang, W.E. Price, T.Y. Cath, L.D. Nghiem, Rejection and fate of trace organic compounds (TrOCs) during membrane distillation, *Journal of Membrane Science*, 453 (2014) 636-642.
- [183] K.C. Wijekoon, F.I. Hai, J. Kang, W.E. Price, W. Guo, H.H. Ngo, T.Y. Cath, L.D. Nghiem, A novel membrane distillation–thermophilic bioreactor system: Biological stability and trace organic compound removal, *Bioresource technology*, 159 (2014) 334-341.
- [184] S. Judd, Principles and applications of membrane bioreactors in water and wastewater treatment. The MBR Book, in, Elsevier Ltd, UK, 2006.
- [185] P. Le-Clech, V. Chen, T.A. Fane, Fouling in membrane bioreactors used in wastewater treatment, *Journal of Membrane Science*, 284 (2006) 17-53.
- [186] J. Radjenović, M. Matošić, I. Mijatović, M. Petrović, D. Barceló, Membrane bioreactor (MBR) as an advanced wastewater treatment technology, in: *Emerging Contaminants from Industrial and Municipal Waste*, Springer, 2008, pp. 37-101.
- [187] K.M. Sombatsompop, Membrane fouling studies in suspended and attached growth membrane bioreactor systems, in, Asian Institute of Technology, 2007.
- [188] R. Ciora, P.K. Liu, Ceramic membranes for environmental related applications, *Fluid/Particle Sep. J.*, 15 (2003) 51.
- [189] B. Hofs, J. Ogier, D. Vries, E.F. Beerendonk, E.R. Cornelissen, Comparison of ceramic and polymeric membrane permeability and fouling using surface water, *Separation and Purification Technology*, 79 (2011) 365-374.
- [190] L. Jin, S.L. Ong, H.Y. Ng, Comparison of fouling characteristics in different pore-sized submerged ceramic membrane bioreactors, *Water research*, 44 (2010) 5907-5918.
- [191] J. Scott, K. Smith, A bioreactor coupled to a membrane to provide aeration and filtration in ice-cream factory wastewater remediation, *Water research*, 31 (1997) 69-74.
- [192] L. Defrance, M. Jaffrin, Comparison between filtrations at fixed transmembrane pressure and fixed permeate flux: application to a membrane bioreactor used for wastewater treatment, *Journal of Membrane Science*, 152 (1999) 203-210.
- [193] S. Holler, W. Trösch, Treatment of urban wastewater in a membrane bioreactor at high organic loading rates, *Journal of biotechnology*, 92 (2001) 95-101.
- [194] C. Wisniewski, A. Grasmick, Floc size distribution in a membrane bioreactor and consequences for membrane fouling, *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 138 (1998) 403-411.
- [195] K.-H. Choo, C.-H. Lee, Membrane fouling mechanisms in the membrane-coupled anaerobic bioreactor, *Water Research*, 30 (1996) 1771-1780.
- [196] J.A. Roberts, P.M. Sutton, P.N. Mishra, Application of the membrane biological reactor system for combined sanitary and industrial wastewater treatment, *International biodeterioration & biodegradation*, 46 (2000) 37-42.
- [197] W. Scholz, W. Fuchs, Treatment of oil contaminated wastewater in a membrane bioreactor, *Water Research*, 34 (2000) 3621-3629.
- [198] J. Mansouri, S. Harissou, V. Chen, Strategies for controlling biofouling in membrane filtration systems: challenges and opportunities, *Journal of Materials Chemistry*, 20 (2010) 4567-4586.

- [199] J. Pieracci, J.V. Crivello, G. Belfort, Increasing membrane permeability of UV-modified poly (ether sulfone) ultrafiltration membranes, *Journal of Membrane Science*, 202 (2002) 1-16.
- [200] B. Kaeselev, J. Pieracci, G. Belfort, Photoinduced grafting of ultrafiltration membranes: comparison of poly (ether sulfone) and poly (sulfone), *Journal of Membrane Science*, 194 (2001) 245-261.
- [201] S. Livazovic, Z. Li, A. Behzad, K.-V. Peinemann, S.P. Nunes, Cellulose multilayer membranes manufacture with ionic liquid, *Journal of Membrane Science*, 490 (2015) 282-293.
- [202] S.P. Nunes, M.L. Sforça, K.-V. Peinemann, Dense hydrophilic composite membranes for ultrafiltration, *Journal of Membrane Science*, 106 (1995) 49-56.
- [203] Y.-C. Chiang, Y. Chang, C.-J. Chuang, R.-C. Ruaan, A facile zwitterionization in the interfacial modification of low bio-fouling nanofiltration membranes, *Journal of Membrane Science*, 389 (2012) 76-82.
- [204] X. Fan, Y. Dong, Y. Su, X. Zhao, Y. Li, J. Liu, Z. Jiang, Improved performance of composite nanofiltration membranes by adding calcium chloride in aqueous phase during interfacial polymerization process, *Journal of Membrane Science*, 452 (2014) 90-96.
- [205] N. Ghaemi, S.S. Madaeni, A. Alizadeh, P. Daraei, M.M.S. Badieli, M. Falsafi, V. Vatanpour, Fabrication and modification of polysulfone nanofiltration membrane using organic acids: Morphology, characterization and performance in removal of xenobiotics, *Separation and Purification Technology*, 96 (2012) 214-228.
- [206] C. Kong, T. Kamada, T. Shintani, M. Kanezashi, T. Yoshioka, T. Tsuru, Enhanced performance of inorganic-polyamide nanocomposite membranes prepared by metal-alkoxide-assisted interfacial polymerization, *Journal of Membrane Science*, 366 (2011) 382-388.
- [207] X. Li, Y. Cao, H. Yu, G. Kang, X. Jie, Z. Liu, Q. Yuan, A novel composite nanofiltration membrane prepared with PHGH and TMC by interfacial polymerization, *Journal of Membrane Science*, 466 (2014) 82-91.
- [208] Y. Li, Y. Su, Y. Dong, X. Zhao, Z. Jiang, R. Zhang, J. Zhao, Separation performance of thin-film composite nanofiltration membrane through interfacial polymerization using different amine monomers, *Desalination*, 333 (2014) 59-65.
- [209] Y. Li, Y. Su, X. Zhao, R. Zhang, J. Zhao, X. Fan, Z. Jiang, Surface fluorination of polyamide nanofiltration membrane for enhanced antifouling property, *Journal of Membrane Science*, 455 (2014) 15-23.
- [210] J. Liu, L. Yu, Y. Zhang, Fabrication and characterization of positively charged hybrid ultrafiltration and nanofiltration membranes via the in-situ exfoliation of Mg/Al hydrotalcite, *Desalination*, 335 (2014) 78-86.
- [211] M. Namvar-Mahboub, M. Pakizeh, Development of a novel thin film composite membrane by interfacial polymerization on polyetherimide/modified SiO₂ support for organic solvent nanofiltration, *Separation and Purification Technology*, 119 (2013) 35-45.
- [212] M.A. Seman, M. Khayet, N. Hilal, Nanofiltration thin-film composite polyester polyethersulfone-based membranes prepared by interfacial polymerization, *Journal of membrane science*, 348 (2010) 109-116.
- [213] M.A. Seman, M. Khayet, N. Hilal, Development of antifouling properties and performance of nanofiltration membranes modified by interfacial polymerisation, *Desalination*, 273 (2011) 36-47.
- [214] P. Veerababu, B.B. Vyas, P.S. Singh, P. Ray, Limiting thickness of polyamide-polysulfone thin-film-composite nanofiltration membrane, *Desalination*, 346 (2014) 19-29.
- [215] X. Wei, X. Kong, J. Yang, G. Zhang, J. Chen, J. Wang, Structure influence of hyperbranched polyester on structure and properties of synthesized nanofiltration membranes, *Journal of Membrane Science*, 440 (2013) 67-76.

- [216] S. Zhang, M.H. Peh, Z. Thong, T.-S. Chung, Thin Film Interfacial Cross-Linking Approach To Fabricate a Chitosan Rejecting Layer over Poly (ether sulfone) Support for Heavy Metal Removal, *Industrial & Engineering Chemistry Research*, 54 (2014) 472-479.
- [217] N.-N. Bui, M.L. Lind, E.M. Hoek, J.R. McCutcheon, Electrospun nanofiber supported thin film composite membranes for engineered osmosis, *Journal of Membrane Science*, 385 (2011) 10-19.
- [218] P. Daraei, S.S. Madaeni, N. Ghaemi, E. Salehi, M.A. Khadivi, R. Moradian, B. Astinchap, Novel polyethersulfone nanocomposite membrane prepared by PANI/Fe₃O₄ nanoparticles with enhanced performance for Cu (II) removal from water, *Journal of Membrane Science*, 415 (2012) 250-259.
- [219] J. Hou, G. Dong, Y. Ye, V. Chen, Enzymatic degradation of bisphenol-A with immobilized laccase on TiO₂ sol-gel coated PVDF membrane, *Journal of Membrane Science*, 469 (2014) 19-30.
- [220] J. Mendret, M. Hatat-Fraile, M. Rivallin, S. Brosillon, Hydrophilic composite membranes for simultaneous separation and photocatalytic degradation of organic pollutants, *Separation and Purification Technology*, 111 (2013) 9-19.
- [221] J. Stawikowska, M.F. Jimenez-Solomon, Y. Bhole, A.G. Livingston, Nanoparticle contrast agents to elucidate the structure of thin film composite nanofiltration membranes, *Journal of Membrane Science*, 442 (2013) 107-118.
- [222] V. Vatanpour, M. Esmaeili, M.H.D.A. Farahani, Fouling reduction and retention increment of polyethersulfone nanofiltration membranes embedded by amine-functionalized multi-walled carbon nanotubes, *Journal of Membrane Science*, 466 (2014) 70-81.
- [223] V. Vatanpour, S.S. Madaeni, L. Rajabi, S. Zinadini, A.A. Derakhshan, Boehmite nanoparticles as a new nanofiller for preparation of antifouling mixed matrix membranes, *Journal of Membrane Science*, 401 (2012) 132-143.
- [224] J. Yin, E.-S. Kim, J. Yang, B. Deng, Fabrication of a novel thin-film nanocomposite (TFN) membrane containing MCM-41 silica nanoparticles (NPs) for water purification, *Journal of Membrane Science*, 423 (2012) 238-246.
- [225] H. Zhang, H. Mao, J. Wang, R. Ding, Z. Du, J. Liu, S. Cao, Mineralization-inspired preparation of composite membranes with polyethyleneimine-nanoparticle hybrid active layer for solvent resistant nanofiltration, *Journal of Membrane Science*, 470 (2014) 70-79.
- [226] J. Zhu, N. Guo, Y. Zhang, L. Yu, J. Liu, Preparation and characterization of negatively charged PES nanofiltration membrane by blending with halloysite nanotubes grafted with poly (sodium 4-styrenesulfonate) via surface-initiated ATRP, *Journal of Membrane Science*, 465 (2014) 91-99.
- [227] A. Linggawati, A. Mohammad, C. Leo, Effects of APTEOS content and electron beam irradiation on physical and separation properties of hybrid nylon-66 membranes, *Materials Chemistry and Physics*, 133 (2012) 110-117.
- [228] A. Linggawati, A.W. Mohammad, Z. Ghazali, Effect of electron beam irradiation on morphology and sieving characteristics of nylon-66 membranes, *European Polymer Journal*, 45 (2009) 2797-2804.
- [229] H.-m. Xu, J.-f. Wei, X.-l. Wang, Nanofiltration hollow fiber membranes with high charge density prepared by simultaneous electron beam radiation-induced graft polymerization for removal of Cr (VI), *Desalination*, 346 (2014) 122-130.
- [230] M. Buonomenna, L. Lopez, M. Davoli, P. Favia, R. d'Agostino, E. Drioli, Polymeric membranes modified via plasma for nanofiltration of aqueous solution containing organic compounds, *Microporous and Mesoporous Materials*, 120 (2009) 147-153.
- [231] E.-S. Kim, Q. Yu, B. Deng, Plasma surface modification of nanofiltration (NF) thin-film composite (TFC) membranes to improve anti organic fouling, *Applied Surface Science*, 257 (2011) 9863-9871.
- [232] X.-l. Wang, J.-f. Wei, Z. Dai, K.-y. Zhao, H. Zhang, Preparation and characterization of negatively charged hollow fiber nanofiltration membrane by plasma-induced graft polymerization, *Desalination*, 286 (2012) 138-144.

- [233] M. Hu, B. Mi, Layer-by-layer assembly of graphene oxide membranes via electrostatic interaction, *Journal of Membrane Science*, 469 (2014) 80-87.
- [234] R.H. Lajimi, E. Ferjani, M.S. Roudesli, A. Deratani, Effect of LbL surface modification on characteristics and performances of cellulose acetate nanofiltration membranes, *Desalination*, 266 (2011) 78-86.
- [235] L.Y. Ng, A.W. Mohammad, C.Y. Ng, C.P. Leo, R. Rohani, Development of nanofiltration membrane with high salt selectivity and performance stability using polyelectrolyte multilayers, *Desalination*, 351 (2014) 19-26.
- [236] D. Saeki, M. Imanishi, Y. Ohmukai, T. Maruyama, H. Matsuyama, Stabilization of layer-by-layer assembled nanofiltration membranes by crosslinking via amide bond formation and siloxane bond formation, *Journal of Membrane Science*, 447 (2013) 128-133.
- [237] K. Hendrix, K. Vanherck, I.F. Vankelecom, Optimization of solvent resistant nanofiltration membranes prepared by the in-situ diamine crosslinking method, *Journal of Membrane Science*, 421 (2012) 15-24.
- [238] J. Miao, H. Lin, W. Wang, L.-C. Zhang, Amphoteric composite membranes for nanofiltration prepared from sulfated chitosan crosslinked with hexamethylene diisocyanate, *Chemical Engineering Journal*, 234 (2013) 132-139.
- [239] G. Mustafa, K. Wyns, P. Vandezande, A. Buekenhoudt, V. Meynen, Novel grafting method efficiently decreases irreversible fouling of ceramic nanofiltration membranes, *Journal of Membrane Science*, 470 (2014) 369-377.
- [240] R. Zhang, Y. Su, X. Zhao, Y. Li, J. Zhao, Z. Jiang, A novel positively charged composite nanofiltration membrane prepared by bio-inspired adhesion of polydopamine and surface grafting of poly (ethylene imine), *Journal of Membrane Science*, 470 (2014) 9-17.
- [241] W.-P. Zhu, J. Gao, S.-P. Sun, S. Zhang, T.-S. Chung, Poly (amidoamine) dendrimer (PAMAM) grafted on thin film composite (TFC) nanofiltration (NF) hollow fiber membranes for heavy metal removal, *Journal of Membrane Science*, 487 (2015) 117-126.
- [242] J. Gao, S.-P. Sun, W.-P. Zhu, T.-S. Chung, Chelating polymer modified P84 nanofiltration (NF) hollow fiber membranes for high efficient heavy metal removal, *Water Research*, 63 (2014) 252-261.
- [243] R. Bernstein, E. Antón, M. Ulbricht, Tuning the nanofiltration performance of thin film strong polyelectrolyte hydrogel composite membranes by photo-grafting conditions, *Journal of Membrane Science*, 427 (2013) 129-138.
- [244] H. Deng, Y. Xu, Q. Chen, X. Wei, B. Zhu, High flux positively charged nanofiltration membranes prepared by UV-initiated graft polymerization of methacrylateoethyl trimethyl ammonium chloride (DMC) onto polysulfone membranes, *Journal of Membrane Science*, 366 (2011) 363-372.
- [245] C. Qiu, Q.T. Nguyen, Z. Ping, Surface modification of cardo polyetherketone ultrafiltration membrane by photo-grafted copolymers to obtain nanofiltration membranes, *Journal of membrane science*, 295 (2007) 88-94.
- [246] P.S. Zhong, N. Widjojo, T.-S. Chung, M. Weber, C. Maletzko, Positively charged nanofiltration (NF) membranes via UV grafting on sulfonated polyphenylenesulfone (sPPSU) for effective removal of textile dyes from wastewater, *Journal of Membrane Science*, 417 (2012) 52-60.
- [247] S. Chisca, P.H.H. Duong, A.H. Emwas, R. Sougrat, S.P. Nunes, Crosslinked copolyazoles with a zwitterionic structure for organic solvent resistant membranes, *Polymer Chemistry*, 6 (2015) 543-554.
- [248] H. Maab, S. Pereira Nunes, Porous polyoxadiazole membranes for harsh environment, *Journal of Membrane Science*, 445 (2013) 127-134.
- [249] P.H. Duong, S. Chisca, P.-Y. Hong, H. Cheng, S.P. Nunes, T.-S. Chung, Hydroxyl functionalized polytriazole-co-polyoxadiazole as substrates for forward osmosis membranes, *ACS applied materials & interfaces*, 7 (2015) 3960-3973.

- [250] S. Hermans, H. Mariën, C. Van Goethem, I.F. Vankelecom, Recent developments in thin film (nano) composite membranes for solvent resistant nanofiltration, *Current Opinion in Chemical Engineering*, 8 (2015) 45-54.
- [251] P. Marchetti, M.F. Jimenez Solomon, G. Szekely, A.G. Livingston, Molecular Separation with Organic Solvent Nanofiltration: A Critical Review, *Chemical Reviews*, 114 (2014) 10735-10806.
- [252] G.W.I.G.I. DesalData), in: Market profile and desalination markets, 2009–2012 yearbooks and GWI website, <http://www.desaldata.com/>.
- [253] F.H. Kiand, Supply of desalinated water by the private sector: 30 MGD Singapore seawater desalination plant, in: MEDRC International Conference on Desalination Costing, Lemesos, Cyprus, December 2004.
- [254] M. Wilf, L. Awerbuch, C. Bartels, M. Mickley, G. Pearce, N. Voutchkov, The guidebook to membrane desalination technology, Balaban Desalination Publication, L'Aquila, Italy, (2007).
- [255] S.S. S. Loeb, UCLA Dept. Eng. Report, in, 1961.
- [256] Europe's Largest SWRO Plant Opens, *Water Desalination Report*, in, 2009.
- [257] J.M. Laine, Design & Operation Considerations: Two Large-Scale Case Studies, in, Suez Environment, 2009.
- [258] A. Shimokawa, Desalination Plant with Unique Methods in Fukuoka, in: Japan-US Governmental Conference on Drinking Water Quality Management and Wastewater Control, Las Vegas, 2009.
- [259] R. Stover, Low Energy Consumption SWRO, submitted to *Proceedings of Clean Technology*, (2008).
- [260] A. Antony, R. Fudianto, S. Cox, G. Leslie, Assessing the oxidative degradation of polyamide reverse osmosis membrane—accelerated ageing with hypochlorite exposure, *Journal of Membrane Science*, 347 (2010) 159-164.
- [261] G.-D. Kang, C.-J. Gao, W.-D. Chen, X.-M. Jie, Y.-M. Cao, Q. Yuan, Study on hypochlorite degradation of aromatic polyamide reverse osmosis membrane, *Journal of membrane science*, 300 (2007) 165-171.
- [262] T. Kawaguchi, H. Tamura, Chlorine - resistant membrane for reverse osmosis. I. Correlation between chemical structures and chlorine resistance of polyamides, *Journal of applied polymer science*, 29 (1984) 3359-3367.
- [263] N.P. Soice, A.R. Greenberg, W.B. Krantz, A.D. Norman, Studies of oxidative degradation in polyamide RO membrane barrier layers using pendant drop mechanical analysis, *Journal of membrane science*, 243 (2004) 345-355.
- [264] Y. Cengeloglu, G. Arslan, A. Tor, I. Kocak, N. Dursun, Removal of boron from water by using reverse osmosis, *Separation and Purification Technology*, 64 (2008) 141-146.
- [265] C. Dominguez-Tagle, V.J. Romero-Ternero, A.M. Delgado-Torres, Boron removal efficiency in small seawater Reverse Osmosis systems, *Desalination*, 265 (2011) 43-48.
- [266] P. Glueckstern, M. Priel, Optimization of boron removal in old and new SWRO systems, *Desalination*, 156 (2003) 219-228.
- [267] N. Hilal, G. Kim, C. Somerfield, Boron removal from saline water: a comprehensive review, *Desalination*, 273 (2011) 23-35.
- [268] N. Nadav, M. Priel, P. Glueckstern, Boron removal from the permeate of a large SWRO plant in Eilat, *Desalination*, 185 (2005) 121-129.
- [269] M.R. Pastor, A.F. Ruiz, M. Chillon, D.P. Rico, Influence of pH in the elimination of boron by means of reverse osmosis, *Desalination*, 140 (2001) 145-152.
- [270] K.L. Tu, L.D. Nghiem, A.R. Chivas, Boron removal by reverse osmosis membranes in seawater desalination applications, *Separation and Purification Technology*, 75 (2010) 87-101.
- [271] L.F. Greenlee, D.F. Lawler, B.D. Freeman, B. Marrot, P. Moulin, Reverse osmosis desalination: water sources, technology, and today's challenges, *Water research*, 43 (2009) 2317-2348.
- [272] B. Sauvet-Goichon, Ashkelon desalination plant—a successful challenge, *Desalination*, 203 (2007) 75-81.

- [273] M. Fathizadeh, A. Aroujalian, A. Raisi, Effect of added NaX nano-zeolite into polyamide as a top thin layer of membrane on water flux and salt rejection in a reverse osmosis process, *Journal of membrane science*, 375 (2011) 88-95.
- [274] G.L. Jadav, P.S. Singh, Synthesis of novel silica-polyamide nanocomposite membrane with enhanced properties, *Journal of Membrane Science*, 328 (2009) 257-267.
- [275] B.-H. Jeong, E.M. Hoek, Y. Yan, A. Subramani, X. Huang, G. Hurwitz, A.K. Ghosh, A. Jawor, Interfacial polymerization of thin film nanocomposites: a new concept for reverse osmosis membranes, *Journal of Membrane Science*, 294 (2007) 1-7.
- [276] T.V. Ratto, J.K. Holt, A.W. Szmodis, Membranes with embedded nanotubes for selective permeability, in, *Google Patents*, 2011.
- [277] H.-L. Yang, J. Chun-Te Lin, C. Huang, Application of nanosilver surface modification to RO membrane and spacer for mitigating biofouling in seawater desalination, *Water research*, 43 (2009) 3777-3786.
- [278] A. González-Pérez, K.B. Stibius, T. Vissing, C.H. Nielsen, O.G. Mouritsen, Biomimetic triblock copolymer membrane arrays: a stable template for functional membrane proteins, *Langmuir*, 25 (2009) 10447-10450.
- [279] M. Kumar, M. Grzelakowski, J. Zilles, M. Clark, W. Meier, Highly permeable polymeric membranes based on the incorporation of the functional water channel protein Aquaporin Z, *Proceedings of the National Academy of Sciences*, 104 (2007) 20719-20724.
- [280] A. Taubert, Controlling water transport through artificial polymer/protein hybrid membranes, *Proceedings of the National Academy of Sciences*, 104 (2007) 20643-20644.
- [281] J.R. McCutcheon, M. Elimelech, Influence of membrane support layer hydrophobicity on water flux in osmotically driven membrane processes, *Journal of Membrane Science*, 318 (2008) 458-466.
- [282] J.T. Arena, B. McCloskey, B.D. Freeman, J.R. McCutcheon, Surface modification of thin film composite membrane support layers with polydopamine: enabling use of reverse osmosis membranes in pressure retarded osmosis, *Journal of Membrane Science*, 375 (2011) 55-62.
- [283] H. Lee, Y. Lee, A.R. Statz, J. Rho, T.G. Park, P.B. Messersmith, Substrate - independent layer - by - layer assembly by using mussel - adhesive - inspired polymers, *Advanced Materials*, 20 (2008) 1619-1623.
- [284] B.D. McCloskey, H.B. Park, H. Ju, B.W. Rowe, D.J. Miller, B.J. Chun, K. Kin, B.D. Freeman, Influence of polydopamine deposition conditions on pure water flux and foulant adhesion resistance of reverse osmosis, ultrafiltration, and microfiltration membranes, *Polymer*, 51 (2010) 3472-3485.
- [285] D. Rana, T. Matsuura, Surface modifications for antifouling membranes, *Chemical reviews*, 110 (2010) 2448-2471.
- [286] G. Han, J.S. de Wit, T.-S. Chung, Water reclamation from emulsified oily wastewater via effective forward osmosis hollow fiber membranes under the PRO mode, *Water Research*, (2015).
- [287] N.Y. Yip, A. Tiraferri, W.A. Phillip, J.D. Schiffman, M. Elimelech, High performance thin-film composite forward osmosis membrane, *Environmental science & technology*, 44 (2010) 3812-3818.
- [288] B. Mi, M. Elimelech, Gypsum scaling and cleaning in forward osmosis: measurements and mechanisms, *Environmental science & technology*, 44 (2010) 2022-2028.
- [289] M.I. Dova, K.B. Petrotos, H.N. Lazarides, On the direct osmotic concentration of liquid foods: Part II. Development of a generalized model, *Journal of Food Engineering*, 78 (2007) 431-437.
- [290] E. Cornelissen, D. Harmsen, K. De Korte, C. Ruiken, J.-J. Qin, H. Oo, L. Wessels, Membrane fouling and process performance of forward osmosis membranes on activated sludge, *Journal of Membrane Science*, 319 (2008) 158-168.
- [291] J.R. McCutcheon, M. Elimelech, Influence of concentrative and dilutive internal concentration polarization on flux behavior in forward osmosis, *Journal of Membrane Science*, 284 (2006) 237-247.

- [292] S. Loeb, L. Titelman, E. Korngold, J. Freiman, Effect of porous support fabric on osmosis through a Loeb-Sourirajan type asymmetric membrane, *Journal of Membrane Science*, 129 (1997) 243-249.
- [293] T.-S. Chung, S. Zhang, K.Y. Wang, J. Su, M.M. Ling, Forward osmosis processes: yesterday, today and tomorrow, *Desalination*, 287 (2012) 78-81.
- [294] A. Tiraferri, N.Y. Yip, W.A. Phillip, J.D. Schiffman, M. Elimelech, Relating performance of thin-film composite forward osmosis membranes to support layer formation and structure, *Journal of Membrane Science*, 367 (2011) 340-352.
- [295] X. Li, K.Y. Wang, B. Helmer, T.-S. Chung, Thin-film composite membranes and formation mechanism of thin-film layers on hydrophilic cellulose acetate propionate substrates for forward osmosis processes, *Industrial & Engineering Chemistry Research*, 51 (2012) 10039-10050.
- [296] N. Widjojo, T.-S. Chung, M. Weber, C. Maletzko, V. Warzelhan, The role of sulphonated polymer and macrovoid-free structure in the support layer for thin-film composite (TFC) forward osmosis (FO) membranes, *Journal of Membrane Science*, 383 (2011) 214-223.
- [297] L.A. Hoover, J.D. Schiffman, M. Elimelech, Nanofibers in thin-film composite membrane support layers: Enabling expanded application of forward and pressure retarded osmosis, *Desalination*, 308 (2013) 73-81.
- [298] X. Song, Z. Liu, D.D. Sun, Nano gives the answer: breaking the bottleneck of internal concentration polarization with a nanofiber composite forward osmosis membrane for a high water production rate, *Advanced materials*, 23 (2011) 3256-3260.
- [299] A. Achilli, T.Y. Cath, A.E. Childress, Selection of inorganic-based draw solutions for forward osmosis applications, *Journal of Membrane Science*, 364 (2010) 233-241.
- [300] B.S. Frank, Desalination of sea water, in, Google Patents, 1972.
- [301] G.W. Batchelder, Process for the demineralization of water, in, Google Patents, 1965.
- [302] G.T. Gray, J.R. McCutcheon, M. Elimelech, Internal concentration polarization in forward osmosis: role of membrane orientation, *Desalination*, 197 (2006) 1-8.
- [303] N.T. Hancock, T.Y. Cath, Solute coupled diffusion in osmotically driven membrane processes, *Environmental science & technology*, 43 (2009) 6769-6775.
- [304] J.R. McCutcheon, R.L. McGinnis, M. Elimelech, Desalination by ammonia-carbon dioxide forward osmosis: influence of draw and feed solution concentrations on process performance, *Journal of membrane science*, 278 (2006) 114-123.
- [305] H.Y. Ng, W. Tang, W.S. Wong, Performance of forward (direct) osmosis process: membrane structure and transport phenomenon, *Environmental science & technology*, 40 (2006) 2408-2413.
- [306] J. Kessler, C. Moody, Drinking water from sea water by forward osmosis, *Desalination*, 18 (1976) 297-306.
- [307] K. Stache, Apparatus for transforming sea water, brackish water, polluted water or the like into a nutritious drink by means of osmosis, in, Google Patents, 1989.
- [308] J. Yaeli, Method and apparatus for processing liquid solutions of suspensions particularly useful in the desalination of saline water, in, Google Patents, 1992.
- [309] S. Adham, Dewatering reverse osmosis concentrate from water reuse applications using forward osmosis, *WaterReuse Foundation*, 2007.
- [310] R.A. Jones, A.J. Ryan, H. Storey, M. Butler, C.J. Crook, Apparatus and method for purifying water by forward osmosis, in, Google Patents, 2007.
- [311] T. Oriard, P. Haggerty, Forward osmosis utilizing a controllable osmotic agent, in, Google Patents, 2007.
- [312] S.K. Yen, M. Su, K.Y. Wang, T.-S. Chung, Study of draw solutes using 2-methylimidazole-based compounds in forward osmosis, *Journal of Membrane Science*, 364 (2010) 242-252.
- [313] Q. Ge, T.-S. Chung, Oxalic acid complexes: promising draw solutes for forward osmosis (FO) in protein enrichment, *Chemical Communications*, 51 (2015) 4854-4857.

- [314] T.-S. Chung, L. Luo, C.F. Wan, Y. Cui, G. Amy, What is next for forward osmosis (FO) and pressure retarded osmosis (PRO), *Separation and Purification Technology*, (2015).
- [315] R.K. McGovern, On the potential of forward osmosis to energetically outperform reverse osmosis desalination, *Journal of Membrane Science*, 469 (2014) 245-250.
- [316] D.L. Shaffer, J.R. Werber, H. Jaramillo, S. Lin, M. Elimelech, Forward osmosis: Where are we now?, *Desalination*, 356 (2015) 271-284.
- [317] M. Khayet, N. Li, A. Fane, W. Winston Ho, *Membrane Distillation, Advance Membrane Technology and Applications*, in, John Wiley, New Jersey, 2008.
- [318] F. Laganà, G. Barbieri, E. Drioli, Direct contact membrane distillation: modelling and concentration experiments, *Journal of Membrane Science*, 166 (2000) 1-11.
- [319] M. Khayet, J. Mengual, T. Matsuura, Porous hydrophobic/hydrophilic composite membranes: application in desalination using direct contact membrane distillation, *Journal of Membrane Science*, 252 (2005) 101-113.
- [320] F.A. Banat, J. Simandl, Theoretical and experimental study in membrane distillation, *Desalination*, 95 (1994) 39-52.
- [321] F.A. Banat, J. Simandl, *Desalination by membrane distillation: a parametric study*, (1998).
- [322] M. El-Bourawi, Z. Ding, R. Ma, M. Khayet, A framework for better understanding membrane distillation separation process, *Journal of Membrane Science*, 285 (2006) 4-29.
- [323] C. Fernández-Pineda, M.A. Izquierdo-Gil, M. García-Payo, Gas permeation and direct contact membrane distillation experiments and their analysis using different models, *Journal of Membrane Science*, 198 (2002) 33-49.
- [324] J. Phattaranawik, R. Jiratananon, A. Fane, Heat transport and membrane distillation coefficients in direct contact membrane distillation, *Journal of Membrane Science*, 212 (2003) 177-193.
- [325] B.L. Pangarkar, M.G. Sane, S.B. Parjane, M. Guddad, Status of membrane distillation for water and wastewater treatment—A review, *Desalination and Water Treatment*, 52 (2014) 5199-5218.
- [326] C. Feng, B. Shi, G. Li, Y. Wu, Preliminary research on microporous membrane from F2. 4 for membrane distillation, *Separation and purification technology*, 39 (2004) 221-228.
- [327] M. Khayet, C. Cojocar, M.d.C. García-Payo, Experimental design and optimization of asymmetric flat-sheet membranes prepared for direct contact membrane distillation, *Journal of membrane science*, 351 (2010) 234-245.
- [328] S. Bonyadi, T.-S. Chung, Highly porous and macrovoid-free PVDF hollow fiber membranes for membrane distillation by a solvent-dope solution co-extrusion approach, *Journal of Membrane Science*, 331 (2009) 66-74.
- [329] M.d.C. García-Payo, M. Essalhi, M. Khayet, Effects of PVDF-HFP concentration on membrane distillation performance and structural morphology of hollow fiber membranes, *Journal of Membrane Science*, 347 (2010) 209-219.
- [330] M.d.C. García-Payo, M. Essalhi, M. Khayet, Preparation and characterization of PVDF-HFP copolymer hollow fiber membranes for membrane distillation, *Desalination*, 245 (2009) 469-473.
- [331] D.E. Suk, T. Matsuura, H.B. Park, Y.M. Lee, Synthesis of a new type of surface modifying macromolecules (nSMM) and characterization and testing of nSMM blended membranes for membrane distillation, *Journal of membrane science*, 277 (2006) 177-185.
- [332] L. Song, B. Li, K.K. Sirkar, J.L. Gilron, Direct contact membrane distillation-based desalination: novel membranes, devices, larger-scale studies, and a model, *Industrial & engineering chemistry research*, 46 (2007) 2307-2323.
- [333] Z. Jin, S.H. Zhang, X.G. Jian, Hydrophobic modification of poly (phthalazinone ether sulfone ketone) hollow fiber membrane for vacuum membrane distillation, *Journal of Membrane Science*, 310 (2008) 20-27.

- [334] Z. Hendren, J. Brant, M. Wiesner, Surface modification of nanostructured ceramic membranes for direct contact membrane distillation, *Journal of Membrane Science*, 331 (2009) 1-10.
- [335] M. Qtaishat, M. Khayet, T. Matsuura, Guidelines for preparation of higher flux hydrophobic/hydrophilic composite membranes for membrane distillation, *Journal of membrane science*, 329 (2009) 193-200.
- [336] M. Qtaishat, M. Khayet, T. Matsuura, Novel porous composite hydrophobic/hydrophilic polysulfone membranes for desalination by direct contact membrane distillation, *Journal of Membrane science*, 341 (2009) 139-148.
- [337] P. Peng, A. Fane, X. Li, Desalination by membrane distillation adopting a hydrophilic membrane, *Desalination*, 173 (2005) 45-54.
- [338] K. Ohta, I. Hayano, T. Okabe, T. Goto, S. Kimura, H. Ohya, Membrane distillation with fluoro-carbon membranes, *Desalination*, 81 (1991) 107-115.
- [339] M. Qtaishat, D. Rana, T. Matsuura, M. Khayet, Effect of surface modifying macromolecules stoichiometric ratio on composite hydrophobic/hydrophilic membranes characteristics and performance in direct contact membrane distillation, *AIChE journal*, 55 (2009) 3145-3151.
- [340] S. Bonyadi, T.S. Chung, Flux enhancement in membrane distillation by fabrication of dual layer hydrophilic-hydrophobic hollow fiber membranes, *Journal of Membrane Science*, 306 (2007) 134-146.
- [341] C. Feng, K. Khulbe, T. Matsuura, R. Gopal, S. Kaur, S. Ramakrishna, M. Khayet, Production of drinking water from saline water by air-gap membrane distillation using polyvinylidene fluoride nanofiber membrane, *Journal of Membrane Science*, 311 (2008) 1-6.
- [342] M.A. Tofighy, Y. Shirazi, T. Mohammadi, A. Pak, Salty water desalination using carbon nanotubes membrane, *Chemical Engineering Journal*, 168 (2011) 1064-1072.
- [343] L. Dumée, K. Sears, J.r. Schütz, N. Finn, M. Duke, S. Gray, Carbon nanotube based composite membranes for water desalination by membrane distillation, *Desalination and Water treatment*, 17 (2010) 72-79.
- [344] K. Gethard, O. Sae-Khow, S. Mitra, Water desalination using carbon-nanotube-enhanced membrane distillation, *ACS applied materials & interfaces*, 3 (2010) 110-114.
- [345] L.F. Dumée, K. Sears, J. Schütz, N. Finn, C. Huynh, S. Hawkins, M. Duke, S. Gray, Characterization and evaluation of carbon nanotube Bucky-Paper membranes for direct contact membrane distillation, *Journal of Membrane Science*, 351 (2010) 36-43.
- [346] M. Su, M.M. Teoh, K.Y. Wang, J. Su, T.-S. Chung, Effect of inner-layer thermal conductivity on flux enhancement of dual-layer hollow fiber membranes in direct contact membrane distillation, *Journal of Membrane Science*, 364 (2010) 278-289.
- [347] K.Y. Wang, S.W. Foo, T.-S. Chung, Mixed matrix PVDF hollow fiber membranes with nanoscale pores for desalination through direct contact membrane distillation, *Industrial & Engineering Chemistry Research*, 48 (2009) 4474-4483.
- [348] A.A.S. H. Maab, L. Francis, S. Livazovic, N. Ghafour, G. L. Amy, S. P. Nunes,, Polyazole hollow fiber membranes for direct contact membrane distillation, *ACS Ind. Eng. Chem. Research* 52 (2013) 10425-10429.
- [349] H. Maab, L. Francis, A. Al-Saadi, C. Aubry, N. Ghaffour, G. Amy, S.P. Nunes, Synthesis and fabrication of nanostructured hydrophobic polyazole membranes for low-energy water recovery, *Journal of Membrane Science*, 423 (2012) 11-19.
- [350] L.D. Tijging, Y.C. Woo, J.-S. Choi, S. Lee, S.-H. Kim, H.K. Shon, Fouling and its control in membrane distillation—A review, *Journal of Membrane Science*, 475 (2015) 215-244.
- [351] G. Naidu, S. Jeong, S. Vigneswaran, T.-M. Hwang, Y.-J. Choi, S.-H. Kim, A review on fouling of membrane distillation, *Desalination and Water Treatment*, (2015) 1-25.
- [352] B.L. Pangarkar, M.G. Sane, M. Guddad, Reverse osmosis and membrane distillation for desalination of groundwater: a review, *ISRN Materials Science*, 2011 (2011).

- [353] L. Tijing, H. Kim, D. Lee, C. Kim, Y. Cho, Use of an oscillating electric field to mitigate mineral fouling in a heat exchanger, *Experimental Heat Transfer*, 22 (2009) 257-270.
- [354] M. Gryta, Calcium sulphate scaling in membrane distillation process, *Chemical Papers*, 63 (2009) 146-151.
- [355] M. Gryta, Polyphosphates used for membrane scaling inhibition during water desalination by membrane distillation, *Desalination*, 285 (2012) 170-176.
- [356] M. Gryta, The influence of magnetic water treatment on CaCO_3 scale formation in membrane distillation process, *Separation and purification technology*, 80 (2011) 293-299.
- [357] L.D. Tijing, H.Y. Kim, D.H. Lee, C.S. Kim, Y.I. Cho, Physical water treatment using RF electric fields for the mitigation of CaCO_3 fouling in cooling water, *International Journal of Heat and Mass Transfer*, 53 (2010) 1426-1437.
- [358] L.D. Tijing, M.-H. Yu, C.-H. Kim, A. Amarjargal, Y.C. Lee, D.-H. Lee, D.-W. Kim, C.S. Kim, Mitigation of scaling in heat exchangers by physical water treatment using zinc and tourmaline, *Applied Thermal Engineering*, 31 (2011) 2025-2031.
- [359] L. Tijing, B. Pak, D. Lee, Y. Cho, Heat-treated titanium balls for the mitigation of mineral fouling in heat exchangers, *Experimental Heat Transfer*, 21 (2008) 115-132.
- [360] J. Ge, Y. Peng, Z. Li, P. Chen, S. Wang, Membrane fouling and wetting in a DCMD process for RO brine concentration, *Desalination*, 344 (2014) 97-107.
- [361] X. Yu, H. Yang, H. Lei, A. Shapiro, Experimental evaluation on concentrating cooling tower blowdown water by direct contact membrane distillation, *Desalination*, 323 (2013) 134-141.
- [362] L.D. Nghiem, T. Cath, A scaling mitigation approach during direct contact membrane distillation, *Separation and Purification Technology*, 80 (2011) 315-322.
- [363] F. He, K.K. Sirkar, J. Gilron, Studies on scaling of membranes in desalination by direct contact membrane distillation: CaCO_3 and mixed $\text{CaCO}_3/\text{CaSO}_4$ systems, *Chemical Engineering Science*, 64 (2009) 1844-1859.
- [364] F. He, K.K. Sirkar, J. Gilron, Effects of antiscalants to mitigate membrane scaling by direct contact membrane distillation, *Journal of Membrane Science*, 345 (2009) 53-58.
- [365] E. Guillen-Burrieza, A. Ruiz-Aguirre, G. Zaragoza, H.A. Arafat, Membrane fouling and cleaning in long term plant-scale membrane distillation operations, *Journal of Membrane Science*, 468 (2014) 360-372.
- [366] Renewables 2015 - Global Status Report, in, Renewables Academy, 2015.
- [367] G.Z. Ramon, B.J. Feinberg, E.M. Hoek, Membrane-based production of salinity-gradient power, *Energy & environmental science*, 4 (2011) 4423-4434.
- [368] R. Pattle, Production of electric power by mixing fresh and salt water in the hydroelectric pile, (1954).
- [369] B.E. Logan, M. Elimelech, Membrane-based processes for sustainable power generation using water, *Nature*, 488 (2012) 313-319.
- [370] S. Loeb, F. Van Hessen, D. Shahaf, Production of energy from concentrated brines by pressure-retarded osmosis: II. Experimental results and projected energy costs, *Journal of Membrane Science*, 1 (1976) 249-269.
- [371] S. Loeb, Production of energy from concentrated brines by pressure-retarded osmosis: I. Preliminary technical and economic correlations, *Journal of Membrane Science*, 1 (1976) 49-63.
- [372] N.Y. Yip, A. Tiraferri, W.A. Phillip, J.D. Schiffman, L.A. Hoover, Y.C. Kim, M. Elimelech, Thin-film composite pressure retarded osmosis membranes for sustainable power generation from salinity gradients, *Environmental science & technology*, 45 (2011) 4360-4369.
- [373] T. Thorsen, T. Holt, The potential for power production from salinity gradients by pressure retarded osmosis, *Journal of Membrane Science*, 335 (2009) 103-110.

- [374] C.C. Mitigation, IPCC special report on renewable energy sources and climate change mitigation, (2011).
- [375] J.W. Post, J. Veerman, H.V. Hamelers, G.J. Euverink, S.J. Metz, K. Nymeijer, C.J. Buisman, Salinity-gradient power: Evaluation of pressure-retarded osmosis and reverse electrodialysis, *Journal of Membrane Science*, 288 (2007) 218-230.
- [376] S. Loeb, F. Van Hessen, J. Levi, M. Ventura, The osmotic power plant, in: 11th Intersociety Energy Conversion Engineering Conference, 1976, pp. 51-57.
- [377] S.E. Skilhagen, J.E. Dugstad, R.J. Aaberg, Osmotic power—power production based on the osmotic pressure difference between waters with varying salt gradients, *Desalination*, 220 (2008) 476-482.
- [378] K. Gerstandt, K.-V. Peinemann, S.E. Skilhagen, T. Thorsen, T. Holt, Membrane processes in energy supply for an osmotic power plant, *Desalination*, 224 (2008) 64-70.
- [379] S. Loeb, T. Honda, M. Reali, Comparative mechanical efficiency of several plant configurations using a pressure-retarded osmosis energy converter, *Journal of Membrane Science*, 51 (1990) 323-335.
- [380] K. Lee, R. Baker, H. Lonsdale, Membranes for power generation by pressure-retarded osmosis, *Journal of Membrane Science*, 8 (1981) 141-171.
- [381] H. Jellinek, H. Masuda, Osmo-power. Theory and performance of an osmo-power pilot plant, *Ocean engineering*, 8 (1981) 103-128.
- [382] G. Mehta, S. Loeb, Performance of permasep B-9 and B-10 membranes in various osmotic regions and at high osmotic pressures, *Journal of Membrane Science*, 4 (1979) 335-349.
- [383] G.D. Mehta, S. Loeb, Internal polarization in the porous substructure of a semipermeable membrane under pressure-retarded osmosis, *Journal of Membrane Science*, 4 (1979) 261-265.
- [384] S. Loeb, G. Mehta, A two-coefficient water transport equation for pressure-retarded osmosis, *Journal of Membrane Science*, 4 (1979) 351-362.
- [385] R.L. McGinnis, J.R. McCutcheon, M. Elimelech, A novel ammonia-carbon dioxide osmotic heat engine for power generation, *Journal of membrane science*, 305 (2007) 13-19.
- [386] Y. Xu, X. Peng, C.Y. Tang, Q.S. Fu, S. Nie, Effect of draw solution concentration and operating conditions on forward osmosis and pressure retarded osmosis performance in a spiral wound module, *Journal of Membrane Science*, 348 (2010) 298-309.
- [387] A. Achilli, T.Y. Cath, A.E. Childress, Power generation with pressure retarded osmosis: An experimental and theoretical investigation, *Journal of membrane science*, 343 (2009) 42-52.
- [388] G. Han, S. Zhang, X. Li, T.-S. Chung, Progress in pressure retarded osmosis (PRO) membranes for osmotic power generation, *Progress in Polymer Science*, (2015).
- [389] The salinity project group, the salinity power project: power production from the osmotic pressure difference between fresh water and seawater—Final report, in, The European Commission, Bruxelles, Lisbon, 2004.
- [390] S. Loeb, Large-scale power production by pressure-retarded osmosis, using river water and sea water passing through spiral modules, *Desalination*, 143 (2002) 115-122.
- [391] A. Zhu, P.D. Christofides, Y. Cohen, On RO membrane and energy costs and associated incentives for future enhancements of membrane permeability, *Journal of Membrane Science*, 344 (2009) 1-5.
- [392] F. Helfer, C. Lemckert, Y.G. Anissimov, Osmotic power with pressure retarded osmosis: theory, performance and trends—a review, *Journal of Membrane Science*, 453 (2014) 337-358.
- [393] International renewable energy agency, Renewable energy technologies: cost analysis series—wind power, in, International Renewable Energy Agency, Power Sector, IRENA, Bonn—Germany, 2012.
- [394] B.C. J. Hinkley, J. Hayward, A. Wonhas, R. Boyd, C. Grima, A. Tadros, R. Hall, K. Naicker, A. Mikhail, Concentrating solar power—driver and opportunities for cost-competitive electricity, in, CSIRO, Canberra, 2011.
- [395] R. Kleiterp, The feasibility of a commercial osmotic power plant, (Master thesis)

- , in: Department of Hydraulic Engineering, Delft University of Technology, Delft–The Netherlands, 2012.
- [396] S.E. Skilhagen, Osmotic power: a new, renewable source of energy, in: The 3rd Annual European Renewable Energy Markets, Platts, Berlin, 2012.
- [397] J.M. A. Syed, S. Thorpe, K. Penney, Australian Energy Projections to 2029–30, ABARE Research Report 10.02, Prepared for the Department of Resources, in, Energy and Tourism, Canberra, 2010.
- [398] K.S. A. Tanioka, M. Irie, S. Zaitso, H. Sakai, H. Hayashi, Power generation by pressure retarded osmosis using concentrated brine from seawater desalination system and treated sewage: review of experience with pilot plant in Japan in: The 3rd Osmosis Membrane Summit, Statkraft, Barcelona, 2012.
- [399] Ø.S.S. S. Bræin, S. E. Skilhagen, Osmotic power: from prototype to industry—what will it take?, in: The 3rd International Conference on Ocean Energy, Bilbao, Spain, 2010.
- [400] R.J.A. S. E. Skilhagen, Power production based on the osmotic pressure difference between fresh water and seawater, in: The European Seminar on Offshore Wind and Other Marine Renewable Energies in Mediterranean and European Seas (Owemes), Citavecchia, Italy, 2006.
- [401] A. Daniilidis, R. Herber, D.A. Vermaas, Upscale potential and financial feasibility of a reverse electrodialysis power plant, *Applied Energy*, 119 (2014) 257-265.
- [402] J.G. Hong, B. Zhang, S. Glabman, N. Uzal, X. Dou, H. Zhang, X. Wei, Y. Chen, Potential ion exchange membranes and system performance in reverse electrodialysis for power generation: A review, *Journal of Membrane Science*, 486 (2015) 71-88.
- [403] N.P. Brandon, S. Skinner, B.C. Steele, Recent advances in materials for fuel cells, *Annual Review of Materials Research*, 33 (2003) 183-213.
- [404] R. Nagarale, G. Gohil, V.K. Shahi, Recent developments on ion-exchange membranes and electro-membrane processes, *Advances in Colloid and Interface Science*, 119 (2006) 97-130.
- [405] E. Guler, Y. Zhang, M. Saakes, K. Nijmeijer, Tailor - Made Anion - Exchange Membranes for Salinity Gradient Power Generation Using Reverse Electrodialysis, *ChemSusChem*, 5 (2012) 2262-2270.
- [406] C. Klayson, S.-H. Moon, B.P. Ladewig, G.M. Lu, L. Wang, Preparation of porous ion-exchange membranes (IEMs) and their characterizations, *Journal of Membrane Science*, 371 (2011) 37-44.
- [407] G.M. Geise, M.A. Hickner, B.E. Logan, Ionic resistance and permselectivity tradeoffs in anion exchange membranes, *ACS applied materials & interfaces*, 5 (2013) 10294-10301.
- [408] P. Długołęcki, K. Nijmeijer, S. Metz, M. Wessling, Current status of ion exchange membranes for power generation from salinity gradients, *Journal of Membrane Science*, 319 (2008) 214-222.
- [409] S. Yun, H. Im, Y. Heo, J. Kim, Crosslinked sulfonated poly (vinyl alcohol)/sulfonated multi-walled carbon nanotubes nanocomposite membranes for direct methanol fuel cells, *Journal of Membrane Science*, 380 (2011) 208-215.
- [410] C.-C. Yang, S.-J. Chiu, W.-C. Chien, S.-S. Chiu, Quaternized poly (vinyl alcohol)/alumina composite polymer membranes for alkaline direct methanol fuel cells, *Journal of Power Sources*, 195 (2010) 2212-2219.
- [411] Y. Wu, J. Hao, C. Wu, F. Mao, T. Xu, Cation exchange PVA/SPPO/SiO₂ membranes with double organic phases for alkali recovery, *Journal of Membrane Science*, 423 (2012) 383-391.
- [412] B.P. Tripathi, V.K. Shahi, Organic–inorganic nanocomposite polymer electrolyte membranes for fuel cell applications, *Progress in Polymer Science*, 36 (2011) 945-979.
- [413] J. Zhang, J. Qiao, G. Jiang, L. Liu, Y. Liu, Cross-linked poly (vinyl alcohol)/poly (diallyldimethylammonium chloride) as anion-exchange membrane for fuel cell applications, *Journal of Power Sources*, 240 (2013) 359-367.
- [414] J.-W. Rhim, H.B. Park, C.-S. Lee, J.-H. Jun, D.S. Kim, Y.M. Lee, Crosslinked poly (vinyl alcohol) membranes containing sulfonic acid group: proton and methanol transport through membranes, *Journal of Membrane Science*, 238 (2004) 143-151.
- [415] C.-P. Liu, C.-A. Dai, C.-Y. Chao, S.-J. Chang, Novel proton exchange membrane based on crosslinked poly (vinyl alcohol) for direct methanol fuel cells, *Journal of Power Sources*, 249 (2014) 285-298.

- [416] S. Aouadj, A. Chapiro, Preparation of hydrophilic membranes by grafting acrylic acid onto pre - irradiated teflon - FEP films, *Die Angewandte Makromolekulare Chemie*, 235 (1996) 73-80.
- [417] T. Xu, W. Yang, B. He, Ionic conductivity threshold in sulfonated poly (phenylene oxide) matrices: a combination of three-phase model and percolation theory, *Chemical Engineering Science*, 56 (2001) 5343-5350.
- [418] T. Xu, D. Wu, L. Wu, Poly (2, 6-dimethyl-1, 4-phenylene oxide)(PPO)—a versatile starting polymer for proton conductive membranes (PCMs), *Progress in Polymer Science*, 33 (2008) 894-915.
- [419] K. Saito, K. Saito, K. Sugita, M. Tamada, T. Sugo, Convection-aided collection of metal ions using chelating porous flat-sheet membranes, *Journal of Chromatography A*, 954 (2002) 277-283.
- [420] S. Hosseini, S. Madaeni, A. Heidari, A. Amirimehr, Preparation and characterization of ion-selective polyvinyl chloride based heterogeneous cation exchange membrane modified by magnetic iron–nickel oxide nanoparticles, *Desalination*, 284 (2012) 191-199.
- [421] N. Gizli, S. Çınarlı, M. Demircioğlu, Characterization of poly (vinylchloride)(PVC) based cation exchange membranes prepared with ionic liquid, *Separation and Purification Technology*, 97 (2012) 96-107.
- [422] J. Hu, C. Zhang, J. Cong, H. Toyoda, M. Nagatsu, Y. Meng, Plasma-grafted alkaline anion-exchange membranes based on polyvinyl chloride for potential application in direct alcohol fuel cell, *Journal of Power Sources*, 196 (2011) 4483-4490.
- [423] M. Arsalan, M.M.A. Khan, A comparative study of theoretical, electrochemical and ionic transport through PVC based Cu₃ (PO₄)₂ and polystyrene supported Ni₃ (PO₄)₂ composite ion exchange porous membranes, *Desalination*, 318 (2013) 97-106.
- [424] S. Hosseini, A. Gholami, S. Madaeni, A. Moghadassi, A. Hamidi, Fabrication of (polyvinyl chloride/cellulose acetate) electrodialysis heterogeneous cation exchange membrane: Characterization and performance in desalination process, *Desalination*, 306 (2012) 51-59.
- [425] E. Güler, W. van Baak, M. Saakes, K. Nijmeijer, Monovalent-ion-selective membranes for reverse electrodialysis, *Journal of membrane science*, 455 (2014) 254-270.
- [426] F.N. R. Kempener, Salinity gradient energy—technology brief, in, *IRENA Ocean Energy Technology*, 2014.
- [427] D.A. Vermaas, M. Saakes, K. Nijmeijer, Doubled power density from salinity gradients at reduced intermembrane distance, *Environmental science & technology*, 45 (2011) 7089-7095.
- [428] FUJIFILM membranes in blue energy test power station, in, 2014.
- [429] H.L. Ferreira, R. Garde, G. Fulli, W. Kling, J.P. Lopes, Characterisation of electrical energy storage technologies, *Energy*, 53 (2013) 288-298.
- [430] N. Balaban, *Energy 2000: The Beginning of a New Millennium*, CRC Press, 2000.
- [431] H. Lee, M. Yanilmaz, O. Toprakci, K. Fu, X. Zhang, A review of recent developments in membrane separators for rechargeable lithium-ion batteries, *Energy & Environmental Science*, 7 (2014) 3857-3886.
- [432] J.-M. Tarascon, M. Armand, Issues and challenges facing rechargeable lithium batteries, *Nature*, 414 (2001) 359-367.
- [433] C. Pillot, in: *AABC Conference*, Georgia, USA, 2014.
- [434] M. Armand, J.-M. Tarascon, Building better batteries, *Nature*, 451 (2008) 652-657.
- [435] V. Deimede, C. Elmasides, Separators for Lithium - Ion Batteries: A Review on the Production Processes and Recent Developments, *Energy Technology*, 3 (2015) 453-468.
- [436] S.S. Zhang, A review on the separators of liquid electrolyte Li-ion batteries, *Journal of Power Sources*, 164 (2007) 351-364.
- [437] P. Arora, Z. Zhang, Battery separators, *Chemical reviews*, 104 (2004) 4419-4462.
- [438] X. Huang, Separator technologies for lithium-ion batteries, *Journal of Solid State Electrochemistry*, 15 (2011) 649-662.

- [439] H.S. Bierenbaum, R.B. Isaacson, M.L. Druin, S.G. Plovan, Microporous polymeric films, *Industrial & Engineering Chemistry Product Research and Development*, 13 (1974) 2-9.
- [440] C. Chandavas, M. Xanthos, K. Sirkar, C. Gogos, Preparation of microporous films from immiscible blends via melt processing, *Journal of plastic film and sheeting*, 16 (2000) 288-300.
- [441] H. Sogo, Separator for a battery using an organic electrolytic solution and method for preparing the same, in, Google Patents, 1997.
- [442] H. Higuchi, K. Matsushita, M. Ezoe, T. Shinomura, Porous film, process for producing the same, and use of the same, in, Google Patents, 1995.
- [443] P. Jacoby, W.T. Tapp, Oriented polymeric microporous films, in, Google Patents, 1993.
- [444] D. Djian, F. Alloin, S. Martinet, H. Lignier, J.-Y. Sanchez, Lithium-ion batteries with high charge rate capacity: Influence of the porous separator, *Journal of power sources*, 172 (2007) 416-421.
- [445] C.T. Love, Thermomechanical analysis and durability of commercial micro-porous polymer Li-ion battery separators, *Journal of Power Sources*, 196 (2011) 2905-2912.
- [446] M.-S. Wu, P.-C.J. Chiang, J.-C. Lin, Y.-S. Jan, Correlation between electrochemical characteristics and thermal stability of advanced lithium-ion batteries in abuse tests—short-circuit tests, *Electrochimica acta*, 49 (2004) 1803-1812.
- [447] G. Venugopal, J. Moore, J. Howard, S. Pendalwar, Characterization of microporous separators for lithium-ion batteries, *Journal of Power Sources*, 77 (1999) 34-41.
- [448] J.A. Morehouse, L.S. Worrel, D.L. Taylor, D.R. Lloyd, B.D. Freeman, D.F. Lawler, The effect of uni-axial orientation on macroporous membrane structure, *Journal of Porous Materials*, 13 (2006) 61-72.
- [449] Z. Jiang, B. Carroll, K. Abraham, Studies of some poly (vinylidene fluoride) electrolytes, *Electrochimica Acta*, 42 (1997) 2667-2677.
- [450] G.-L. Ji, B.-K. Zhu, Z.-Y. Cui, C.-F. Zhang, Y.-Y. Xu, PVDF porous matrix with controlled microstructure prepared by TIPS process as polymer electrolyte for lithium ion battery, *Polymer*, 48 (2007) 6415-6425.
- [451] D. Djian, F. Alloin, S. Martinet, H. Lignier, Macroporous poly (vinylidene fluoride) membrane as a separator for lithium-ion batteries with high charge rate capacity, *Journal of Power Sources*, 187 (2009) 575-580.
- [452] A. Magistris, P. Mustarelli, F. Parazzoli, E. Quartarone, P. Piaggio, A. Bottino, Structure, porosity and conductivity of PVdF films for polymer electrolytes, *Journal of power sources*, 97 (2001) 657-660.
- [453] J. Saunier, F. Alloin, J.-Y. Sanchez, G. Caillon, Thin and flexible lithium-ion batteries: investigation of polymer electrolytes, *Journal of power sources*, 119 (2003) 454-459.
- [454] F. Boudin, X. Andrieu, C. Jehoulet, I. Olsen, Microporous PVdF gel for lithium-ion batteries, *Journal of Power Sources*, 81 (1999) 804-807.
- [455] A. Bottino, G. Camera-Roda, G. Capannelli, S. Munari, The formation of microporous polyvinylidene difluoride membranes by phase separation, *Journal of membrane science*, 57 (1991) 1-20.
- [456] G. Appetecchi, F. Croce, B. Scrosati, High-performance electrolyte membranes for plastic lithium batteries, *Journal of power sources*, 66 (1997) 77-82.
- [457] F. Groce, F. Gerace, G. Dautzemberg, S. Passerini, G. Appetecchi, B. Scrosati, Synthesis and characterization of highly conducting gel electrolytes, *Electrochimica Acta*, 39 (1994) 2187-2194.
- [458] B. Jung, Preparation of hydrophilic polyacrylonitrile blend membranes for ultrafiltration, *Journal of membrane science*, 229 (2004) 129-136.
- [459] B. Jung, J.K. Yoon, B. Kim, H.-W. Rhee, Effect of crystallization and annealing on polyacrylonitrile membranes for ultrafiltration, *Journal of membrane science*, 246 (2005) 67-76.
- [460] H.-S. Min, J.-M. Ko, D.-W. Kim, Preparation and characterization of porous polyacrylonitrile membranes for lithium-ion polymer batteries, *Journal of power sources*, 119 (2003) 469-472.
- [461] M.-H. Lee, H.J. Kim, E. Kim, S.B. Rhee, M.J. Moon, Effect of phase separation on ionic conductivity of poly (methyl methacrylate)-based solid polymer electrolyte, *Solid State Ionics*, 85 (1996) 91-98.

- [462] O. Bohnke, G. Frand, M. Rezrazi, C. Rousselot, C. Truche, Fast ion transport in new lithium electrolytes gelled with PMMA. 1. Influence of polymer concentration, *Solid State Ionics*, 66 (1993) 97-104.
- [463] G. Appetecchi, F. Croce, B. Scrosati, Kinetics and stability of the lithium electrode in poly (methacrylate)-based gel electrolytes, *Electrochimica Acta*, 40 (1995) 991-997.
- [464] A.I. Gopalan, P. Santhosh, K.M. Manesh, J.H. Nho, S.H. Kim, C.-G. Hwang, K.-P. Lee, Development of electrospun PVdF–PAN membrane-based polymer electrolytes for lithium batteries, *Journal of Membrane Science*, 325 (2008) 683-690.
- [465] A.M. Stephan, K. Nahm, Review on composite polymer electrolytes for lithium batteries, *Polymer*, 47 (2006) 5952-5964.
- [466] M. Yang, J. Hou, Membranes in lithium ion batteries, *Membranes*, 2 (2012) 367-383.
- [467] A. Magistris, E. Quartarone, P. Mustarelli, Y. Saito, H. Kataoka, PVDF-based porous polymer electrolytes for lithium batteries, *Solid State Ionics*, 152 (2002) 347-354.
- [468] D. Zhou, G. Wang, W. Li, G. Li, C. Tan, M. Rao, Y. Liao, Preparation and performances of porous polyacrylonitrile–methyl methacrylate membrane for lithium-ion batteries, *Journal of Power Sources*, 184 (2008) 477-480.
- [469] Y. Liao, D. Zhou, M. Rao, W. Li, Z. Cai, Y. Liang, C. Tan, Self-supported poly (methyl methacrylate–acrylonitrile–vinyl acetate)-based gel electrolyte for lithium ion battery, *Journal of Power Sources*, 189 (2009) 139-144.
- [470] G. Wu, H.-Y. Yang, H.-Z. Chen, F. Yuan, L.-G. Yang, M. Wang, R.-J. Fu, Novel porous polymer electrolyte based on polyacrylonitrile, *Materials chemistry and physics*, 104 (2007) 284-287.
- [471] S. Zhang, K. Xu, D. Foster, M. Ervin, T. Jow, Microporous gel electrolyte Li-ion battery, *Journal of power sources*, 125 (2004) 114-118.
- [472] Q. Shi, M. Yu, X. Zhou, Y. Yan, C. Wan, Structure and performance of porous polymer electrolytes based on P (VdF-HFP) for lithium ion batteries, *Journal of power Sources*, 103 (2002) 286-292.
- [473] C.M. Costa, V. Sencadas, J.G. Rocha, M. Silva, S. Lanceros-Méndez, Evaluation of the main processing parameters influencing the performance of poly (vinylidene fluoride–trifluoroethylene) lithium-ion battery separators, *Journal of Solid State Electrochemistry*, 17 (2013) 861-870.
- [474] H. Li, H. Zhang, Z.-Y. Liang, Y.-M. Chen, B.-K. Zhu, L.-P. Zhu, Preparation and Properties of Poly (vinylidene fluoride)/poly (dimethylsiloxane) graft (poly (propylene oxide)-block-poly (ethylene oxide)) blend porous separators and corresponding electrolytes, *Electrochimica Acta*, 116 (2014) 413-420.
- [475] H. Li, C.-E. Lin, J.-L. Shi, X.-T. Ma, B.-K. Zhu, L.-P. Zhu, Preparation and characterization of safety PVDF/P (MMA-co-PEGMA) active separators by studying the liquid electrolyte distribution in this kind of membrane, *Electrochimica Acta*, 115 (2014) 317-325.
- [476] C. Costa, J.G. Ribelles, S. Lanceros-Méndez, G. Appetecchi, B. Scrosati, Poly (vinylidene fluoride)-based, co-polymer separator electrolyte membranes for lithium-ion battery systems, *Journal of Power Sources*, 245 (2014) 779-786.
- [477] N.-S. Choi, Y.-G. Lee, J.-K. Park, J.-M. Ko, Preparation and electrochemical characteristics of plasticized polymer electrolytes based upon a P (VdF-co-HFP)/PVAc blend, *Electrochimica acta*, 46 (2001) 1581-1586.
- [478] J.-D. Jeon, B.-W. Cho, S.-Y. Kwak, Solvent-free polymer electrolytes based on thermally annealed porous P (VdF-HFP)/P (EO-EC) membranes, *Journal of power sources*, 143 (2005) 219-226.
- [479] Z.-l. Wang, Z.-y. Tang, A novel polymer electrolyte based on PMAML/PVDF-HFP blend, *Electrochimica acta*, 49 (2004) 1063-1068.
- [480] Z. Ren, Y. Liu, K. Sun, X. Zhou, N. Zhang, A microporous gel electrolyte based on poly (vinylidene fluoride-co-hexafluoropropylene)/fully cyanoethylated cellulose derivative blend for lithium-ion battery, *Electrochimica Acta*, 54 (2009) 1888-1892.

- [481] Z. Tian, W. Pu, X. He, C. Wan, C. Jiang, Preparation of a microporous polymer electrolyte based on poly (vinyl chloride)/poly (acrylonitrile-butyl acrylate) blend for Li-ion batteries, *Electrochimica acta*, 52 (2007) 3199-3206.
- [482] H.-J. Rhoo, H.-T. Kim, J.-K. Park, T.-S. Hwang, Ionic conduction in plasticized PVCPMMA blend polymer electrolytes, *Electrochimica acta*, 42 (1997) 1571-1579.
- [483] T. Ma, Z. Cui, Y. Wu, S. Qin, H. Wang, F. Yan, N. Han, J. Li, Preparation of PVDF based blend microporous membranes for lithium ion batteries by thermally induced phase separation: I. Effect of PMMA on the membrane formation process and the properties, *Journal of Membrane Science*, 444 (2013) 213-222.
- [484] D.-J. Lin, C.-L. Chang, C.-K. Lee, L.-P. Cheng, Preparation and characterization of microporous PVDF/PMMA composite membranes by phase inversion in water/DMSO solutions, *European polymer journal*, 42 (2006) 2407-2418.
- [485] I. Nicotera, L. Coppola, C. Oliviero, M. Castriota, E. Cazzanelli, Investigation of ionic conduction and mechanical properties of PMMA–PVdF blend-based polymer electrolytes, *Solid State Ionics*, 177 (2006) 581-588.
- [486] B. Jung, J.K. Yoon, B. Kim, H.-W. Rhee, Effect of molecular weight of polymeric additives on formation, permeation properties and hypochlorite treatment of asymmetric polyacrylonitrile membranes, *Journal of membrane science*, 243 (2004) 45-57.
- [487] A. Subramania, N.K. Sundaram, G.V. Kumar, Structural and electrochemical properties of micro-porous polymer blend electrolytes based on PVdF-co-HFP-PAN for Li-ion battery applications, *Journal of power sources*, 153 (2006) 177-182.
- [488] H. Li, X.-T. Ma, J.-L. Shi, Z.-K. Yao, B.-K. Zhu, L.-P. Zhu, Preparation and properties of poly (ethylene oxide) gel filled polypropylene separators and their corresponding gel polymer electrolytes for Li-ion batteries, *Electrochimica Acta*, 56 (2011) 2641-2647.
- [489] J.-Y. Sohn, S.-J. Gwon, J.-H. Choi, J. Shin, Y.-C. Nho, Preparation of polymer-coated separators using an electron beam irradiation, *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 266 (2008) 4994-5000.
- [490] H.-S. Kim, P. Periasamy, S.-I. Moon, Electrochemical properties of the Li-ion polymer batteries with P (VdF-co-HFP)-based gel polymer electrolyte, *Journal of power sources*, 141 (2005) 293-297.
- [491] Y.M. Lee, N.-S. Choi, J.A. Lee, W.-H. Seol, K.-Y. Cho, H.-Y. Jung, J.-W. Kim, J.-K. Park, Electrochemical effect of coating layer on the separator based on PVdF and PE non-woven matrix, *Journal of power sources*, 146 (2005) 431-435.
- [492] Y.-B. Jeong, D.-W. Kim, Effect of thickness of coating layer on polymer-coated separator on cycling performance of lithium-ion polymer cells, *Journal of Power sources*, 128 (2004) 256-262.
- [493] Y.M. Lee, J.-W. Kim, N.-S. Choi, J.A. Lee, W.-H. Seol, J.-K. Park, Novel porous separator based on PVdF and PE non-woven matrix for rechargeable lithium batteries, *Journal of power sources*, 139 (2005) 235-241.
- [494] R.W. Callahan, R.W. Call, K.J. Harleson, T.-H. Yu, Battery separators with reduced splitting propensity, in, *Google Patents*, 2003.
- [495] J.T. Lundquist, C.B. Lundsager, N.I. Palmer, H.J. Troffkin, Battery separator, in, *Google Patents*, 1987.
- [496] J.Y. Lee, Y.M. Lee, B. Bhattacharya, Y.-C. Nho, J.-K. Park, Separator grafted with siloxane by electron beam irradiation for lithium secondary batteries, *Electrochimica Acta*, 54 (2009) 4312-4315.
- [497] J.Y. Lee, B. Bhattacharya, Y.-C. Nho, J.-K. Park, New separator prepared by electron beam irradiation for high voltage lithium secondary batteries, *Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms*, 267 (2009) 2390-2394.
- [498] K. Gao, X. Hu, T. Yi, C. Dai, PE-g-MMA polymer electrolyte membrane for lithium polymer battery, *Electrochimica Acta*, 52 (2006) 443-449.

- [499] J.Y. Kim, Y. Lee, D.Y. Lim, Plasma-modified polyethylene membrane as a separator for lithium-ion polymer battery, *Electrochimica Acta*, 54 (2009) 3714-3719.
- [500] J.-Y. Sohn, J.-S. Im, J. Shin, Y.-C. Nho, PVDF-HFP/PMMA-coated PE separator for lithium ion battery, *Journal of Solid State Electrochemistry*, 16 (2012) 551-556.
- [501] J.-L. Shi, L.-F. Fang, H. Li, H. Zhang, B.-K. Zhu, L.-P. Zhu, Improved thermal and electrochemical performances of PMMA modified PE separator skeleton prepared via dopamine-initiated ATRP for lithium ion batteries, *Journal of Membrane Science*, 437 (2013) 160-168.
- [502] S.M. Kang, M.-H. Ryou, J.W. Choi, H. Lee, Mussel- and diatom-inspired silica coating on separators yields improved power and safety in Li-ion batteries, *Chemistry of Materials*, 24 (2012) 3481-3485.
- [503] L.-F. Fang, J.-L. Shi, B.-K. Zhu, L.-P. Zhu, Facile introduction of polyether chains onto polypropylene separators and its application in lithium ion batteries, *Journal of Membrane Science*, 448 (2013) 143-150.
- [504] M.H. Ryou, Y.M. Lee, J.K. Park, J.W. Choi, Mussel - Inspired Polydopamine - Treated Polyethylene Separators for High - Power Li - Ion Batteries, *Advanced Materials*, 23 (2011) 3066-3070.
- [505] M.H. Ryou, D.J. Lee, J.N. Lee, Y.M. Lee, J.K. Park, J.W. Choi, Excellent Cycle Life of Lithium - Metal Anodes in Lithium - Ion Batteries with Mussel - Inspired Polydopamine - Coated Separators, *Advanced Energy Materials*, 2 (2012) 645-650.
- [506] Y. Lee, M.-H. Ryou, M. Seo, J.W. Choi, Y.M. Lee, Effect of polydopamine surface coating on polyethylene separators as a function of their porosity for high-power Li-ion batteries, *Electrochimica Acta*, 113 (2013) 433-438.
- [507] F. Zhang, X. Ma, C. Cao, J. Li, Y. Zhu, Poly (vinylidene fluoride)/SiO₂ composite membranes prepared by electrospinning and their excellent properties for nonwoven separators for lithium-ion batteries, *Journal of Power Sources*, 251 (2014) 423-431.
- [508] P. Raghavan, X. Zhao, J. Manuel, G.S. Chauhan, J.-H. Ahn, H.-S. Ryu, H.-J. Ahn, K.-W. Kim, C. Nah, Electrochemical performance of electrospun poly (vinylidene fluoride-co-hexafluoropropylene)-based nanocomposite polymer electrolytes incorporating ceramic fillers and room temperature ionic liquid, *Electrochimica Acta*, 55 (2010) 1347-1354.
- [509] Y. Chen, Y. Chuang, J. Su, H. Yu, Y. Chen-Yang, High discharge capacity solid composite polymer electrolyte lithium battery, *Journal of Power Sources*, 196 (2011) 2802-2809.
- [510] H.-S. Jeong, D.-W. Kim, Y.U. Jeong, S.-Y. Lee, Effect of phase inversion on microporous structure development of Al₂O₃/poly (vinylidene fluoride-hexafluoropropylene)-based ceramic composite separators for lithium-ion batteries, *Journal of Power Sources*, 195 (2010) 6116-6121.
- [511] M. Kim, J.H. Park, Inorganic thin layer coated porous separator with high thermal stability for safety reinforced Li-ion battery, *Journal of Power Sources*, 212 (2012) 22-27.
- [512] J. Fang, A. Kelarakis, Y.-W. Lin, C.-Y. Kang, M.-H. Yang, C.-L. Cheng, Y. Wang, E.P. Giannelis, L.-D. Tsai, Nanoparticle-coated separators for lithium-ion batteries with advanced electrochemical performance, *Physical Chemistry Chemical Physics*, 13 (2011) 14457-14461.
- [513] H.-S. Jeong, S.-Y. Lee, Closely packed SiO₂ nanoparticles/poly (vinylidene fluoride-hexafluoropropylene) layers-coated polyethylene separators for lithium-ion batteries, *Journal of Power Sources*, 196 (2011) 6716-6722.
- [514] M. Kim, G.Y. Han, K.J. Yoon, J.H. Park, Preparation of a trilayer separator and its application to lithium-ion batteries, *Journal of Power Sources*, 195 (2010) 8302-8305.
- [515] M. Kim, Y.-C. Nho, J.H. Park, Electrochemical performances of inorganic membrane coated electrodes for Li-ion batteries, *Journal of Solid State Electrochemistry*, 14 (2010) 769-773.
- [516] K. Prasanna, C.-S. Kim, C.W. Lee, Effect of SiO₂ coating on polyethylene separator with different stretching ratios for application in lithium ion batteries, *Materials Chemistry and Physics*, 146 (2014) 545-550.
- [517] W.-K. Shin, D.-W. Kim, High performance ceramic-coated separators prepared with lithium ion-containing SiO₂ particles for lithium-ion batteries, *Journal of Power Sources*, 226 (2013) 54-60.

- [518] D. Fu, B. Luan, S. Argue, M.N. Bureau, I.J. Davidson, Nano SiO₂ particle formation and deposition on polypropylene separators for lithium-ion batteries, *Journal of Power Sources*, 206 (2012) 325-333.
- [519] H.-S. Jeong, S.C. Hong, S.-Y. Lee, Effect of microporous structure on thermal shrinkage and electrochemical performance of Al₂O₃/poly (vinylidene fluoride-hexafluoropropylene) composite separators for lithium-ion batteries, *Journal of Membrane Science*, 364 (2010) 177-182.
- [520] J.-H. Park, J.-H. Cho, W. Park, D. Ryoo, S.-J. Yoon, J.H. Kim, Y.U. Jeong, S.-Y. Lee, Close-packed SiO₂/poly (methyl methacrylate) binary nanoparticles-coated polyethylene separators for lithium-ion batteries, *Journal of Power Sources*, 195 (2010) 8306-8310.
- [521] J.-A. Choi, S.H. Kim, D.-W. Kim, Enhancement of thermal stability and cycling performance in lithium-ion cells through the use of ceramic-coated separators, *Journal of Power Sources*, 195 (2010) 6192-6196.
- [522] S.-M. Eo, E. Cha, D.-W. Kim, Effect of an inorganic additive on the cycling performances of lithium-ion polymer cells assembled with polymer-coated separators, *Journal of Power Sources*, 189 (2009) 766-770.
- [523] Y. Liao, X. Li, C. Fu, R. Xu, L. Zhou, C. Tan, S. Hu, W. Li, Polypropylene-supported and nano-Al₂O₃ doped poly (ethylene oxide)-poly (vinylidene fluoride-hexafluoropropylene)-based gel electrolyte for lithium ion batteries, *Journal of Power Sources*, 196 (2011) 2115-2121.
- [524] P. Gavelin, R. Ljungbäck, P. Jannasch, B. Wesslen, Amphiphilic solid polymer electrolytes, *Solid state ionics*, 147 (2002) 325-332.
- [525] J. Ji, J. Keen, W.-H. Zhong, Simultaneous improvement in ionic conductivity and mechanical properties of multi-functional block-copolymer modified solid polymer electrolytes for lithium ion batteries, *Journal of Power Sources*, 196 (2011) 10163-10168.
- [526] L. Wang, N. Li, X. He, C. Wan, C. Jiang, Macromolecule plasticized interpenetrating structure solid state polymer electrolyte for lithium ion batteries, *Electrochimica Acta*, 68 (2012) 214-219.
- [527] A. Suresh, A. Kulkarni, A. Sharma, PEO based solid polymer electrolyte plasticized by dibutyl phthalate, *Solid State Ionics*, 113 (1998) 179-186.
- [528] Q. Cheng, Z. Cui, J. Li, S. Qin, F. Yan, J. Li, Preparation and performance of polymer electrolyte based on poly (vinylidene fluoride)/polysulfone blend membrane via thermally induced phase separation process for lithium ion battery, *Journal of Power Sources*, 266 (2014) 401-413.
- [529] H. Li, Y.-M. Chen, X.-T. Ma, J.-L. Shi, B.-K. Zhu, L.-P. Zhu, Gel polymer electrolytes based on active PVDF separator for lithium ion battery. I: Preparation and property of PVDF/poly (dimethylsiloxane) blending membrane, *Journal of Membrane Science*, 379 (2011) 397-402.
- [530] L. Zhao, H. Zhang, X. Li, J. Zhao, C. Zhao, X. Yuan, Modification of electrospun poly (vinylidene fluoride - co - hexafluoropropylene) membranes through the introduction of poly (ethylene glycol) dimethacrylate, *Journal of Applied Polymer Science*, 111 (2009) 3104-3112.
- [531] X.H. Flora, M. Ulaganathan, R.S. Babu, S. Rajendran, Evaluation of lithium ion conduction in PAN/PMMA-based polymer blend electrolytes for Li-ion battery applications, *Ionics*, 18 (2012) 731-736.
- [532] M. Rao, X. Geng, Y. Liao, S. Hu, W. Li, Preparation and performance of gel polymer electrolyte based on electrospun polymer membrane and ionic liquid for lithium ion battery, *Journal of Membrane Science*, 399 (2012) 37-42.
- [533] J. Cao, L. Wang, M. Fang, Y. Shang, L. Deng, J. Yang, J. Li, H. Chen, X. He, Interfacial compatibility of gel polymer electrolyte and electrode on performance of Li-ion battery, *Electrochimica Acta*, 114 (2013) 527-532.
- [534] F. Croce, M.L. Focarete, J. Hassoun, I. Meschini, B. Scrosati, A safe, high-rate and high-energy polymer lithium-ion battery based on gelled membranes prepared by electrospinning, *Energy & Environmental Science*, 4 (2011) 921-927.
- [535] I. Basumallick, P. Roy, A. Chatterjee, A. Bhattacharya, S. Chatterjee, S. Ghosh, Organic polymer gel electrolyte for Li-ion batteries, *Journal of power sources*, 162 (2006) 797-799.

- [536] A. Chakrabarti, A. Juilfs, R. Filler, B.K. Mandal, Novel PEO-based dendronized polymers for lithium-ion batteries, *Solid State Ionics*, 181 (2010) 982-986.
- [537] Y. Liu, L. Tan, L. Li, Ion exchange membranes as electrolyte to improve high temperature capacity retention of LiMn_2O_4 cathode lithium-ion batteries, *Chemical Communications*, 48 (2012) 9858-9860.
- [538] Y. Liu, Z. Cai, L. Tan, L. Li, Ion exchange membranes as electrolyte for high performance Li-ion batteries, *Energy & Environmental Science*, 5 (2012) 9007-9013.
- [539] Z. Cai, Y. Liu, S. Liu, L. Li, Y. Zhang, High performance of lithium-ion polymer battery based on non-aqueous lithiated perfluorinated sulfonic ion-exchange membranes, *Energy & Environmental Science*, 5 (2012) 5690-5693.
- [540] Y. Wang, K.S. Chen, J. Mishler, S.C. Cho, X.C. Adroher, A review of polymer electrolyte membrane fuel cells: technology, applications, and needs on fundamental research, *Applied Energy*, 88 (2011) 981-1007.
- [541] T. Lipman, D. Sperling, Market concepts, competing technologies and cost challenges for automotive and stationary applications, *Handbook of Fuel Cells*, (2003).
- [542] C. Gittleman, D. Masten, S. Jorgensen, J. Waldecker, S. Hirano, M. Mehall, T. Abdel-Baset, Automotive fuel cell R&D needs, in: DOE Fuel Cell Pre-Solicitation Workshop March, 2010.
- [543] L.C. Jerram, Bus survey, *Fuel Cell Today*, (2008).
- [544] J. Butler, Portable fuel cell survey 2009, *Fuel Cell Today*, UK, April, (2009).
- [545] S. Narayanan, T. Valdez, Portable direct methanol fuel cell systems, *Handbook of Fuel Cells*, (2010).
- [546] S. Geiger, M. Cropper, Fuel cell market survey: small stationary applications, *Fuel Cell Today*, 30 (2003) 1-19.
- [547] F.C. Today, Small Stationary Survey 2009, (2009).
- [548] T.D. S. Agro, S. DeFelice, L. Thoma, Annual Progress Report for the DOE Hydrogen Program, in: US Department of Energy (DOE) website: <http://www.hydrogen.energy.gov>, 2005, pp. p. 790.
- [549] A. Arico, S. Srinivasan, V. Antonucci, DMFCs: from fundamental aspects to technology development, *Fuel cells*, 1 (2001) 133-161.
- [550] B. Smitha, S. Sridhar, A. Khan, Solid polymer electrolyte membranes for fuel cell applications—a review, *Journal of membrane science*, 259 (2005) 10-26.
- [551] A. Chandan, M. Hattenberger, A. El-Kharouf, S. Du, A. Dhir, V. Self, B.G. Pollet, A. Ingram, W. Bujalski, High temperature (HT) polymer electrolyte membrane fuel cells (PEMFC)—A review, *Journal of Power Sources*, 231 (2013) 264-278.
- [552] V. Neburchilov, J. Martin, H. Wang, J. Zhang, A review of polymer electrolyte membranes for direct methanol fuel cells, *Journal of Power Sources*, 169 (2007) 221-238.
- [553] S.J. Hamrock, M.A. Yandrasits, Proton exchange membranes for fuel cell applications, *Journal of Macromolecular Science, Part C: Polymer Reviews*, 46 (2006) 219-244.
- [554] F.R. Kalhammer, P.R. Prokopius, V.P. Roan, G.E. Voecks, Status and prospects of fuel cells as automobile engines, State of California Air Resources Board, California, (1998).
- [555] D. Gautam, S. Anjum, S. Ikram, Proton Exchange Membrane (PEM) in Fuel Cells: A Review, *The IUP Journal of Chemistry*, 3 (2010) 51-81.
- [556] A. Kraytsberg, Y. Ein-Eli, Review of Advanced Materials for Proton Exchange Membrane Fuel Cells, *Energy & Fuels*, 28 (2014) 7303-7330.
- [557] T. Kinumoto, M. Inaba, Y. Nakayama, K. Ogata, R. Umebayashi, A. Tasaka, Y. Iriyama, T. Abe, Z. Ogumi, Durability of perfluorinated ionomer membrane against hydrogen peroxide, *Journal of power Sources*, 158 (2006) 1222-1228.
- [558] N. Zamel, X. Li, Effect of contaminants on polymer electrolyte membrane fuel cells, *Progress in Energy and Combustion Science*, 37 (2011) 292-329.
- [559] M. Shi, F.C. Anson, Dehydration of protonated Nafion® coatings induced by cation exchange and monitored by quartz crystal microgravimetry, *Journal of Electroanalytical Chemistry*, 425 (1997) 117-123.

- [560] J. St-Pierre, D. Wilkinsor, S. Knights, M. Bos, Relationships between water management, contamination and lifetime degradation in PEFC, *Journal of New Materials for Electrochemical Systems*, 3 (2000) 99-106.
- [561] R. Borup, J. Meyers, B. Pivovar, Y.S. Kim, R. Mukundan, N. Garland, D. Myers, M. Wilson, F. Garzon, D. Wood, Scientific aspects of polymer electrolyte fuel cell durability and degradation, *Chemical reviews*, 107 (2007) 3904-3951.
- [562] M.P. Rodgers, L.J. Bonville, H.R. Kunz, D.K. Slattey, J.M. Fenton, Fuel cell perfluorinated sulfonic acid membrane degradation correlating accelerated stress testing and lifetime, *Chemical reviews*, 112 (2012) 6075-6103.
- [563] J. Healy, C. Hayden, T. Xie, K. Olson, R. Waldo, M. Brundage, H. Gasteiger, J. Abbott, Aspects of the chemical degradation of PFSA ionomers used in PEM fuel cells, *Fuel cells*, 5 (2005) 302-308.
- [564] Y. Tang, A.M. Karlsson, M.H. Santare, M. Gilbert, S. Cleghorn, W.B. Johnson, An experimental investigation of humidity and temperature effects on the mechanical properties of perfluorosulfonic acid membrane, *Materials Science and Engineering: A*, 425 (2006) 297-304.
- [565] J. Wu, X.Z. Yuan, J.J. Martin, H. Wang, J. Zhang, J. Shen, S. Wu, W. Merida, A review of PEM fuel cell durability: degradation mechanisms and mitigation strategies, *Journal of Power Sources*, 184 (2008) 104-119.
- [566] H. Tang, S. Peikang, S.P. Jiang, F. Wang, M. Pan, A degradation study of Nafion proton exchange membrane of PEM fuel cells, *Journal of Power Sources*, 170 (2007) 85-92.
- [567] S. Shi, G. Chen, Z. Wang, X. Chen, Mechanical properties of Nafion 212 proton exchange membrane subjected to hygrothermal aging, *Journal of Power Sources*, 238 (2013) 318-323.
- [568] A. Kusoglu, A.M. Karlsson, M.H. Santare, S. Cleghorn, W.B. Johnson, Mechanical response of fuel cell membranes subjected to a hygro-thermal cycle, *Journal of Power Sources*, 161 (2006) 987-996.
- [569] T. Li, G. Zhong, R. Fu, Y. Yang, Synthesis and characterization of Nafion/cross-linked PVP semi-interpenetrating polymer network membrane for direct methanol fuel cell, *Journal of Membrane Science*, 354 (2010) 189-197.
- [570] J. Ma, H.-J. Ni, D.-Y. Su, M.-Y. Huang, X.-X. Wang, The research status of Nafion ternary composite membrane, *international journal of hydrogen energy*, 37 (2012) 13185-13190.
- [571] Y. Alvarez-Gallego, B. Ruffmann, V. Silva, H. Silva, A.E. Lozano, G. Jose, S.P. Nunes, J. de Abajo, Sulfonated polynaphthalimides with benzimidazole pendant groups, *Polymer*, 49 (2008) 3875-3883.
- [572] D. Gomes, J. Roeder, M.L. Ponce, S.P. Nunes, Single-step synthesis of sulfonated polyoxadiazoles and their use as proton conducting membranes, *Journal of Power Sources*, 175 (2008) 49-59.
- [573] Y. Álvarez - Gallego, S.P. Nunes, A.E. Lozano, J.G. de la Campa, J. de Abajo, Synthesis and properties of novel polyimides bearing sulfonated benzimidazole pendant groups, *Macromolecular rapid communications*, 28 (2007) 616-622.
- [574] J. Roeder, D. Gomes, M.L. Ponce, V. Abetz, S.P. Nunes, Protonation of Sulfonated Poly (4, 4' - diphenylether - 1, 3, 4 - oxadiazole) Membranes, *Macromolecular Chemistry and physics*, 208 (2007) 467-473.
- [575] S. Vetter, S. Nunes, Synthesis and characterization of new sulfonated poly (arylene ether 1, 3, 4-oxadiazole) s, *Reactive and Functional Polymers*, 61 (2004) 171-182.
- [576] L. Carrette, K. Friedrich, U. Stimming, Fuel cells—fundamentals and applications, *Fuel cells*, 1 (2001) 5-39.
- [577] N. Sammes, R. Bove, K. Stahl, Phosphoric acid fuel cells: Fundamentals and applications, *Current opinion in solid state and materials science*, 8 (2004) 372-378.
- [578] S. Narayanan, S.-P. Yen, L. Liu, S. Greenbaum, Anhydrous proton-conducting polymeric electrolytes for fuel cells, *The Journal of Physical Chemistry B*, 110 (2006) 3942-3948.

- [579] M. Kawahara, J. Morita, M. Rikukawa, K. Sanui, N. Ogata, Synthesis and proton conductivity of thermally stable polymer electrolyte: poly (benzimidazole) complexes with strong acid molecules, *electrochimica Acta*, 45 (2000) 1395-1398.
- [580] X. Glipa, B. Bonnet, B. Mula, D.J. Jones, J. Rozière, Investigation of the conduction properties of phosphoric and sulfuric acid doped polybenzimidazole, *Journal of Materials Chemistry*, 9 (1999) 3045-3049.
- [581] J.A. Asensio, E.M. Sánchez, P. Gómez-Romero, Proton-conducting membranes based on benzimidazole polymers for high-temperature PEM fuel cells. A chemical quest, *Chemical Society Reviews*, 39 (2010) 3210-3239.
- [582] B. Xing, O. Savadogo, The effect of acid doping on the conductivity of polybenzimidazole (PBI), *Journal of New Materials for Electrochemical Systems*, 2 (1999) 95-102.
- [583] O. Savadogo, B. Xing, Hydrogen/oxygen polymer electrolyte membrane fuel cell (PEMFC) based on acid-doped polybenzimidazole (PBI), *Journal of New Materials for Electrochemical Systems*, 3 (2000) 343-347.
- [584] H. Vogel, C. Marvel, Polybenzimidazoles, new thermally stable polymers, *Journal of Polymer Science*, 50 (1961) 511-539.
- [585] D. Seel, B. Benicewicz, L. Xiao, T. Schmidt, High - temperature polybenzimidazol - based membranes, *Handbook of fuel cells*, (2009).
- [586] S. Galbiati, A. Baricci, A. Casalegno, R. Marchesi, Degradation in phosphoric acid doped polymer fuel cells: A 6000 h parametric investigation, *International Journal of Hydrogen Energy*, 38 (2013) 6469-6480.
- [587] D. Puppen, Environmental evaluation of biofuels, *Periodica Polytechnica Social and Management Sciences*, 10 (2002) 95-116.
- [588] A. Bauen, G. Berndes, M. Junginger, M. Londo, F. Vuille, R. Ball, T. Bole, C. Chudziak, A. Faaij, H. Mozaffarian, Bioenergy: a sustainable and reliable energy source. A review of status and prospects, *Bioenergy: a sustainable and reliable energy source. A review of status and prospects*, (2009).
- [589] OECD-FAO Agricultural outlook 2011-2020, in, 2011.
- [590] A. Demirbas, Biofuels sources, biofuel policy, biofuel economy and global biofuel projections, *Energy conversion and management*, 49 (2008) 2106-2116.
- [591] A.I.F. Sheet, *Renewables in Global Energy Supply*, (2002).
- [592] G. Szabó, I. Fazekas, K. Kisari, T. Buday, G. Szabó, S. Szabó, M. Paládi, A. Kerényi, The environmental and economic aspects of a biogas power plant, *Energy and Sustainability V*, 186 (2014) 149.
- [593] F. Bauer, C. Hulteberg, T. Persson, D. Tamm, Biogas upgrading-Review of commercial technologies, *SGC Rapport*, (2013).
- [594] L. Guerreiro, J. Castanheiro, I. Fonseca, R. Martin-Aranda, A. Ramos, J. Vital, Transesterification of soybean oil over sulfonic acid functionalised polymeric membranes, *Catalysis Today*, 118 (2006) 166-171.
- [595] S. Baroutian, M.K. Aroua, A.A.A. Raman, N.M. Sulaiman, A packed bed membrane reactor for production of biodiesel using activated carbon supported catalyst, *Bioresource technology*, 102 (2011) 1095-1102.
- [596] M. Dube, A. Tremblay, J. Liu, Biodiesel production using a membrane reactor, *Bioresource technology*, 98 (2007) 639-647.
- [597] S. Baroutian, M.K. Aroua, A.A.A. Raman, N.M.N. Sulaiman, Methanol recovery during transesterification of palm oil in a $\text{TiO}_2/\text{Al}_2\text{O}_3$ membrane reactor: experimental study and neural network modeling, *Separation and purification Technology*, 76 (2010) 58-63.
- [598] W. Shi, B. He, J. Ding, J. Li, F. Yan, X. Liang, Preparation and characterization of the organic-inorganic hybrid membrane for biodiesel production, *Bioresource technology*, 101 (2010) 1501-1505.

- [599] J. Castanheiro, A. Ramos, I. Fonseca, J. Vital, Esterification of acetic acid by isoamyl alcohol over catalytic membranes of poly (vinyl alcohol) containing sulfonic acid groups, *Applied Catalysis A: General*, 311 (2006) 17-23.
- [600] M. Zhu, B. He, W. Shi, Y. Feng, J. Ding, J. Li, F. Zeng, Preparation and characterization of PSSA/PVA catalytic membrane for biodiesel production, *Fuel*, 89 (2010) 2299-2304.
- [601] L. Guerreiro, P. Pereira, I. Fonseca, R. Martin-Aranda, A. Ramos, J. Dias, R. Oliveira, J. Vital, PVA embedded hydrotalcite membranes as basic catalysts for biodiesel synthesis by soybean oil methanolysis, *Catalysis Today*, 156 (2010) 191-197.
- [602] A. Villa, J.-P. Tessonnier, O. Majoulet, D.S. Su, R. Schlögl, Amino-functionalized carbon nanotubes as solid basic catalysts for the transesterification of triglycerides, *Chemical Communications*, (2009) 4405-4407.
- [603] J. Saleh, A.Y. Tremblay, M.A. Dubé, Glycerol removal from biodiesel using membrane separation technology, *Fuel*, 89 (2010) 2260-2266.
- [604] P. Wei, L.-H. Cheng, L. Zhang, X.-H. Xu, H.-I. Chen, C.-j. Gao, A review of membrane technology for bioethanol production, *Renewable and Sustainable Energy Reviews*, 30 (2014) 388-400.
- [605] H.-J. Huang, S. Ramaswamy, U. Tschirner, B. Ramarao, A review of separation technologies in current and future biorefineries, *Separation and Purification Technology*, 62 (2008) 1-21.
- [606] W. Parawira, M. Tekere, Biotechnological strategies to overcome inhibitors in lignocellulose hydrolysates for ethanol production: review, *Critical reviews in biotechnology*, 31 (2011) 20-31.
- [607] G. Murthy, S. Sridhar, M.S. Sunder, B. Shankaraiah, M. Ramakrishna, Concentration of xylose reaction liquor by nanofiltration for the production of xylitol sugar alcohol, *Separation and purification technology*, 44 (2005) 221-228.
- [608] M. Balat, H. Balat, C. Öz, Progress in bioethanol processing, *Progress in energy and combustion science*, 34 (2008) 551-573.
- [609] H. Udriot, S. Ampuero, I. Marison, U. Von Stockar, Extractive fermentation of ethanol using membrane distillation, *Biotechnology letters*, 11 (1989) 509-514.
- [610] X. Zhan, J. Li, J. Huang, C. Chen, Ethanol perm-selective membranes by pervaporation, *Prog Chem*, 20 (2008) 1416-1426.
- [611] L.M. Vane, Separation technologies for the recovery and dehydration of alcohols from fermentation broths, *Biofuels, Bioproducts and Biorefining*, 2 (2008) 553-588.
- [612] S.L. Schmidt, M.D. Myers, S.S. Kelley, J.D. McMillan, N. Padukone, Evaluation of PTMSP membranes in achieving enhanced ethanol removal from fermentations by pervaporation, in: *Biotechnology for Fuels and Chemicals*, Springer, 1997, pp. 469-482.
- [613] S. Basu, A.L. Khan, A. Cano-Odena, C. Liu, I.F. Vankelecom, Membrane-based technologies for biogas separations, *Chemical Society Reviews*, 39 (2010) 750-768.
- [614] P. Ylivero, J. Akinbomi, M.J. Taherzadeh, Membrane bioreactors' potential for ethanol and biogas production: a review, *Environmental technology*, 34 (2013) 1711-1723.
- [615] S. Rasi, A. Veijanen, J. Rintala, Trace compounds of biogas from different biogas production plants, *Energy*, 32 (2007) 1375-1380.
- [616] R.W. Baker, Future directions of membrane gas separation technology, *Industrial & Engineering Chemistry Research*, 41 (2002) 1393-1411.
- [617] J. Mohr, D. Paul, I. Pinnau, W. Koros, Surface fluorination of polysulfone asymmetric membranes and films, *Journal of membrane science*, 56 (1991) 77-98.
- [618] M.D. Guiver, G.P. Robertson, Y. Dai, F. Bilodeau, Y.S. Kang, K.J. Lee, J.Y. Jho, J. Won, Structural characterization and gas - transport properties of brominated matrimid polyimide, *Journal of Polymer Science Part A: Polymer Chemistry*, 40 (2002) 4193-4204.
- [619] S. Hess, C. Staudt, Variation of esterification conditions to optimize solid-state crosslinking reaction of DABA-containing copolyimide membranes for gas separations, *Desalination*, 217 (2007) 8-16.

- [620] Y. Kamiya, K. Mizoguchi, T. Hirose, Y. Naito, Sorption and dilation in poly (ethyl methacrylate)–carbon dioxide system, *Journal of Polymer Science Part B: Polymer Physics*, 27 (1989) 879-892.
- [621] A. Bos, I. Pünt, M. Wessling, H. Strathmann, Plasticization-resistant glassy polyimide membranes for CO₂/CO₄ separations, *Separation and Purification Technology*, 14 (1998) 27-39.
- [622] A. Ismail, W. Lorna, Suppression of plasticization in polysulfone membranes for gas separations by heat-treatment technique, *Separation and purification technology*, 30 (2003) 37-46.
- [623] C. Cao, T.-S. Chung, Y. Liu, R. Wang, K. Pramoda, Chemical cross-linking modification of 6FDA-2, 6-DAT hollow fiber membranes for natural gas separation, *Journal of membrane science*, 216 (2003) 257-268.
- [624] S.S. Hosseini, M.M. Teoh, T.S. Chung, Hydrogen separation and purification in membranes of miscible polymer blends with interpenetration networks, *Polymer*, 49 (2008) 1594-1603.
- [625] T. Visser, N. Masetto, M. Wessling, Materials dependence of mixed gas plasticization behavior in asymmetric membranes, *Journal of Membrane Science*, 306 (2007) 16-28.