# **Critical Mineral Resources of the United States - Graphite**

Course No: P01-004

Credit: 1 PDH

James R. Weaver, P.E.



Continuing Education and Development, Inc. 22 Stonewall Court Woodcliff Lake, NJ 07677

P: (877) 322-5800 info@cedengineering.com



# **Graphite**


Chapter J of

Critical Mineral Resources of the United States—Economic and Environmental Geology and Prospects for Future Supply



Professional Paper 1802–J

## **Periodic Table of Elements**



Modified from Los Alamos National Laboratory Chemistry Division; available at http://periodic.lanl.gov/images/periodictable.pdf.

# **Graphite**

By Gilpin R. Robinson, Jr., Jane M. Hammarstrom, and Donald W. Olson

Chapter J of

Critical Mineral Resources of the United States—Economic and Environmental Geology and Prospects for Future Supply

Edited by Klaus J. Schulz, John H. DeYoung, Jr., Robert R. Seal II, and Dwight C. Bradley

Professional Paper 1802-J

# U.S. Department of the Interior

RYAN K. ZINKE, Secretary

## **U.S. Geological Survey**

William H. Werkheiser, Acting Director

U.S. Geological Survey, Reston, Virginia: 2017

For more information on the USGS—the Federal source for science about the Earth, its natural and living resources, natural hazards, and the environment—visit https://www.usgs.gov or call 1–888–ASK–USGS.

For an overview of USGS information products, including maps, imagery, and publications, visit https://store.usgs.gov/.

Any use of trade, firm, or product names is for descriptive purposes only and does not imply endorsement by the U.S. Government.

Although this information product, for the most part, is in the public domain, it also may contain copyrighted materials as noted in the text. Permission to reproduce copyrighted items must be secured from the copyright owner.

#### Suggested citation:

Robinson, G.R., Jr., Hammarstrom, J.M., and Olson, D.W., 2017, Graphite, chap. J of Schulz, K.J., DeYoung, J.H., Jr., Seal, R.R., II, and Bradley, D.C., eds., Critical mineral resources of the United States—Economic and environmental geology and prospects for future supply: U.S. Geological Survey Professional Paper 1802, p. J1–J24, https://doi.org/10.3133/pp1802J.

ISSN 2330-7102 (online)

# **Contents**

Abstract	J1
Introduction	J1
Commercial Classifications of Graphite	J1
Natural Graphite	J3
Synthetic Graphite	J3
Uses and Applications	J3
Demand and Availability of Supply	J4
Graphite Prices and Pricing	J4
Substitutes for Natural Graphite	J4
Strategic and Critical Resource Issues	J5
Geology	J5
Geochemistry	J5
Mineralogy	J5
Deposit Types	J6
Amorphous Graphite Deposits	J6
Deposits of Flake Graphite Disseminated in Metasedimentary Rocks	J7
Vein Deposits Containing Lump or Chip Graphite	J15
Mining and Beneficiation Methods	J16
Resources and Production	J16
Distribution of Graphite Deposits and Districts	J16
World Graphite Production and Resources	J17
Exploration for New Deposits	J19
Environmental Considerations	J19
Mine Waste Characteristics	J19
Human Health Concerns	J20
Ecological Health Concerns	J20
Carbon Footprint	J21
Regulatory and Environmental Considerations	J21
Problems and Future Research	J21
References Cited	J22

# **Figures**

J1.	Diagram showing the arrangement of carbon atoms in graphite	J6
J2.	World map showing locations of major graphite deposits and districts in the world, by commodity type	J14
J3.	Plot of grade and tonnage for some of the amorphous and crystalline graphite deposits listed in table J3, by deposit type	J16
J4.	Pie chart showing average annual natural graphite production for the period 2006–10, by country or region and amount	J17
Table	es e	
J1.	Characteristics of graphite commodities, deposits, and uses, by commodity type.	J2
J2.	Selected physical properties of graphite	J3
J3.	Location, grade, tonnage and other data for selected graphite deposits and districts of the world	J8
J4.	Estimates of world graphite resources, by country, commodity type, and resource category, in thousand metric tons of recoverable graphite	J18

# **Conversion Factors**

International System of Units to Inch/Pound

Multiply	Ву	To obtain
	Length	
angstrom (Å) (0.1 nanometer)	0.003937	microinch
angstrom (Å) (0.1 nanometer)	0.000937	mil
micrometer (µm) [or micron]	0.000003937	mil
millimeter (mm)	0.03937	
		inch (in.)
centimeter (cm)	0.3937	inch (in.)
meter (m)	3.281	foot (ft)
meter (m)	1.094	yard (yd)
kilometer (km)	0.6214	mile (mi)
	Area	
hectare (ha)	2.471	acre
square kilometer (km²)	247.1	acre
square meter (m <sup>2</sup> )	10.76	square foot (ft²)
square centimeter (cm <sup>2</sup> )	0.1550	square inch (ft²)
square kilometer (km²)	0.3861	square mile (mi <sup>2</sup> )
	Volume	
milliliter (mL)	0.03381	ounce, fluid (fl. oz)
liter (L)	33.81402	ounce, fluid (fl. oz)
liter (L)	1.057	quart (qt)
liter (L)	0.2642	gallon (gal)
cubic meter (m³)	264.2	gallon (gal)
cubic centimeter (cm³)	0.06102	cubic inch (in³)
cubic meter (m³)	1.308	cubic yard (yd³)
cubic kilometer (km³)	0.2399	cubic mile (mi³)
	Mass	
microgram (μg)	0.00000003527	ounce, avoirdupois (oz)
milligram (mg)	0.00003527	ounce, avoirdupois (oz)
gram (g)	0.03527	ounce, avoirdupois (oz)
gram (g)	0.03215075	ounce, troy
kilogram (kg)	32.15075	ounce, troy
kilogram (kg)	2.205	pound avoirdupois (lb)
ton, metric (t)	1.102	ton, short [2,000 lb]
ton, metric (t)	0.9842	ton, long [2,240 lb]
	Deposit grade	
gram per metric ton (g/t)	0.0291667	ounce per short ton (2,000 lb) (oz/T)
<u> </u>	Pressure	•
megapascal (MPa)	10	bar
gigapascal (GPa)	10,000	bar
	Density	
gram per cubic centimeter (g/cm³)	62.4220	pound per cubic foot (lb/ft³)
milligram per cubic meter (mg/m³)	0.00000006243	pound per cubic foot (lb/ft³)
	Energy	
joule (J)	0.0000002	kilowatthour (kWh)
joule (J)	$6.241 \times 10^{18}$	electronvolt (eV)
joule (J)	0.2388	calorie (cal)
kilojoule (kJ)	0.2388	kilocalorie (kcal)
knojouie (ki)	0.0002388	KHOCAIOHE (KCAI)

International System of Units to Inch/Pound—Continued

Multiply	Ву	To obtain
	Radioactivity	
becquerel (Bq)	0.00002703	microcurie (μCi)
kilobecquerel (kBq)	0.02703	microcurie (μCi)
	Electrical resistivity	
ohm meter (Ω-m)	39.37	ohm inch (Ω-in.)
ohm-centimeter ( $\Omega$ -cm)	0.3937	ohm inch ( $\Omega$ -in.)
watt per centimeter per degree Celsius (watt/cm °C)	693.1798	International British thermal unit inch per hour per square foot per degree Fahrenheit (Btu in/h ft² °F)
watt per meter kelvin (W/m-K)	6.9318	International British thermal unit inch per hour per square foot per degree Fahrenheit (Btu in/h ft² °F)

#### Inch/Pound to International System of Units

	Length	
nil	25.4	micrometer (µm) [or micron]
nch (in.)	2.54	centimeter (cm)
nch (in.)	25.4	millimeter (mm)
Foot (ft)	0.3048	meter (m)
mile (mi)	1.609	kilometer (km)
	Volume	
ounce, fluid (fl. oz)	29.57	milliliter (mL)
ounce, fluid (fl. oz)	0.02957	liter (L)
	Mass	
ounce, avoirdupois (oz)	28,350,000	microgram
ounce, avoirdupois (oz)	28,350	milligram
ounce, avoirdupois (oz)	28.35	gram (g)
ounce, troy	31.10 348	gram (g)
ounce, troy	0.03110348	kilogram (kg)
oound, avoirdupois (lb)	0.4536	kilogram (kg)
ton, short (2,000 lb)	0.9072	ton, metric (t)
on, long (2,240 lb)	1.016	ton, metric (t)
	Deposit grade	
ounce per short ton (2,000 lb) (oz/T)	34.285714	gram per metric ton (g/t)
	Energy	
kilowatthour (kWh)	3,600,000	joule (J)
electronvolt (eV)	$1.602 \times 10^{-19}$	joule (J)
	Radioactivity	
microcurie (μCi)	37,000	becquerel (Bq)
microcurie (μCi)	37	kilobecquerel (kBq)

Temperature in degrees Celsius (°C) may be converted to degrees Fahrenheit (°F) as follows:

$$^{\circ}F = (1.8 \times ^{\circ}C) + 32$$

Temperature in degrees Celsius (°C) may be converted to kelvin (K) as follows:

$$K = {}^{\circ}C + 273.15$$

Temperature in degrees Fahrenheit (°F) may be converted to degrees Celsius (°C) as follows:

$$^{\circ}C = (^{\circ}F - 32)/1.8$$

#### **Datum**

Unless otherwise stated, vertical and horizontal coordinate information is referenced to the World Geodetic System of 1984 (WGS 84). Altitude, as used in this report, refers to distance above the vertical datum.

# **Supplemental Information**

Specific conductance is given in microsiemens per centimeter at 25 degrees Celsius ( $\mu$ S/cm at 25 °C).

Concentrations of chemical constituents in soils and (or) sediment are given in milligrams per kilogram (mg/kg), parts per million (ppm), or parts per billion (ppb).

Concentrations of chemical constituents in water are given in milligrams per liter (mg/L), micrograms per liter ( $\mu$ g/L), nanogams per liter ( $\mu$ g/L), nanomoles per kilogram ( $\mu$ g/k), parts per million ( $\mu$ g), parts per billion ( $\mu$ g), or parts per trillion ( $\mu$ g).

Concentrations of suspended particulates in water are given in micrograms per gram ( $\mu$ g/g), milligrams per kilogram ( $\mu$ g/kg), or femtograms per gram (fg/g).

Concentrations of chemicals in air are given in units of the mass of the chemical (milligrams, micrograms, nanograms, or picograms) per volume of air (cubic meter).

Activities for radioactive constituents in air are given in microcuries per milliliter (µCi/mL).

Deposit grades are commonly given in percent, grams per metric ton (g/t)—which is equivalent to parts per million (ppm)—or troy ounces per short ton (oz/T).

Geologic ages are expressed in mega-annum (Ma, million years before present, or 10<sup>6</sup> years ago) or giga-annum (Ga, billion years before present, or 10<sup>9</sup> years ago).

For ranges of years, "to" and (or) the en dash ("-") mean "up to and including."

Concentration unit	Equals
milligram per kilogram (mg/kg)	part per million
microgram per gram (µg/g)	part per million
microgram per kilogram (μg/kg)	part per billion (10 <sup>9</sup> )

#### **Equivalencies**

```
part per million (ppm): 1 ppm=1,000 ppb=1,000,000 ppt=0.0001 percent part per billion (ppb): 0.001 ppm=1 ppb=1,000 ppt=0.0000001 percent part per trillion (ppt): 0.000001 ppm=0.001 ppb=1 ppt=0.00000000001 percent
```

#### **Metric system prefixes**

```
1 trillion
tera- (T-)
                         1 billion
giga- (G-)
                 10^{9}
mega- (M-)
                10^{6}
                         1 million
kilo-(k-)
                 10^{3}
                         1 thousand
                10^{2}
                         1 hundred
hecto-(h-)
                10
                         1 ten
deka- (da-)
deci- (d-)
                10^{-1}
                         1 tenth
                10^{-2}
centi- (c-)
                         1 hundredth
milli- (m-)
                10^{-3}
                         1 thousandth
micro- (µ-)
                10^{-6}
                         1 millionth
                 10^{-9}
                         1 billionth
nano- (n-)
                 10^{-12}
                         1 trillionth
pico- (p-)
                10^{-15}
femto-(f-)
                         1 quadrillionth
                10^{-18}
                         1 quintillionth
atto- (a-)
```

# **Abbreviations and Symbols**

 $^{\circ}$ C degree Celsius  $_{\mu m}$  micrometer  $_{cm}$  centimeter

g/cm³ gram per cubic centimeter

ISMI International Strategic Minerals Inventory

kg/cm<sup>2</sup> kilogram per square centimeter

km kilometer m meter

MRDS Mineral Resources Data System

NIOSH National Institute for Occupational Safety and Health

TWA time-weighted average

# **Graphite**

By Gilpin R. Robinson, Jr., Jane M. Hammarstrom, and Donald W. Olson

#### **Abstract**

Graphite is a form of pure carbon that normally occurs as black crystal flakes and masses. It has important properties, such as chemical inertness, thermal stability, high electrical conductivity, and lubricity (slipperiness) that make it suitable for many industrial applications, including electronics, lubricants, metallurgy, and steelmaking. For some of these uses, no suitable substitutes are available. Steelmaking and refractory applications in metallurgy use the largest amount of produced graphite; however, emerging technology uses in large-scale fuel cell, battery, and lightweight high-strength composite applications could substantially increase world demand for graphite.

Graphite ores are classified as "amorphous" (microcrystalline), and "crystalline" ("flake" or "lump or chip") based on the ore's crystallinity, grain-size, and morphology. All graphite deposits mined today formed from metamorphism of carbonaceous sedimentary rocks, and the ore type is determined by the geologic setting. Thermally metamorphosed coal is the usual source of amorphous graphite. Disseminated crystalline flake graphite is mined from carbonaceous metamorphic rocks, and lump or chip graphite is mined from veins in high-grade metamorphic regions. Because graphite is chemically inert and nontoxic, the main environmental concerns associated with graphite mining are inhalation of fine-grained dusts, including silicate and sulfide mineral particles, and hydrocarbon vapors produced during the mining and processing of ore. Synthetic graphite is manufactured from hydrocarbon sources using high-temperature heat treatment, and it is more expensive to produce than natural graphite.

Production of natural graphite is dominated by China, India, and Brazil, which export graphite worldwide. China provides approximately 67 percent of worldwide output of natural graphite, and, as the dominant exporter, has the ability to set world prices. China has significant graphite reserves, and China's graphite production is expected to increase, although rising labor costs and some mine production problems are developing. China is expected to continue to be the dominant exporter for the near future. Mexico and Canada export graphite mainly to the United States, which has not had domestic production of natural graphite since the 1950s. Most

graphite deposits in the United States are too small, low-grade, or remote to be of commercial value in the near future, and the likelihood of discovering larger, higher-grade, or favorably located domestic deposits is unlikely. The United States is a major producer of synthetic graphite.

#### Introduction

Graphite, which is a soft form of elemental carbon, is an industrial mineral commodity that is produced only in small amounts globally—worldwide production of approximately 1 million metric tons of graphite concentrate was reported as yearly production from 2010 to 2012 (Olson, 2012, 2013). The word graphite is derived from the Greek word for writing, graphein, which reflects the long use of graphite (mixed with clay) for the "lead" in pencils. The unique physical and chemical properties of graphite, particularly coarse crystalline graphite, make it useful for many industrial applications, and for some of those uses, no suitable substitutes are available. Although graphite is widely disseminated in many types of metamorphic and some igneous rocks, most occurrences have no economic importance. The significant deposits of graphite are found in carbonaceous sedimentary rocks that have been subjected to regional or contact metamorphism and in veins precipitated from fluids.

## **Commercial Classifications of Graphite**

Sources of commercial graphite include both natural graphite mined from rock and synthetic graphite manufactured from other carbonaceous materials. For commercial purposes, natural graphite is classified into the following three categories, according to its crystallinity, grain size, and morphology: amorphous, crystalline (flake), and crystalline (lump or chip). These commodity classes differ in the level of purity of the graphite, the proposed industrial use, the price, and the geologic setting in which the graphite occurs (table J1). Descriptions of (a) the graphite commodity classes and their industrial uses, and (b) their associated deposit types, geologic settings, and producing deposit locations are given

#### J2 Critical Mineral Resources of the United States—Graphite

Table J1. Characteristics of graphite commodities, deposits, and uses, by commodity type.

[Descriptions of graphite commodity classes and their industrial uses, commodity prices, and classes of associated deposit types and geologic settings are summarized from information in Klar (1958), Weis (1973), Krauss and others (1988), Sutphin (1991a–c), Simandl and Kenan (1997a–c), Taylor (2006), and Olson (2011, 2012, 2013). NA, not applicable; µm, micrometer; cm, centimeter; °C, degree Celsius; m, meter; \$, U.S. dollar]

Charactaristic	Commodity type					
Characteristic	Amorphous	Lump or chip	Synthetic			
Deposit type	Amorphous	Disseminated flake	Vein	NA		
Crystallinity	Microcrystalline	Crystalline	Crystalline	Microcrystalline to crystalline		
Properties (crystallinity, form)	Earthy to compact micro- crystalline aggregates; grain size is <4 μm	Well-developed crystal platelets, with grain size between 40 $\mu$ m and 4 cm (but generally $\leq$ 1 cm), and 1 to 150 $\mu$ m thick	Interlocking aggregates of coarse crystals. Available as powders to 10-cm pieces	Available in particle size from 2-µm powders to 2-cm pieces		
Origin	Contact metamorphism, often by diabasic or granitic intrusions, and (or) regional metamor- phism of carbonaceous sediments, often coal	Regional metamorphism of carbonaceous sedi- ments at or exceeding amphibolite facies conditions	Epigenetic veins and lodes formed from metamorphic fluids in high-grade metamorphic rocks, usually granulites	Produced by heat treat- ment (graphitization) of, or chemical deposi- tion from, hydrocarbon materials above 2,100 °C		
Orebody	Layers, seams, and lenses in carbonaceous rock, each a few meters thick and hundreds of meters to several kilometers in length; may be folded and faulted	Strata-bound; tabular or lense form, as much as 33 m thick and thou- sands of meters long. Irregular in hinge areas of folds. The lenses have variable graphite content internally and between lenses	Vein and fracture-filling within or crosscutting metamorphic structures and rock contacts. Individual veins range from 0.05 to 3 m thick, although usually less than 0.3 m, and extend up to hundreds of meters, although rarely more than tens of meters	NA		
Ore grade (percent carbon)	50 to 90 (aggregates may contain nongraphitic carbonaceous material)	Generally 5 to 30, locally higher	40 to 90 (may require hand sorting)	NA		
Deposit tonnage (million metric tons)	0.1 to 500	0.1 to 100	Small; no reliable data for individual veins	NA		
Mine operations	Surface or underground mines using mecha- nized and sometimes hand methods	Generally open pit surface mines. Graphite grades and ease of mining enhanced by weather- ing destruction of gangue minerals	Mines are typically small, labor-intensive, and under- ground. Mines in Sri Lanka are from 30 to 400 m deep. Ore is hand sorted, washed, and screened	NA		
Product grade (percent graphite)	60 to 90	75 to 97	90 to 99.9	99.95		
Main uses	Refractories, steel industry, paint, coat- ings, and batteries	Refractories, brake linings, lubricants, batteries, and expandable graphite applications	Carbon brushes, brake linings, and lubricants	Batteries, carbon brushes graphite electrodes, nuclear moderator rods (porosity unsuitable fo refractory applications		
Prices (per metric ton)	December 2011 prices (80–85 percent graphite) ranged from \$600 to \$800	December 2011 prices (90% graphite, medium-large flake) ranged from \$1,150 to \$2,000	Prices in 2011 for Sri Lankan lump and chip graphite (99% graphite) ranged from \$1,700 to \$2,070. Prices vary by purity, grade, and size	December 2011 prices (99.9 percent graphite) ranged from \$7,000 to \$20,000, which was about 4 to 7 times that of flake graphite		
Major producers and resources (in order of pro- duction level)	China, Republic of Korea, Mexico, Austria	China, Brazil, India, Madagascar, Germany, Austria, Norway, Canada, Zimbabwe	Sri Lanka	China, Japan, United States, Germany (Roskill Information Services, Ltd., 2012)		

by Klar (1958), Weis (1973), Krauss and others (1988), and Taylor (2006). Descriptive models of the geology and characteristics of the deposit types that produce graphite are given by Sutphin and Bliss (1990), Sutphin (1991a–c), and Simandl and Kenan (1997a–c). A summary of information from these and other sources follows.

#### Natural Graphite

Natural graphite is mined from deposits in metamorphic rocks, such as marble, schist, and gneiss, and from accumulations in vein deposits. Natural graphite typically forms as a result of metamorphism (regional or contact) of accumulations of organic matter in sedimentary rocks. Commercial deposits of graphite occur in three types of geologic settings that generally correspond to the following commodity classes (table J1):

- a. "Amorphous graphite" is the commercial designation for earthy to compact fine-grained graphite that generally results from thermal metamorphism of coal. Commercial deposits typically contain more than 1 million metric tons of ore that is more than 75 percent carbon. Both the raw ore and the commodity may contain nongraphitic carbonaceous material in addition to graphite.
- b. "Flake graphite" is the commercial designation for well-developed crystal platelets of graphite that are between 40 micrometers (μm) and 4 centimeters (cm—but generally less than or equal to 1 cm) in size and that are disseminated in beds of carbonaceous sediments that have been subjected to amphibolite-facies or higher grade regional metamorphism. Commercial deposits generally contain more than 200,000 metric tons of ore that grade greater than 8 percent graphite. Disseminated flake graphite deposits are located in belts of crystalline metamorphic rock that are predominately Archean to late Proterozoic in age.
- c. "Lump or chip" is the commercial designation for interlocking aggregates of coarse graphite crystals that occur as veins or fracture-fillings in igneous and crystalline metamorphic rocks that commonly are of Precambrian age. The only commercial deposits occur in Sri Lanka where families of veins that are up to 3 meters (m) thick and which consist of 60 to 95 percent graphite are mined to depths of 30 to 650 m (Touzain and others, 2010). The ore may be hand sorted to provide a product grade that exceeds 90 percent. No reliable data on the tonnages of individual vein deposits are available, but most of the deposits are small and likely do not exceed 100,000 metric tons.

#### Synthetic Graphite

Most of the graphite used by industries in the United States is synthetic. Synthetic graphite of high purity is produced by heat treatment (graphitization) of, or chemical deposition from, hydrocarbon materials above 2,100 degrees Celsius (°C). High-temperature processing is required to transform the precursor carbon forms to a graphite structure and to vaporize impurities, which include hydrogen, metals, nitrogen, organic compounds, and sulfur in the source materials. As a result of this treatment, synthetic graphite is more than 99.9 percent graphite, but it has slightly higher porosity, lower density, lower electrical conductivity, and a much higher price than natural flake graphite. Synthetic graphite is available in particle sizes ranging from 2-µm powders to 2-cm pieces; the morphology varies from flakey in fine powders to irregular grains and needles in coarser products.

#### **Uses and Applications**

Graphite has physical and chemical properties of both metals and nonmetals, which make it ideally suited for many industrial and technology applications. The metallic properties include high thermal and electrical conductivity (table J2). The nonmetallic properties include inertness to most chemical reagents (strong acids, bases, solvents, and fluxes), high thermal resistance, low thermal expansion, and excellent cleavage and lubricity (slipperiness). In a nonoxidizing atmosphere, graphite remains stable to temperatures above 3,000 °C. Graphite has a hardness of 1 to 2 on the Mohs scale and is thus extremely soft.

**Table J2.** Selected physical properties of graphite.

[Modified from Krauss and others (1988). g/cm³, gram per cubic centimeter;  $^{\circ}$ C, degree Celsius; watt/cm  $^{\circ}$ C, watt per centimeter per degree Celsius;  $\Omega$ -cm, ohm-centimeter]

_	
Property	Description
Composition	Carbon
Color	Gray to black, metallic luster
Hardness (Mohs scale)	0.5 to 1
Density (g/cm³)	2.09 to 2.26
Morphology	Hexagonal system; perfect basal cleavage; usually platy
Melting point	About 3,550 °C in nonoxidizing conditions; decomposes above 600 °C in oxidizing conditions
Miscellaneous	Chemically inert; nontoxic; high ther- mal and electrical conductivity; high lubricity (natural lubricant)
Thermal conductivity (watt/cm °C)	<i>a</i> axis: 4.0 <i>c</i> axis: 0.8
Thermal expansion coefficient (1/°C)	<i>a</i> axis: $1 \times 10^{-7}$ <i>c</i> axis: $140 \times 10^{-7}$
Electrical resistivity (Ω-cm×10 <sup>4</sup> )	<i>a</i> axis: 1 to 100 <i>c</i> axis: 10,000

Some of the major end uses of graphite are in brake linings, refractories, and steelmaking. Batteries, brushes for electrical motors, foundry materials, fuel cells, and high-temperature lubricants are additional end uses of graphite. Graphite forms intercalation compounds with alkali metal vapors—usually potassium, lithium, rubidium, and cesium—where the metal ions fit between the planar carbon sheets of the graphite structure. These compounds have applications in the energy sector and other technologies. The industrial uses and associated commercial value of natural graphite depend on the characteristics and crystallinity of the mined graphite (table J1).

Fine-grained microcrystalline graphite powder (amorphous graphite) is used extensively in foundry and refractory applications, as a source of carbon in steelmaking, and in other applications where additions of graphite improve the manufacturing process or end product. Coarse-grained crystalline graphite in the form of separate lamellar crystals (flake graphite) has high value and is used in high-temperature lubricants, high-quality foundry and refractory ware, powder metallurgy, coatings, and battery and fuel cell applications. Crystalline flake graphite accounted for about 50 percent of natural graphite usage in the United States in the past decade.

Massive crystalline graphite from vein deposits (lump or chip graphite) has the highest purity and grain size of the natural graphite sold commercially. Because of its purity and crystallinity, many of the highest quality electrical motor brushes and other current-carrying carbon products use formulations of graphite from vein deposits.

Synthetic graphite is used in many applications that require high-purity graphite, including anticorrosion products, batteries, carbon brushes, coatings, conductive fillers, electrodes and electrolytic processes, fuel cell bipolar plates, and nuclear moderator rods. Synthetic graphite is unsuitable for foundry applications because of its increased porosity relative to natural graphite. Synthetic graphite is used in more applications in North America than natural graphite and accounts for a significant share of the graphite market.

## **Demand and Availability of Supply**

No natural graphite was reported to have been mined in the United States in 2010 (Olson, 2012), and the major domestic sources of industrial graphite included imports of natural graphite, mostly from China, Mexico, Canada, Brazil, and Madagascar (in order of tonnage of imports), and synthetic graphite manufactured from carbonaceous materials. In 2010, 65,400 metric tons of natural graphite valued at an estimated \$52 million was reported to have been imported into the United States for domestic consumption and 134,000 metric tons of synthetic graphite valued at an estimated \$1.07 billion was reported to have been produced in the United States (Olson, 2012).

#### **Graphite Prices and Pricing**

Graphite is not traded on any commodity exchange. Commodity prices are subject to negotiation between buyer and seller and depend on carbon content, flake size and distribution (for crystalline flake), and the amount and nature of impurities. China is the dominant global natural graphite producer and has been the world price setter for decades. Four price series for graphite commodities based on production and value data reported by the U.S. Geological Survey (Olson, 2013) and Roskill Information Services, Ltd. (2012) are given in table J1. They are (a) microcrystalline (amorphous) graphite powder (from Mexico), which is currently in a long-term decline in importance because its low-technology end uses are becoming obsolete; (b) crystalline flake, which has become the most important natural graphite commodity in the past few decades and accounts for 80 to 90 percent of the value of U.S. imports of natural graphite; (c) lump graphite from Sri Lanka, which is a specialty product because its relatively high price results in low demand, and (d) synthetic graphite, which is a specialty product used primarily for applications that require high purity; its high price also limits demand. The price of microcrystalline (amorphous) graphite powder (80 to 85 percent carbon) ranged from \$600 to \$800 per metric ton in 2011; that of flake graphite (90 percent graphite) ranged from \$1,150 to \$2,000 per metric ton; Sri Lankan lump and chip graphite (99 percent graphite), from \$1,700 to \$2,070, depending on purity, grade, and particle size; and synthetic graphite (99.9 percent graphite), from \$7,000 to \$20,000 per metric ton, which is about four to seven times that of flake graphite (table J1).

In 2010, graphite prices increased more rapidly for crystalline flake graphite than for amorphous graphite owing to increased demand for crystalline graphite used in friction material applications, such as brake linings, high-quality refractories, and lubricants, and in the manufacturing of graphite foils and long-life alkaline batteries (Industrial Minerals, 2010).

#### Substitutes for Natural Graphite

The most common substitutes for natural graphite are other forms of carbon. Manufactured synthetic graphite powders and graphite recovered from discarded foundry and manufactured materials can substitute for natural graphite in some applications, depending on the relative price. In steelmaking and some foundry applications, petroleum coke, anthracite, and synthetic graphite can be used instead of natural graphite. Synthetic graphite and natural graphite powder are commonly substituted for each other, or mixtures containing both kinds are prepared for customers (Taylor, 2006). Crystalline graphite is recovered from some foundry and refractory materials, although its recovery cost makes it noncompetitive relative to natural graphite for some applications (Weis, 1973; Olson, 2013).

#### Strategic and Critical Resource Issues

Graphite is considered a critical and strategic mineral because of its essential applications in the aerospace and energy sectors (such as refractory and foundry applications in the steel and metal industries and use in high-temperature lubricants, high-strength lightweight composite materials, batteries, modern nuclear reactors, fuel cells, electric motors, and evolving electronic applications that anticipate rapid growth in demand for graphite). The high concentration of resource supply from few countries could increase the commodity's susceptibility to market manipulation or disruption (Krauss and others, 1988; Taylor, 2006; European Commission, 2014). The United States has not produced natural graphite since the 1950s; China, Mexico, and Canada, in order of import supply, are the dominant sources of graphite imports to the United States (Olson, 2013). China has very low labor and production costs, and, with aggressive marketing, it established dominance in the world market in the 1980s (Taylor, 2006; Olson, 2013). China's graphite production is expected to increase and remain dominant in the world graphite market for the near future (Olson, 2013). China's rapidly growing domestic market for graphite may restrict future exports, however, which has raised concerns about possible supply shortages of graphite, particularly crystalline flake graphite, needed for anticipated large-scale fuel cell and battery applications; such applications could dramatically increase world demand for graphite (Taylor, 2006; Olson, 2013; Olson and others, 2016).

Graphite has played an important role in the emerging noncarbon energy sector and is used in several new energy applications. In energy production applications, graphite is used in pebbles for modular nuclear reactors and in highstrength composites for wind, tide, and wave turbines. In energy storage applications, graphite is used in bipolar plates for fuel cells and flow batteries, in anodes for lithium-ion batteries, in electrodes for supercapacitors, in high-strength composites for fly wheels, in phase change heat storage, and in solar boilers. In energy management applications, graphite is used in high-performance thermal insulation and in silicon chip heat-dissipation applications. These new energy applications commonly use specialty graphite products with such properties as extreme purity (>99.9 percent graphite), very large or small (nano) particle size, and perfect crystallinity. Current graphite capacity may not be adequate for the increasing demands of these new energy applications, which, when fully implemented, may require double the current graphite supply, especially of high-purity crystalline flake graphite (O'Driscoll, 2010; Olson and others, 2016).

# Geology

#### Geochemistry

Carbon is the fourth most abundant element in the solar system, and in terms of its abundance in Earth's crust, is ranked about 12th to 17th in abundance, with an estimated crustal concentration between 180 and 270 parts per million. The abundance of carbon in Earth's crust is difficult to determine because carbon stores exist and cycle between rock, sediment, atmosphere, biosphere, and ocean reservoirs. The behavior of carbon in its geochemical cycle is influenced by the form in which the carbon occurs. Most of the carbon in Earth's crust (approximately 80 to 90 percent) is contained in carbonate minerals in carbonate rocks. Most of the remaining carbon in the Earth system occurs in living and fossil organic matter and as carbon dioxide (CO<sub>2</sub>) in the atmosphere or dissolved in the ocean. These remaining carbon forms dominate the carbon cycle. Graphite makes up only a small proportion of the carbon in Earth's crust, probably less than 0.5 percent, and much of this graphite likely formed by high-temperature thermal alteration of organic matter from biogenic sources deposited in sedimentary rocks and subsurface reservoirs. The mineral graphite is stable and inert in the crustal environment and is unchanged under surface weathering conditions. Burial and thermal metamorphism tends only to recrystallize graphite. Therefore, graphite is largely isolated from the overall carbon cycle.


## **Mineralogy**

Graphite is one of four forms of crystalline elemental carbon; the others are carbon nanotubes, diamond, and fullerenes. Graphite crystallizes in the hexagonal system, with rhombohedral symmetry, commonly forming six-sided tabular crystal flakes. It occurs naturally in metamorphic rocks and in some igneous rocks. Well-crystallized graphite flakes have a black metallic luster, whereas microcrystalline material is black and earthy with an amorphous appearance.

The crystal structure of graphite consists of carbon atoms tightly arranged in parallel-stacked (*c* axis, fig. J1), planar honeycomb-lattice sheets (*a* axis, fig. J1). When the graphite structure is only a 1-atom-thick planar sheet, it is called graphene.

The physical properties of graphite are listed in table J2. Many properties listed in table J2 vary by crystallographic orientation (*a*-axis and *c*-axis values, table J2) because of differences in bonding within (*a* axis, fig. J1) and between lattice sheets (*c* axis, fig. J1). The intraplanar (*a* axis) covalent bonding in graphite sheets is strong, but the electrostatic interlayer (*c* axis) forces holding the sheets together are weak, resulting in delocalized electrons that are free to move between sheets, which separates the sheets and allows them to

Figure J1. Diagram showing the arrangement of carbon atoms in graphite, which consists of stacks of parallel sheets of carbon atoms (red circles in the figure), with each sheet containing hexagonal arrays of carbon atoms. Each carbon atom within a sheet is connected to its three nearest neighbors by covalent bonds that separate the atoms by a distance of 1.415 angstroms (Å)—an angstrom is one ten-billionth of a meter. The stacked sheets (shown here in their A and B orientation) are held together by weak intermolecular van der Waals' forces and are separated from each other by a distance of 3.354 Å. The arrangement of atoms defined by the dashed lines portrays one hexagonal (2H) unit cell of graphite. Modified from Kraus and others, 1989.



slide across one another easily. This gives graphite a density of 2.09 to 2.26 grams per cubic centimeter (g/cm<sup>3</sup>), perfect basal (one-plane) cleavage, softness (0.5 to 1 on the Mohs scale), a greasy feel, and self-lubricating properties that make it useful as a lubricant. The ratio of force required to induce gliding of graphite sheets relative to compression force is low, resulting in high lubricity. These delocalized interlayer electrons also give graphite its high electrical and thermal conductivity. Graphite is the most electrically and thermally conductive of the nonmetallic elements (a-axis values, table J2); however, the intraplanar covalent bonds are very strong and require high energy to break them. These bonding properties make graphite chemically inert and physically stable at high temperatures (refractory). Graphite resists chemical attack by most reagents and is infusible in most common fluxes. Thermal oxidation of graphite in the presence of oxygen begins at about 300 °C, and the rate increases with temperature; however, it is stable in a nonoxidizing atmosphere to above 3,000 °C. Graphite sublimes between 3,300 °C and 3,500 °C at 1.033 kilograms per square centimeter (kg/cm<sup>2</sup>) and it melts at approximately 3,550 °C at a triple point under a pressure of 88 kg/cm<sup>2</sup>. Graphite is flexible but not elastic. All these properties combined make graphite desirable for many industrial applications.

## **Deposit Types**

Natural graphite is a common constituent of metasedimentary rocks and is mined in three geologic settings: (a) microcrystalline (amorphous) graphite deposits formed by metamorphism of coal, petroleum, or carbon-rich sediments, (b) disseminated flakes in metamorphic rock (flake graphite), and (c) graphite vein deposits (lump or chip graphite). Similar to most industrial mineral commodities, the economics of

a deposit depend on its location and transportation costs to markets in addition to deposit grade, size, and mining characteristics. Impurities in the deposit, such as silica, sulfides, or biotite, may limit the economic potential of a deposit.

#### Amorphous Graphite Deposits

Amorphous graphite deposits, which are formed by thermal metamorphism of coal, petroleum pools, or other highly carbonaceous sedimentary rocks, contain earthy to compact masses of microcrystalline graphite. Deposits may consist of multiple layers, seams, and lenses containing 50 to 90 percent carbon; each deposit is a few meters thick and up to a kilometer in length and lies within clastic metasedimentary rocks. The carbon content of amorphous deposits is dependent on the amount of carbon present in the original sediments, and the grade, tonnage, and purity of the deposit depend upon the characteristics of the precursor coal sequence or carbonaceous material. Deposits in metamorphosed massive coal seams may contain as much as 90 percent graphitic carbon, whereas deposits in other carbonaceous sediments or impure coal sequences commonly range from 25 to 60 percent carbon.

Chemical and isotopic biomarkers found in natural graphite provide evidence of its origin from ancient biological material. Amorphous graphite deposits occur in geologic settings and environments where coal and other organicrich sedimentary rocks, such as oil shale, occur, including (a) shoreline, fluvial-deltaic, and alluvial fan depositional environments in passive continental margin settings, and (b) lacustrine and shallow inland seas and margins in foreland, continental, sag, or intracontinental rift basin settings. Host rocks include conglomerate, metagraywacke, quartzite, and schist. The thermal metamorphism is commonly caused by

crosscutting diabasic or granitic intrusions with associated hornfels alteration of host rocks. Hornfels is a hard metamorphic rock formed by contact metamorphism of sedimentary rocks close to intrusive igneous bodies.

Graphite does not form until temperatures exceed 300 °C to 400 °C (Landis, 1971). The degree of metamorphism controls the degree of graphitization, and the ratio of graphite to nongraphitic carbon varies, but typically increases towards the heat source. Mineral impurities include meta-anthracite, anthracite, quartz, mica, pyrite, and other sulfides. Most currently mined deposits typically contain at least 80 percent carbon in deposits exceeding 1 million metric tons.

The world's main sources of amorphous graphite are the metamorphosed coal deposits in Sonora, Mexico; Siberia, Russia; and the large coal province stretching from China into the Korean peninsula (table J3). The deposits in Sonora, Mexico, are the most significant deposits of amorphous graphite in the Western Hemisphere. They occur in a series of beds in an area 30 kilometers (km) long by 15 km wide located 60 km southeast of Hermosillo. In the district, the orebodies average 3 m in thickness, but deformation can produce seams up to 7 m wide. Grades exceed 75 percent contained graphite and some contain as much as 95 percent. The Moradillas deposit (Lourdes area, Mexico) has been reinterpreted as formed from a graphitized hydrocarbon protolith owing to its vein-like structure and lack of evidence that it is metamorphosed coal (Taylor, 2006). In the United States, small amorphous graphite deposits occur in metamorphosed coal deposits in the Narragansett Basin, Rhode Island, and in deposits in northern Michigan. An additional U.S. example occurs at Raton, New Mexico, where a basalt dike intersects a coal seam.

# Deposits of Flake Graphite Disseminated in Metasedimentary Rocks

A large proportion of worldwide graphite production is derived from deposits of disseminated flake graphite found in metamorphic rocks, such as paragneiss (a gneiss derived from sedimentary rock), quartzite, and, sometimes, marble. These deposits formed when preexisting carbonaceous matter in the host sedimentary rock was converted to graphite during regional metamorphic conditions at or exceeding medium-pressure and medium-to-high-temperature conditions (amphibolite facies). These metamorphic conditions are sufficient to crystallize fully ordered graphite (Hoefs and Frey, 1976) and recrystallize the rock matrix. The precursor host rocks of these deposits are interpreted as occurring in depositional settings where organic-rich sediments accumulate and are preserved. These settings include sediment-starved intracratonic and continental margin basins with low-oxygen conditions at depth to accumulate organic sediments, and periods of transgression (compare with, for example, Wilde and others, 1999), when sea level rises relative to land, preserving organic-rich sediments without erosion. The sedimentary rocks that are deposited during transgression may

be deposited directly on existing basement rocks of the crust and are termed supracrustal rocks.

The metamorphic conditions sufficient to form these deposits occur in the roots of continental mountain belts formed by deformation of Earth's crust, and significant postmetamorphic uplift and erosion are required to expose deposits in minable settings. Alumina-rich paragneiss, quartzites, and marbles at or near the highest grade of regional metamorphism at medium pressure (granulite facies) are favorable host rocks for flake graphite deposits because of their granular texture, coarse grain size, and low mica content. Supracrustal metasedimentary belts with these metamorphic features are termed crystalline metamorphic basement; their worldwide distribution has been mapped by Chorlton (2007). Most flake graphite deposits are located in Precambrian crystalline metamorphic basement (fig. J2), principally of Neoarchean to Proterozoic eras; however, deposits could occur in crystalline basement of any age. Precambrian supracrustal metamorphic belts appear to be more extensive, and metamorphosed to higher grades, than Phanerozoic belts (Chacko and others, 1987).

The principal flake graphite deposits occur as stratabound lenses or layers; individual lenses in deposits are as much as tens of meters thick and hundreds of meters long. The lenses have variable graphite content, both within themselves and from one lens to another. The graphite content of a typical deposit varies from about 8 to 15 percent carbon, but the grade can vary from as low as 3 percent to about 60 percent carbon locally in individual deposits and between deposits. In Madagascar, one rich lens was reported to contain 60 percent graphite, and grades in the Kigluaik Mountains graphite district, Alaska, exceed 50 percent graphite in some areas (Coats, 1944). In paragneiss-hosted deposits, gangue (non-ore) minerals include in order of general abundance, feldspar, biotite, pyroxene, garnet, and sulfide minerals. Gangue minerals in carbonate-hosted deposits include calcite, pyroxene, feldspar, garnet, and sulfides. Flake graphite in crushed ore is separated from mineral impurities using washing, screening, flotation, and, sometimes, leach methods.

The highest graphite grades commonly are associated with rock contacts between marble and paragneiss or quartzite, lenses in fault zones, in segregations within fold crests, and in structures that acted as channels for metamorphic fluids, all suggesting structural control of mineralization. Although most carbon in these deposits is thought to be present in the original sedimentary rocks, some carbon enrichment may be caused by processes involving internal or external buffering or mixing of metamorphic fluids (Lamb and Valley, 1984; Newton, 1986).

Crystals in each deposit vary from a fraction of a millimeter to a few centimeters in size, usually reflecting the grain size in the parent rock. Most currently mined flake graphite deposits typically contain at least 8 to 12 percent graphitic carbon in deposits exceeding 0.5 million metric tons. Graphite is stable in the weathering environment; deposit grades and ease of mining are enhanced by weathering destruction of other minerals. Some deposits become so weathered that they can be mined with shovels and other hand tools.

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.

dentification	Name	Country State/Province		Latitude	Longitude
number	Name	Country	State/Province	Decimal degrees WGS	
1	Quebrada Del Gato	Argentina	San Juan	-31.43	-68.13
2	Undercliff	Australia	New South Wales	-28.66	152.21
3	Jack's Creek	Australia	Queensland	-20.67	147.87
4	Koppio-Uley mines	Australia	South Australia	-34.80	135.71
5	Munglinup River	Australia	Western Australia	-33.50	120.85
6	Doppl-Muehldorf-Zettlitz	Austria	Niederosterreich	48.38	15.45
7	Kaisersberg-Trieben	Austria	Steiermark	47.35	15.07
8	Itanhem	Brazil	Bahia	-17.10	-40.35
9	Itapacerica	Brazil	Minas Gerais	-20.43	-45.13
10	Pedra Azul	Brazil	Minas Gerais	-15.88	-45.13
11	Bisset Creek	Canada	Ontario	46.23	-78.07
12	Coronation	Canada	Ontario	45.29	-77.94
13	Graphite Lake-Ryerson-Todd area	Canada	Ontario	45.73	-79.08
14	Kirkham-Portland-Timmins area	Canada	Ontario	44.56	-76.57
15	Tagliamonte	Canada	Ontario	46.23	-78.07
16	Graphex-Graphico-Orwell Mines	Canada	Quebec	46.14	-75.55
17	North American Mine	Canada	Quebec	45.52	-75.55
18	St-Amime-Lac Des Iles	Canada	Quebec	46.25	-75.53
19	Lac Knife	Canada	Quebec	52.55	-61.18
20	Pollon Lake area	Canada	Saskatchewan	56.38	-103.13
21	Haikou	China	Hainan	20.08	110.42
22	Heling	China	Heilongjiang [Heilungkiang]	46.31	129.55
23	Jixi (Liu Mao)	China	Heilongjiang [Heilungkiang]	45.28	131.00
24	Liu Mao	China	Heilongjiang [Heilungkiang]	45.30	131.07
25	Honan deposits	China	Henan [Honan]	32.50	113.88
26	Hunan	China	Hunan	26.00	113.00
27	Panshi	China	Jilin [Kirin]	42.93	125.97
28	Hohot	China	Nei Mongol (Inner Mongolia)	40.81	111.62
29	Shandong Peninsula	China	Shandong [Shantung]	37.03	120.32
30	Xing He	China	_	40.88	113.88
31	Kolledeye	Czech Republic	_	49.22	14.45
32	Velke Vbrno-Konstantin Vvk	Czech Republic	_	50.13	17.33
33	Kropfmühl-Cesky Krumlov	Germany and Czech Republic	Bayern [Bavaria, Germany]	48.80	14.32

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.—Continued

Identification number	Record type	Ore type	Operation	Development status	Tonnage	Grade (% of carbon)
1	District	Crystalline (flake or lump?)	Unknown	Producer	_	_
2	Site	Amorphous	Surface	Past producer	793	32
3	Site	Amorphous	Surface,underground	Past producer	2,200	61
4	District	Flake, weathering	Surface,underground	Past producer	35,030	15
5	District	Flake	Surface,underground	Past producer	30,000	25
6	District	Flake	Surface	Producer	1,000,000	10
7	District	Amorphous	Underground	Producer	1,000,000	85
8	Site	Lump	Surface	Producer	2,778	40
9	Site	Flake, weathering	Surface	Producer	383,000	15.7
10	Site	Flake, weathering	Surface	Producer	26,800,000	11.9
11	Site	Flake	Surface	Prospect	4,938,000	15.58
12	Site	Flake	Unknown	Occurrence	_	_
13	District	Flake	Surface	Producer	Large	_
14	District	Flake	Surface	Producer	478,000	9
15	Site	Flake	Surface	Prospect	_	_
16	District	Flake	Surface	Producer	2,200,000	10
17	Site	Flake	Unknown	Past producer	_	_
18	Site	Flake	Surface	Producer	_	_
19	Site	Flake	Surface	Prospect	4,900,000	15.8
20	District	Flake	Unknown	Past producer	1,663,000	10.3
21	Site	Flake	Surface	Producer	5,000,000	3.7
22	Site	Amorphous	Unknown	Producer	_	_
23	Site	Amorphous	Surface	Past producer	300,000,000	85
24	Site	Flake	Unknown	Producer	3,000,000	18.5
25	District	Unknown	Unknown	Producer	_	_
26	District	Amorphous	Underground	Producer	_	_
27	Site	Amorphous	Underground	Producer	_	_
28	District	Crystalline (flake or lump?)	Surface	Producer	_	_
29	District	Flake	Surface	Producer	5,900,000	5
30	Site	Flake	Unknown	Producer	_	_
31	District	Flake	Surface,underground	Prospect	<del></del>	_
32	Site	Amorphous	Surface	Producer	200,000	50
33	District	Flake	Underground	Producer	_	16

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.—Continued

dentification	Name	Country	State/Province	Latitude	Longitude
number	ivalile	Country	State/Province	Decimal de	rees WGS 84
34	East Godavari	India	Andhra Pradesh	17.38	81.85
35	Khammam	India	Andhra Pradesh	17.38	81.33
36	Srikakulam	India	Andhra Pradesh	18.33	83.10
37	Visakhapatnam	India	Andhra Pradesh	18.02	82.93
38	Khamdih	India	Bihar	23.97	84.22
39	Sokra	India	Bihar	23.97	84.13
40	Dandatapa area	India	Odisha	20.80	84.60
41	Sargipali area	India	Odisha	20.90	83.08
42	Titlagarh area	India	Odisha	20.20	83.37
43	Tumdibandh-Phulbani area	India	Odisha	19.83	83.63
44	Tamatia mines	India	Rajasthan	23.62	74.50
45	Madurai	India	Tamil Nadu [Madras]	10.07	77.83
46	Chawia	Kenya	_	-3.46	38.38
47	Oldoinyo-Nyiro	Kenya	_	0.75	37.00
48	Yonghung-Kaechon area	Korea, North	Hamgyong-Namdo	39.83	127.43
49	Songjin deposits	Korea, North	Hwanghae-Namdo	40.67	129.20
50	Wolmyong-Kaerim-Pongmyong	Korea, Republic of	Ch'Ungch'Ong-Bukto	36.41	127.75
51	Yongwon-GunJa-Pyongtack-Shihung	Korea, Republic of	Ch'Ungch'Ong-Namdo	36.91	127.67
52	Ampangadiatany	Madagascar	Toamasina	-19.41	48.89
53	Ambatomitamba Sahanovo area	Madagascar	Toamasina	-18.35	49.10
54	Perinet-Ambatovy area	Madagascar	_	-18.93	48.45
55	Vatomandry area	Madagascar	_	-19.34	48.94
56	Telixtlahuaca	Mexico	Oaxaca	17.33	-96.86
57	Las Trincheras	Mexico	Sonora	30.40	-111.53
58	Lourdes area	Mexico	Sonora	28.60	-110.50
59	Tonichi	Mexico	Sonora	28.58	-109.57
60	Skaland-Senja	Norway	_	69.45	17.29
61	La Galgada-La Limena-San Carlos Mines	Peru	Ancash	-8.46	-78.13
62	Baia De Fier	Romania	_	45.23	23.75
63	Botogolsk	Russia	Buryatiya	52.46	100.75
64	Boyarsk	Russia	Buryatiya	51.85	106.10
65	Kureyka	Russia	Krasnodarskiy Kray	66.48	87.17
66	Noginskoje	Russia	Krasnodarskiy Kray	64.50	91.25
67	Soyusnoye	Russia	-	47.91	130.93
68	Tayginsk	Russia	_	55.63	60.65
69	Gumbu graphite mine	South Africa	_	-22.32	30.67
70	Malonga graphite mine	South Africa	_	-22.65	30.88
71	Kahatagaha-Kolongaha mines	Sri Lanka	_	7.57	80.53

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.—Continued

ldentification number	Record type	Ore type	Operation	Development status	Tonnage	Grade (% of carbon)
34	District	Flake, lump	Surface	Producer	_	_
35	District	Flake, lump	Surface,underground	Producer	_	_
36	District	Flake, lump	Unknown	Producer	_	_
37	District	Flake, lump	Surface	Producer	_	_
38	District	Flake, lump	Surface	Producer	_	
39	District	Flake, lump	Surface	Producer	_	_
40	District	Flake, lump	Surface	Producer	_	_
41	District	Flake, lump	Surface	Producer	_	_
42	District	Flake, lump	Surface	Producer	_	_
43	District	Flake, lump	Surface	Producer	_	_
44	District	Flake	Surface	Producer	1,120,000	14.1
45	District	Flake, lump	Surface	Producer	130,000	19.5
46	District	Flake, weathering	Surface	Past producer	_	_
47	Site	Flake, weathering	Surface	Prospect	1,200,000	13
48	District	Amorphous	Surface,underground	Producer	_	_
49	District	Flake	Unknown	Producer	_	_
50	District	Amorphous	Underground	Producer	12,000,000	80
51	District	Flake, weathering	Surface	Producer	1,400,000	3.5
52	Site	Flake, weathering	Surface	Past producer	_	_
53	District	Flake, weathering	Surface	Producer	2,000,000	9
54	District	Flake, weathering	Surface	Producer	_	_
55	District	Flake, weathering	Surface	Producer	2,000,000	7
56	Site	Flake, weathering	Surface	Producer	13,400,000	4
57	Site	Amorphous	Underground	Producer	_	_
58	District	Amorphous	Underground	Producer	2,000,000	80
59	Site	Amorphous	Unknown	Producer	2,000,000	75
60	Site	Flake	Underground	Producer	2,000,000	30
61	District	Amorphous	Unknown	Past producer	_	_
62	Site	Amorphous	Surface,underground	Past producer	58,000	70
63	Site	Lump, flake	Underground	Producer	Small	_
64	District	Flake	Unknown	Past producer	Large	5
65	Site	Amorphous	Surface,underground	Producer	87,000,000	88
66	Site	Amorphous	Underground	Producer	10,000,000	85
67	Site	Flake	Surface	Producer	8,200,000	18
68	Site	Flake	Surface	Producer	1,116,000	3
69	Site	Flake	Unknown	Past producer	_	_
70	Site	Amorphous	Surface	Past producer	20,000,000	63.5
71	District	Lump	Underground	Producer	100,000	60

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.—Continued

dentification	Name	Country	State/Province	Latitude	Longitude
number	Name	Country	State/Province	Decimal degrees WGS 84	
72	Zavalyevskiy	Ukraine	_	48.20	30.03
73	Clay-Coosa-Chilton graphite district	United States	Alabama	33.28	-85.84
74	Christophosen Creek	United States	Alaska	65.03	-165.63
75	Graphite Creek	United States	Alaska	65.04	-165.54
76	Imuruk Basin Graphite	United States	Alaska	65.04	-165.55
77	Kigluaik Mountains graphite district	United States	Alaska	65.04	-165.54
78	Southern California area	United States	California	34.65	-118.47
79	Black Lady Nos. 1 and 2	United States	California	36.90	-118.07
80	Eureka Plumbago-Morgan mines	United States	California	38.02	-120.38
81	Skinner Ranch	United States	California	38.19	-122.59
82	Unnamed	United States	California	36.28	-121.56
83	Unnamed	United States	California	41.21	-123.77
84	Wedge	United States	California	32.80	-115.98
85	Graphite Basin	United States	Colorado	38.59	-106.38
86	Unnamed graphite deposit	United States	Colorado	38.67	-105.98
87	Graphite mines	United States	Connecticut	41.86	-73.37
88	Lead Hill Mine graphite deposits	United States	Connecticut	41.94	-72.18
89	Unnamed graphite mine	United States	Georgia	34.12	-84.74
90	Detroit-Northern Graphite quarries	United States	Michigan	46.63	-88.35
91	Black Diamond Carbon Graphite	United States	Montana	46.32	-111.63
92	Crystal Graphite Mine	United States	Montana	45.10	-112.51
93	Boston-Goshen-Osgood Mines area	United States	New Hampshire	43.27	-72.10
94	Stone Mills Graphite Mine	United States	New Jersey	40.68	-74.88
95	Adirondack Mining & Milling Mine	United States	New York	43.56	-73.46
96	Essex-Warren area	United States	New York	43.90	-73.47
97	Champlain Graphite Mine	United States	New York	43.54	-73.48
98	M. B. Hooper Graphite Mine	United States	New York	43.55	-73.50
99	Pope Mills-Rossie deposits	United States	New York	44.47	-75.55
100	Rowland Graphite Mine area	United States	New York	43.60	-73.97
101	Silver Leaf Graphite Co. Mine	United States	New York	43.59	-73.43
102	Dillinger Mine and mill	United States	North Carolina	35.90	-82.18
103	Cranston-Penners Ledge Mines	United States	Rhode Island	41.77	-71.46
104	Copper Cliff Mine	United States	South Dakota	44.12	-103.84
105	Burnet-Llano district	United States	Texas	30.78	-98.36
106	Rabbit Creek area	United States	Wyoming	42.21	-105.23
107	Taskazgan	Uzbekistan	_	40.81	63.38
108	Lynx Mine	Zimbabwe	_	-16.43	29.30

Table J3. Location, grade, tonnage and other data for selected graphite deposits and districts of the world.—Continued

Identification number	Record type	Ore type	Operation	Development status	Tonnage	Grade (% of carbon)
72	Site	Flake, weathering	Surface	Producer	100,000,000	5.5
73	District	Flake	Unknown	Past producer	300,000	10
74	Site	Flake	Unknown	Past producer	65,000	52
75	Site	Flake	Unknown	Past producer	_	_
76	Site	Flake	Surface	Past producer	_	_
77	District	Flake	Unknown	Past producer	10,000,000	10
78	District	Flake	Surface	Past producer	_	_
79	Site	Flake	Surface	Past producer	_	_
80	District	Flake	Unknown	Past producer	_	_
81	Site	Flake	Surface	Past producer	_	_
82	Site	Flake	Unknown	Past producer	_	_
83	Site	Flake	Unknown	Past producer	_	_
84	Site	Flake	Unknown	Past producer	_	_
85	District	Flake	Underground	Past producer	_	_
86	Site	Flake	Unknown	Past producer	_	_
87	Site	Lump or flake	Surface	Past producer	Small	_
88	Site	Lump or flake	Surface	Past producer	Small	_
89	Site	Flake	Surface	Past producer	_	_
90	Site	Amorphous	Surface	Past producer	_	_
91	Site	Flake	Surface	Past producer	_	_
92	Site	Lump or flake	Unknown	Past producer	_	_
93	District	Lump or flake	Surface	Past producer	_	_
94	Site	Lump or flake	Unknown	Past producer	_	_
95	Site	Lump or flake	Surface	Past producer	_	_
96	District	Lump or flake	Surface-Underground	Past producer	_	_
97	Site	Lump or flake	Surface	Past producer	_	_
98	Site	Lump or flake	Underground	Past producer	_	_
99	District	Lump or flake	Underground	Past producer	_	_
100	District	Lump or flake	Surface-Underground	Past producer	_	_
101	Site	Lump or flake	Surface	Past producer	_	_
102	Site	Flake	Surface	Past producer	_	_
103	District	Amorphous	Unknown	Past producer	_	_
104	Site	Flake	Unknown	Past producer	_	_
105	District	Flake	Unknown	Past producer	400,000	5
106	Site	Flake	Underground	Past producer	_	_
107	Site	Flake	Surface	Producer	2,300,000	15
108	Site	Flake	Underground	Producer?	6,700,000	26.2




Figure J2. World map showing locations of major graphite deposits and districts in the world, by commodity type. Numbers refer to the identifier number in table J3. Distribution of crystalline metamorphic basement is from Chorlton (2007).

The world's main sources of crystalline flake graphite are the deposits in Brazil, Canada, China, India, and Madagascar. Probably the largest resources of high-grade crystalline flake graphite in the world are in China (Jixi district) and the island country of Madagascar. The deposits in both areas occur in belts of Neoarchean to late Proterozoic micaceous gneiss and schist that are interpreted to be associated with a series of mountain-building events related to the formation of the Gondwana supercontinent about 600 million years ago (Wilde and others, 1999), named the Pan-African orogeny. Pan-African age supracrustal metamorphic belts also occur in areas in Western Australia, eastern India, and Sri Lanka; these areas also host significant flake graphite deposits located in the most productive graphite-bearing regions of the world (fig. J2).

Graphite-rich horizons in Madagascar occur over a distance of more than 800 km in the eastern half of the island. Individual deposits are graphite-rich layers that range from 3 m to more than 35 m in thickness and extend up to a few kilometers. Ore grades average 4 to 10 percent graphite, but grades are reported to be as high as 60 percent in some areas. The flake graphite deposits in the State of Minas Gerais, Brazil, are mined from graphite-bearing soils overlying extensively weathered host rock with grades of 12 to 16 percent graphite; the ore is mined by front-end loader or shovel. Shandong Province in China is a major flake graphite producer. The flake graphite deposits in the vicinity of Jixi, China, are mined from deformed lenses and discordant layers of graphite schist and gneiss in paragneiss; graphite content ranges from 15 percent in the gneiss to up to 45 percent in the schists, with local flake graphite resources exceeding 360 million metric tons (Wilde and others, 1999). Little is known about the deposits in Russia and India.

Large disseminated flake graphite deposits occur at a number of places in the Grenville Province metamorphic belt in Canada's Quebec and southeastern Ontario Provinces, and small deposits associated with Grenville series marble, gneiss, and pegmatites also occur in the Adirondack Mountains west and northwest of Ticonderoga, New York (Alling, 1918). The Grenville Province is a southwest-trending belt of deformed high-grade supracrustal metamorphic rocks of Mesoproterozoic age that is exposed across 2,000 km from Labrador, through Quebec, into southeastern Ontario, and continues in the subsurface a further 3,000 km to Texas and Mexico. The Lac Knife graphite deposit at Fermont, Quebec, has high-grade ore hosted by migmatized quartz-feldspar (biotite) gneiss. The host rock is the southern extension of carbonaceous shales and sandstones that have been deformed and metamorphosed in the crosscutting Grenville Province metamorphic belt.

Deposits of flake graphite in the United States have been mined in Alabama, Alaska, and Texas. The deposits of the Clay-Coosa-Chilton graphite district, Alabama, occur in two parallel layers and lenses in the Ashland quartz-mica schist that contain 1 to 5 percent disseminated flake graphite (Pallister and Thoenin, 1948). The layers and lenses range from 6 m to more than 35 m in thickness, dip gently, and occur

in a northeast-trending 1- to 3-km-wide belt that extends for more than 90 km. The deposits are weathered to depths of 35 m. The deposits in the Burnet-Llano district, Texas, occur in the Precambrian Packsaddle schist and show a wide range of graphite content and flake size (Needham, 1946). The graphite flake deposits in the Kigluaik Mountains graphite district, Alaska (Coats, 1944) represent the largest known domestic graphite resource, but are located in a rugged and remote area with high mining costs.

## Vein Deposits Containing Lump or Chip Graphite

Crystalline graphite of the lump or chip commodity type is generally found in well-defined veins composed almost entirely of graphite that cut high-grade metamorphic rocks or as accumulations along intrusive contacts of pegmatites with marbles or paragneiss. The veins form in high-grade regional metamorphic environments where metasedimentary belts are invaded by igneous rocks. In some areas, the veins are localized in granulite-facies domains within the broader regional metamorphic belt (Chamberlain and Rumble, 1988).

Graphite-bearing veins form within or crosscut metamorphic structures, rock contacts, and folds. The veins range from thin films to massive bodies that are more than 3 m thick and may extend for hundreds of meters, although they usually extend for less than tens of meters. The veins consist largely of coarse, platy, or needlelike interlocking crystals of graphite. Mineral impurities depend largely upon the host rock; quartz, feldspar, pyroxene, and calcite are common. Ore grades range from 40 to more than 90 percent graphitic carbon; the percentage largely depends on the amount of wallrock contained with the ore material. Hand sorting may be required to provide lump concentrates of high purity.

Graphite vein deposits are found in similar settings as disseminated flake graphite deposits, and they may be spatially associated with them. The Sri Lankan graphite deposits, which are the only economically significant examples of the vein-type deposits, occur in high-grade metamorphic rocks of Neoarchean to Proterozoic age. Most vein deposits and prospects occur in crystalline metamorphic basement rocks of Neoarchean to late Proterozoic age, although deposits may be of any age. The graphite in these deposits occurs as veins in fractures and structures that are emplaced near or after peak metamorphic conditions.

It is clear that the carbon in the vein deposits has been transported by metamorphic or replacement processes, presumably aided by metamorphic or other fluids; however, the nature of the processes responsible for the precipitation of graphite in the veins is uncertain and controversial, and may vary between deposits. Most veins are hosted in high-grade metamorphic rocks; however, graphite precipitation may take place after the most intense deformation and thermal conditions of regional metamorphism have been achieved, as suggested by the localization of veins in brittle structures that are not disturbed by penetrative deformation associated with metamorphism and veins that crosscut syntectonic intrusives

**J16** 

others, 1986).

(Rumble and Hoering, 1986; Rumble and others, 1986). In some veins, low-temperature minerals, such as prehnite, occur with graphite. Textural evidence and age determinations on zircon inclusion rims in graphite (Zeitler and others, 1990), however, indicate that some veins were emplaced during or soon after peak metamorphic conditions and that the hydrothermal systems responsible for vein formation may also be responsible for the high-grade metamorphic conditions found in their immediate vicinity (Chamberlain and Rumble, 1988). Carbon isotope studies of the vein deposits show a wide range in isotopic composition between and within districts; this variation may be explained by varying carbon sources from two crustal reservoirs: (a) reduced biogenic carbon, and (b) carbonate minerals (Rumble and Hoering, 1986). The most probable processes resulting in graphite precipitation in veins likely include rock-fluid redox reactions, such as oxidation of methane (CH<sub>4</sub>)-bearing fluids or reduction of CO<sub>2</sub>-bearing

The United States has small graphite vein deposits in New Hampshire, Connecticut, the Adirondacks of New York, and Montana; these deposits are largely of only scientific interest. The Crystal Graphite Mine near Dillon, Montana, is the largest known graphite vein deposit in the United States. At this deposit, veins up to 60 cm thick and 15 m long occur in fractures in gneiss and pegmatite (Bastin, 1912); the fractures and veins formed after the peak of metamorphism in these rocks (Ford, 1954).

fluids by wall rock (internal or external buffering), cooling

of hot fluids saturated with respect to graphite, and mixing

of fluids with differing CH<sub>4</sub> and CO<sub>2</sub> contents (Rumble and

# **Mining and Beneficiation Methods**


Natural graphite is mined from both open pit and underground mine operations (table J3). Production from open pit operations is less expensive and is preferred where the overburden can be removed economically. Most crystalline flake deposits are mined using open pit methods; the exception is some steeply dipping bodies with high-grade minable lenses containing 15 percent or more contained carbon (table J3). Graphite is stable in the weathering environment, and intensely weathered crystalline flake deposits, such as those in Brazil, Kenya, Madagascar, and Oaxaca, Mexico, can be easily and profitably mined using open pit methods. Underground mining methods are used in some amorphous deposits in China, Europe, the Republic of Korea, and Mexico, and vein deposits in Sri Lanka, where the ore intervals are deep and of high grade (>80 percent contained carbon). Beneficiation processes for graphite vary from simple hand sorting and screening of high-grade ore at some amorphous graphite deposits and at the Sri Lankan vein operations to multistage crushing, screening, washing, and flotation cycles required to produce high-quality and high-purity graphite flake and powder products. No refining of amorphous graphite ore is needed for most uses.

#### **Resources and Production**

#### **Distribution of Graphite Deposits and Districts**

The world map in figure J2 shows the location of 108 natural graphite deposits and districts characterized as:
(a) amorphous deposits that result from thermal or contact metamorphism of highly carbonaceous sediments, usually graphitized coal beds, or (b) crystalline deposits of either disseminated flake graphite, which have resulted from regional metamorphism of carbonaceous sediments under conditions exceeding amphibolite facies, or coarse graphite aggregates (lump or chip) in fracture-filling veins cutting igneous and metamorphic rocks. Both of the crystalline deposit types (flake, or lump and chip) are mostly located in crystalline metamorphic bedrock (fig. J2), consisting primarily of coarse-grained quartzofeldspathic metasedimentary rocks at high metamorphic grades (Chorlton, 2007).

Table J3 describes the features of the 108 natural graphite deposits and districts shown in figure J2 that are known to have produced graphite or are significant prospects with potential for future development. A number of deposits and districts with past production, particularly those in the United States, have grade and tonnage characteristics that render the deposits subeconomic under current conditions; these are included to identify broad areas and regions that may be future sources of graphite production or may contain undiscovered deposits. The names, locations, and descriptions of most of the deposits in table J3 are taken from the International Strategic Minerals Inventory (ISMI) graphite inventory (Krauss and others, 1988) and the U.S. Geological Survey Mineral Resources Data System (MRDS) (U.S. Geological Survey, 2012). Figure J3 shows the deposit grade (percent carbon) and tonnage reported for some of the deposits in table J3, characterized by deposit type. The lowest tonnage and grade deposits in figure J3 are



**Figure J3.** Plot of grade (carbon) and tonnage for some of the amorphous and crystalline graphite deposits listed in table J3, by deposit type. The table also gives additional resource data, and sources.


subeconomic under current market conditions; typical ranges of commercial grades and deposit tonnage, by commodity type, are given in table J1.

#### **World Graphite Production and Resources**

Natural graphite is produced by more than 20 nations, but world production is dominated by China, India, and Brazil. Figure J4 shows the average level and amounts of natural graphite produced worldwide by area from 2006 to 2010, based on data from Olson (2011). During this period, China accounted for approximately 67 percent of worldwide production of natural graphite, and established itself as the dominant exporter with the ability to set world prices. China became a major global supplier of graphite in the 1980s owing in part to very low production costs and aggressive marketing. India and Brazil are significant worldwide exporters of graphite whereas Mexico and Canada export mainly to the United States.

Global graphite resources are large relative to annual global consumption, and undoubtedly extensive, but their extent is poorly known because resources of industrial mineral commodities typically are not fully delineated and reported far in advance of development. Complete estimates of graphite resources are likely not available for any single major graphite district in the world. Table J4 tabulates conservative estimates for recoverable graphite resources for a number of major graphite-producing nations. Reserves of natural graphite (that is, the identified, delineated, and reported world resources that are considered to warrant economic exploitation at the time of reserve determination) are equivalent to 81 million metric tons. Approximately 26 percent of reserves are crystalline (flake and vein type [lump or chip]) graphite materials for which demand is increasing. Other identified resources beyond reserves ("Other identified resources" in table J4) are about an additional 1.4 billion metric tons, leading to an estimate of total identified graphite resources of approximately 1.5 billion metric tons worldwide. Approximately one-half of this total resource estimate is flake graphite. Future exploration is likely to result in the discovery of world resources that are many times this estimate; however, many new discoveries are likely to be located in remote areas with high mining costs and limited access to infrastructure and industrial markets that use graphite. The Lac Knife deposit in Quebec, Canada, is an example of a relatively recent discovery in a remote setting (Bonneau and Raby, 1990).

Future discoveries of amorphous and flake graphite deposits in the conterminous United States are likely to be limited by favorable geology and preexisting exploration coverage. The coal fields of the United States are well explored and delineated, and past igneous activity in the coalfields is either absent or of such limited scale that the chance of finding amorphous graphite deposits of commercial size and grade is negligible. Furthermore, with the exception of Alaska, crystalline metamorphic rocks that could potentially host flake and vein (lump or chip) graphite deposits have limited extent and exposure in the United States, and most of the crystalline basement that is present is well characterized. The identified flake graphite deposits in the Kigluaik Mountains of Alaska indicate potential for additional deposits in surrounding areas; however, these are likely to occur in remote areas with rugged terrain and limited infrastructure, and such deposits would be a great distance from graphite markets and have high mining costs. The weathered low-grade crystalline flake deposit districts in Alabama and Texas may provide future domestic sources of graphite if flake graphite prices increase, because of the ease of mining the deposits and their proximity to markets.



**Figure J4.** Pie chart showing average annual natural graphite production for the period 2006–10, by country or region and amount (in thousand metric tons [kt]). The tonnages are estimated based on data reported in Olson (2011).

Table J4. Estimates of world graphite resources, by country, commodity type, and resource category, in thousand metric tons of recoverable graphite.

[Resources reported for recoverable amorphous, flake, or crystalline (vein-type) commodity categories. Resource categories: (a) Reserves are demonstrated resources of recoverable natural graphite considered to warrant economic exploitation at the time of reserve determination; (b) Other identified resources are estimates of characterized recoverable resources beyond those reported as reserves; only part of this estimate would be economic; and, (c) Total identified resources includes reserves and other identified resources. Data are adapted from Olson (2013) and Taylor (2006) and rounded to two significant figures. NA, not available]

Country	Туре	Reserves	Other identified resources	Total identified resources¹
Austria	Amorphous	50	1,100	1,200
Brazil	Flake	360	3,400	3,800
Canada	Flake	1,500	4,200	5,700
China	Amorphous	55,000	NA	NA
	Flake	6,000	350,000	360,000
Czech Republic	Flake	900	12,000	13,000
Germany	Flake	130	690	820
India	Flake	735	13,000	14,000
Madagascar	Flake	940	180,000	180,000
Mexico	Amorphous	3,100	10,000	13,000
	Flake	106	320	430
North Korea	Amorphous	1,000	30,000	31,000
	Flake	700	1,400	2,100
Norway	Flake	200	260	460
Republic of Korea	Amorphous	20	2,100	2,100
	Flake	6	74	80
Romania	Amorphous	300	NA	300
Russia, with Ukraine	Amorphous	1,000	560,000	560,000
	Flake	6,400	94,000	100,000
Sri Lanka	Crystalline, vein	50	400	450
	Flake	1,800	7,000	8,800
United States <sup>2</sup>	Amorphous	0	5,900	5,900
	Flake	0	280	280
Zimbabwe	Flake	600	1,200	1,800
Other	Flake	280	920	1,200
Total	Amorphous	60,000	750,000	810,000
Total	Flake	21,000	670,000	690,000
Total	Crystalline, vein	50	400	450
Total	By resource category	81,000	1,400,000	1,500,000

<sup>&</sup>lt;sup>1</sup>Total identified resources includes reserves and other identified resources.

<sup>&</sup>lt;sup>2</sup>Other identified resources includes Alabama, Alaska, and New York.

# **Exploration for New Deposits**

Prospecting for graphite deposits consists primarily of outcrop examination, trenching, and sampling, usually followed by drilling. Because of its chemical inertness, graphite resists weathering, and outcrops containing graphite and residual soils containing conspicuous graphite flakes may be evident. Knowledge of areal geology and the geologic features and settings of different graphite deposit types and associated deposits, such as coal, can be used to identify promising exploration targets. The Lac Knife flake graphite deposit was initially discovered during routine geologic mapping. When interest developed, the prospect was trenched by shovel, followed by further surface excavation, and later systematically characterized at depth by more than 99 drill holes. All this activity occurred during a more than 30-year time period (Bonneau and Raby, 1990).

Because of the high electrical conductivity of graphite (in deposits where individual graphite flakes are touching), a variety of electromagnetic methods have been used to search for deposits, principally flake graphite deposits. Electro-magnetic geophysical methods measure variations in the electrical conductivity of the ground caused by changes in mineral content, properties, or subsurface features. The methods rely on the process of electromagnetic induction that describes how a conductive material, such as graphite, will interact with a magnetic field. Surveys are conducted by using either surface or airborne methods; all methods use a transmitter and receiver coil spaced in standard configurations. The different methods use different operating frequencies to provide a range of depth penetrations and resolution needed for different applications. High-frequency electromagnetic systems are best for locating small shallow targets; lower frequency systems are used to investigate deeper subsurface conditions or define regional targets. The relative merits of various geophysical techniques in detecting graphite deposits are discussed by Goosens (1982, p. 136).

Graphite flakes may be found in stream sediment samples collected during exploration geochemical surveys. The presence of sulfides and vanadium-bearing garnet (goldmanite) may also be an indicator. There is a positive correlation between carbon, uranium, and vanadium contents in some deposits (Li and others, 1985), and positive vanadium, nickel, and (or) uranium anomalies in soil associated with graphite beds were reported by Tichy and Turnovec (1978) and may be considered a geochemical indicator of graphite deposits. These geochemical features probably relate to the depositional environment and trace element content of the protolith and likely vary among deposits. Therefore, it may be difficult to use these features effectively in grassroots exploration for graphite deposits.

## **Environmental Considerations**

Because of the chemically inert, nontoxic nature of graphite, the main environmental concerns associated with graphite mining are (a) the presence of other minerals that can occur with graphite, and (b) inhalation of graphite particles or fine-grained silica minerals in graphite during mining and processing. For example, the iron sulfide minerals pyrite and pyrrhotite are present in amounts ranging from a trace to several percent in some graphite deposits. These minerals can cause acid-rock drainage if exposed to air and water in waste rock or tailings. Graphite in soils and stream or river sediments is inert and poses no known terrestrial or aquatic risks.

#### **Mine Waste Characteristics**

The volumes and mineralogical characteristics of mine wastes depend on the size and type of deposit, as well as the mining and processing practices employed. For open pit mines, the amount of overburden that must be stripped prior to the onset of mining contributes to the mine waste. Ore processing for disseminated flake graphite typically includes milling, flotation, screening, and drying. The resulting mine waste and flotation tailings are composed of the minerals that make up the host rocks, typically schists and gneisses composed mainly of quartz and feldspars. Other silicate minerals in these rocks include pyroxenes, amphiboles, micas, garnet, and sillimanite. These are all moderate- or slow-weathering minerals (Jambor, 2003). Quartz persists in the environment, whereas feldspars weather to clays. Fast-weathering, potentially acid-producing sulfide minerals, such as pyrite and pyrrhotite, are reported at some deposits. The yellow iron sulfate mineral jarosite, which is an indicator of acidic conditions, is a common weathering product of pyritic, gneiss-hosted graphite deposits (Simandl and Kenan, 1997b). Calcite and other carbonate minerals may be present in gangue and can provide acid neutralization if present in sufficient amounts.

The largest known flake graphite deposit, the Zavalyevskiy deposit in Ukraine, has total resources on the order of 100 million metric tons with reserves of 6.4 million metric tons containing 5 to 7 percent graphite (Zavalyevskiy Graphite Ltd., 2013). The ore is kaolinized gneiss that contains garnet, biotite, chlorite, pyroxene, quartz, and sillimanite. Both garnet and crushed stone products are recovered from the ore. The graphite ore is processed by flotation to produce a high-purity graphite concentrate (86 to 97 percent graphite) and ash (10 to 13 percent graphite). Graphite orebodies in graphite schist at the Liu Mao Mine in China are elevated in vanadium (0.2 percent vanadium pentoxide  $[V_2O_5]$ ), titanium (0.5 percent titanium dioxide  $[TiO_2]$ ), and uranium (0.004 percent U). These elemental concentrations

are attributed to garnet intergrown with graphite in the deposit (Wilde and others, 1999). In Canada, a composite grab sample for metallurgical testing at the Trout Lake (also known as Treelined Lake) graphite prospect in southern Ontario contains 1.8 percent sulfur, which is attributed to 4.5 percent pyrrhotite in the sample; the preliminary test indicated that pyrrhotite removal by screening and flotation would be required to obtain a salable graphite product (Kuehnbaum and Zebruck, 2002). At the Bissett Creek flake graphite deposit in Ontario, both ore and waste rock are recognized as potential acid generators (Systèmes Gèostat International Inc., 2007). The graphite occurs in a calcareous biotite-amphibole-quartzofeldspathic gneiss with disseminated graphite, pyrite, pyrrhotite, and trace chalcopyrite. Graphite concentrations range from about 1 to 10 percent; the sulfide minerals constitute 1 to 5 percent of the rock. Mine plans call for underwater tailings storage and the addition of carbonate-bearing material to the waste dump to neutralize acid potential. In contrast, at the Eagle deposit in British Columbia, high-purity flake graphite is quarried from quartz-rich sands, and slightly alkaline sand and aggregate byproducts are marketed as construction materials.

Amorphous graphite deposits range from about 300 to 800 million metric tons of ore and have higher average graphite grades than other types of graphite deposits (table J1). The ore is essentially the entire graphitized unit. The associated waste primarily is any overburden that must be removed to access the deposit. Mineral impurities in amorphous graphite deposits reflect the compositions of the protolith coal or sediment (Simandl and Kenan, 1997a). In the Bohemia region of the Czech Republic, elevated concentrations of vanadium and nickel anomalies are associated with amorphous graphite deposits (Tichy and Turnovec, 1978). Waste material described as graphite gangue at the Jixi deposit in China contains zinc, nickel, and mercury (Liu and Man, 2007).

Vein graphite from Sri Lanka, which is significant for its purity and high degree of crystallinity, is mined underground at the Bogala Mine (370 m deep) and Kahatagaha-Kolongaha Mine (650 m deep). Total inferred reserves for these two mines are about 400,000 metric tons. At these mines, graphite veins are blasted with dynamite. When the fumes clear, the ore is hauled to the surface and then hand cobbed and graded; no further processing is required, so no tailings or large waste piles are produced (Ranasinha and Uragoda, 1972). Hydrothermal minerals associated with the graphite from Sri Lanka include apatite, biotite, calcite, chalcopyrite, pyrite, and quartz. The average chemical contents reported for different vein graphite morphologies from the Bogala and the Kahatagaha-Kolongaha Mines reported by Touzain and others (2010) are as follows: 93 to 99 percent carbon, 0.06 to 1.06 percent iron oxide (Fe<sub>2</sub>O<sub>2</sub>), 0.05 to 0.45 percent silicon dioxide (SiO<sub>2</sub>), 0.01 to 0.19 percent sulfur, and 0.004 to 0.82 percent calcium oxide (CaO).

#### **Human Health Concerns**

The primary human health concern associated with graphite mining is inhalation of dust and fumes generated during mining and processing. Graphite is not considered to be toxic and is not a listed carcinogen, although crystalline silica (a common impurity in graphite) is considered to be carcinogenic. Graphite is considered a nuisance dust. The time-weighted average (TWA) recommended exposure level set by the U.S. National Institute for Occupational Safety and Health (NIOSH) is 2.5 milligrams per cubic meter.

Chronic exposure to graphite dust is associated with pneumoconiosis, a group of lung diseases associated with chronic exposure to mineral and metallic dusts. Graphite pneumoconiosis was recognized in the 1940s in graphite workers in Sri Lanka based on similarities to pneumoconiosis in coal miners (Uragoda, 1997). The fact that graphite always contains some quartz (typically about 2 percent but up to 10 percent) raised concerns that graphite pneumoconiosis was actually a slow developing form of silicosis (Ranasinha and Uragoda, 1972). A review of 605 cases of graphite pneumoconiosis reported in the literature and experimental studies on animals concluded that although many years of occupational exposure to pure graphite may cause disease, most studies indicate that mixed-dust inhalation is a more likely cause of lung disease (Hanoa, 1983). Implementation of dust abatement protocols in mining and processing has resulted in decreased incidence of lung disease in graphite workers since the 1970s.

#### **Ecological Health Concerns**

The environmental fate and effects of dispersed graphite flakes were addressed in a study of the use of graphite flakes in a dust cloud to obscure visual and electromagnetic observation of military operations under battlefield conditions (Driver and others, 1993). Graphite mixed with fog oil and dispersed as an aerosol provides a chemically inert obscurant used to protect movements of troops and equipment. Dispersion of airborne plumes of these mixtures can deposit graphite on soil, vegetation, and water surfaces or pose inhalation risks to wildlife. Although obscurant releases are short-term events (~30 minutes), airborne distribution and surface deposition of flake graphite can occur many kilometers downwind of the release site. Deposited graphite persists in the environment, so the repeated use on military training sites warranted an evaluation of potential ecological impacts. These studies are not directly applicable to graphite mining and processing, but they do demonstrate that graphite flakes likely pose little or no chemical risk to the environment. The series of experiments described by Driver and others (1993) showed that (a) graphite flakes are not toxic to soil invertebrates (oligochaeta, or earthworms), (b) no adverse effects on terrestrial plants (corn and cucumber) were noted in soils amended with graphite flakes in

concentrations up to 0.5 percent, by weight, and (c) a 48-hour acute aquatic toxicity test toward *daphnia* (water fleas) using graphite suspensions was toxic; however, iron contaminants in the graphite may explain the toxicity. The long-term effects of obscurant flake graphite on exposed avian and mammalian wildlife are unknown.

#### **Carbon Footprint**

The term "carbon footprint" refers to the amount of carbon dioxide (CO<sub>2</sub>) emitted in a 1-year period. According to GrafTech International Holdings, Inc. (2013), natural graphite has a substantially lower carbon footprint for both CO<sub>2</sub> emissions and energy consumption during mining and processing than other mineral commodities for which data are available, such as aluminum or copper, on an equivalent mass, volume, or yearly production basis. Cost- and energy-efficient technologies that could reduce CO<sub>2</sub> to synthetic graphite could lower CO<sub>2</sub> emissions and produce inert graphite, providing an industrial option to sequester carbon from the atmosphere (Xu and others, 2005).

#### **Regulatory and Environmental Considerations**

The environmental requirements for natural graphite, which is an inert, nontoxic substance, are limited to dust control and control of organic vapors that may arise during mining or processing of graphite ores or the fabrication of graphite products. Given the current and likely future absence of graphite mining in the United States, no other domestic regulatory or environmental requirements are anticipated.

## **Problems and Future Research**

Major shifts in U.S. consumption of natural graphite by end use are underway and include a long-term decrease in the use of amorphous graphite for refractory and other applications and an increase in the use of flake graphite, particularly for emerging energy and high-technology applications (Taylor, 2006). In addition, shifts in the global graphite supply and exports are anticipated as China's rapidly growing domestic market for graphite, coupled with their developing mine production problems and rising labor costs, may serve to

limit Chinese exports in the future, particularly of crystalline flake graphite; meanwhile, anticipated large-scale fuel cell and battery applications could dramatically increase world demand for graphite (Taylor, 2006; Olson, 2013; Olson and others, 2016). For the near future, however, China's graphite production is expected to increase and its dominance of world production to continue (Olson, 2013). Possible disruptions to global supplies are likely to be temporary or sporadic because identified reserves in China are sufficient to support new mines and additional production. In addition, exploration for new flake graphite deposits is ongoing, and additional deposits are near development in Canada and elsewhere (Olson, 2013; Olson and others, 2016).

Other than scientific studies on some vein graphite deposits of scientific (not commercial) interest, little recent geologic characterization and study has been undertaken on graphite deposits in the United States, and exploration for new deposits has not taken place. The lack of exploration is chiefly because known deposits are considered noncommercial, large areas of the country lack the geologic conditions and settings thought necessary to form economic graphite deposits, graphite supplies have been reliably available from foreign sources for many years, and synthetic graphite is increasingly used for many applications. As earlier noted by Weis (1973), research and development of better techniques to beneficiate low-grade flake graphite ores would be needed to support a viable domestic industry.

Studies on the temporal variation of carbon deposition and preservation and the behavior of organic matter and graphite under metamorphic and hydrothermal conditions might provide additional insights into the occurrence and distribution of high-grade flake graphite deposits. Many of the important flake graphite deposits worldwide occur in Precambrian crystalline metamorphic rocks, and most of these occur in Pan-African age supracrustal metamorphic belts. In addition, many of these deposits have grades exceeding 15 percent contained carbon, which exceeds the typical carbon content range of organic-bearing shales (Vine and Tourtelot, 1970). It is not known whether these deposits represent unusual protoliths—for example, saprolitic alginate (oilshale), unusual periods or regions of biological productivity and preservation of organic matter, or if they record some carbon enrichment owing to mechanical deformation or precipitation of graphite by processes involving internal or external buffering or mixing of metamorphic fluids.

#### **References Cited**

Note: All Web links listed were active as of the access date but may no longer be available.

- Alling, H.L., 1918, The Adirondack graphite deposits: Albany, N.Y., New York State Museum Bulletin 199, 172 p.
- Bastin, E.S., 1912, The graphite deposits of Ceylon, with a description of a similar graphite deposit near Dillon, Montana: Economic Geology, v. 7, p. 419–443.
- Bonneau, J., and Raby, R., 1990, The Lake Knife graphite deposit: Mining Magazine, v. 163, no. 1, p. 12–18.
- Chacko, T., Kumar, G.R.R., and Newton, R.C., 1987, Metamorphic P–T conditions of the Kerala (South India) khondalite belt, a granulite facies supracrustal terrain: The Journal of Geology, v. 95, no. 3, p. 343–358.
- Chamberlain, C.P., and Rumble, D., 1988, Thermal anomalies in a regional metamorphic terrain—An isotopic study of the role of fluids: Journal of Petrology, v. 29, p. 1215–1232.
- Chorlton, L.B., 2007, Generalized geology of the world—Bedrock domains and major faults in GIS format; a small-scale world geology map with an extended geological attribute database: Geological Survey of Canada Open File 5529, 48 p., CD–ROM.
- Coats, R.R., 1944, Graphite deposits on the north side of the Kigluaik Mountains, Seward Peninsula, Alaska: U.S. Geological Survey Open-File Report 10, 8 p.
- Driver, C.J., Ligotke, M.W., Landis, W.G., Downs, J.L., Tiller, B.L., Moore, E.B., Jr., and Cataldo, D.A., 1993, Environmental and health effects review for obscurant graphite flakes—Report prepared for the U.S. Army Chemical and Biological Defense Agency: Richland, Wash., Pacific Northwest Laboratory, 28 p.
- European Commission, 2014, Critical raw materials for the EU—Report of the ad-hoc Working Group on defining critical raw materials: Brussels, Belgium, and Luxembourg, Luxembourg, European Commission, 41 p., accessed September 19, 2015, at http://ec.europa.eu/growth/sectors/raw-materials/specific-interest/critical/index\_en.htm.
- Ford, R.B., 1954, Occurrence and origin of the graphite deposits near Dillon, Montana: Economic Geology, v. 49, p. 31–43.
- Goosens, P.J., 1982, Graphite deposits of the Precambrian and their mining development, *in* Natural Resources and Energy Division, United Nations Department of Technical Cooperation for Development, The development potential of Precambrian mineral deposits: New York, N.Y., Pergamon Press, p. 123–155.

- GrafTech International Holdings, Inc., 2013, About natural graphite: GrafTech International Holdings, Inc., accessed September 19, 2015, at http://aetpublic.wiredviews.com/getdoc/411491a4-0d68-4781-993e-7d992adfa2d4/Trade-Shows.aspx.
- Hanoa, Rolf, 1983, Graphite pneumoconiosis—A review of etiologic and epidemiologic aspects: Scandinavian Journal of Work, Environment, and Health, v. 9, no. 4, p. 303–314.
- Hoefs, J., and Frey, M., 1976, The isotopic composition of carbonaceous matter in a metamorphic profile from the Swiss Alps: Geochimica et Cosmochimica Acta, v. 40, p. 945–951.
- Industrial Minerals, 2010, Graphite prices rising daily: Industrial Minerals, June 29, accessed September 15, 2019, at http://www.indmin.com/Article/2620429/Graphite-pricesrising-daily.html.
- Jambor, J.L., 2003, Mine-waste mineralogy and mineralogical perspectives of acid-base accounting, chap. 6 of Jambor, J.L., Blowes, D.W., and Ritchie, A.I.M., eds., Environmental aspects of mine wastes: Mineralogical Association of Canada Short Course Series, v. 31, p. 117–145.
- Klar, G., 1958, The important graphite deposits of the world: Mining Magazine, v. 98, p. 137–142.
- Krauss, U.H., Schmidt, H.W., Taylor, H.A., Jr., and Sutphin, D.M., 1988, International Strategic Minerals Inventory summary report—Natural graphite: U.S. Geological Survey Circular 930–H, 29 p. [Also available at https://pubs.er.usgs.gov/publication/cir930H.]
- Kuehnbaum, R., and Zebruck, G., 2002, Treelined Lake graphite deposit—Beneficiation study: Megagraphite Inc. Treelined Lake Project report, 10 p. plus details of tests, accessed September 19, 2015, at http://www.geologyontario.mndmf.gov.on.ca/mndmfiles/afri/data/imaging/52L08SW2010//52L08SW2010.Pdf.
- Lamb, W., and Valley, J.W., 1984, Metamorphism of reduced granulites in low-CO<sub>2</sub> vapor free environment: Nature (London), v. 312, November 1, p. 56–58. [Also available at http://dx.doi.org/10.1038/312056a0.]
- Landis, C.A., 1971, Graphitization of dispersed carbonaceous material in metamorphic rocks: Contributions to Mineralogy and Petrology, v. 30, p. 34–45.
- Li, C., Yue, J., and Zhang, Y., 1985, Research on geological background and origin of Liu Mao graphite deposits, Heilongjiang Province, *in* Cheng, Y., ed., International Symposium on Metallogeny of the Early Precambrian: Abstracts, Organizational Committee of the International Symposium of Metallogeny, China, p. 108–109.
- Liu, Wen-yong, and Man, Xiu-liu, 2007, Evaluation and content of heavy metal pollution in mine areas wasteland of Jixi: Journal of Soil and Water Conservation, v. 6, p. 70–74.

- Natural Earth, 2014, Small scale data: Natural Earth map dataset, scale 1:110,000,000, accessed February 12, 2014, at http://www.naturalearthdata.com/.
- Needham, A.B., 1946, Mining and milling operations of Southwestern Graphite Co., Burnet County, Texas: U.S. Bureau of Mines Information Circular 7339, 7 p.
- Newton, R.C., 1986, Fluids of granulite facies metamorphism, *in* Walther, J.V., and Wood, B.J., eds., Fluid-rock interactions during metamorphism: Berlin, Springer, p. 36–59.
- O'Driscoll, Mike, 2010, Minerals meet in Miami heat: Industrial Minerals, no. 510, February 25, accessed September 19, 2015, at http://www.indmin.com/ Article/2398524/Minerals-meet-in-Miami-heat.html/.
- Olson, D.W., 2011, Graphite (natural): U.S. Geological Survey Mineral Commodity Summaries 2011, p. 68–69, accessed February 25, 2013, at https://minerals.usgs.gov/minerals/pubs/commodity/graphite/mcs-2011-graph.pdf.
- Olson, D.W., 2012, Graphite, *in* Metals and minerals: U.S. Geological Survey Minerals Yearbook 2010, v. I, p. 32.1–32.10, accessed November 12, 2012, at http://minerals.usgs.gov/minerals/pubs/commodity/graphite/myb1-2010-graph.pdf.
- Olson, D.W., 2013, Graphite (natural): U.S. Geological Survey Mineral Commodity Summaries 2013, p. 68–69, accessed February 25, 2013, at https://minerals.usgs.gov/minerals/pubs/commodity/graphite/mcs-2013-graph.pdf.
- Olson, D.W., Virta, R.L., Mahdavi, Mahbood, Sangine, E.S., and Fortier, S.M., 2016, Natural graphite demand and supply—Implications for electric vehicle battery requirements, *in* Wessel, G.R., and Greenberg, J.K., eds., Geoscience for the public good and global development—Toward a sustainable future: Geological Society of America Special Paper 520, p. SPE520-08, April 19, accessed June 30, 2016, at http://dx.doi.org/10.1130/2016.2520(08).
- Pallister, H.D., and Thoenin, J.R., 1948, Flake graphite and vanadium investigations in Clay, Coosa, and Chilton Counties, Alabama: U.S. Bureau of Mines Report of Investigations 4366, 81 p.
- Ranasinha, K.W., and Uragoda, G.G., 1972, Graphite pneumoconiosis: British Journal of Industrial Medicine, v. 29, p. 178–183.
- Roskill Information Services, Ltd., 2012, Natural and synthetic graphite—Global industry markets and outlook, 8th ed.: London, Roskill Information Services, Ltd., 413 p.
- Rumble, D., III, and Hoering, T.C., 1986, Carbon isotope geochemistry of graphite vein deposits from New Hampshire, U.S.A.: Geochimica et Cosmochimica Acta, v. 50, no. 6, p. 1239–1247.

- Rumble, D., III, Duke, E.F., and Hoering, T.C., 1986, Hydrothermal graphite in New Hampshire—Evidence of carbon mobility during regional metamorphism: Geology, v. 14, no. 6, p. 452–455.
- Simandl, G.J., and Kenan, W.M., 1997a, Microcrystalline graphite, *in* Geological fieldwork 1997, British Columbia Ministry of Employment and Investment, Paper 1998–1, p. 24O-1–24O-3.
- Simandl, G.J., and Kenan, W.M., 1997b, Crystalline flake graphite, *in* Geological fieldwork 1997, British Columbia Ministry of Employment and Investment, Paper 1998–1, p. 24P-1–24P-3.
- Simandl, G.J., and Kenan, W.M., 1997c, Vein graphite in metamorphic terrains, *in* Geological fieldwork 1997, British Columbia Ministry of Employment and Investment, Paper 1998–1, p. 24Q–1 to 24Q–3.
- Sutphin, D.M., 1991a, Descriptive model of amorphous graphite, Model 18k, *in* Orris, G.J., and Bliss, J.D., eds., Some industrial mineral deposit models—Descriptive deposit models: U.S. Geological Survey Open-File Report 91–11A, p. 9–10.
- Sutphin, D.M., 1991b, Descriptive model of disseminated flake graphite, Model 37f, *in* Orris, G.J., and Bliss, J.D., eds., Some industrial mineral deposit models—Descriptive deposit models: U.S. Geological Survey Open-File Report 91–11A, p. 55–57.
- Sutphin, D.M., 1991c, Descriptive model of graphite veins, Model 37g, *in* Orris, G.J., and Bliss, J.D., eds., Some industrial mineral deposit models—Descriptive deposit models: U.S. Geological Survey Open-File Report 91–11A, p. 58–60.
- Sutphin, D.M., and Bliss, J.D., 1990, Disseminated flake graphite and amorphous graphite deposit types—An analysis using grade and tonnage models: Canadian Mining and Metallurgical Bulletin, v. 83, no. 940, p. 85–89.
- Systèmes Gèostat International Inc., 2007, Preliminary assessment on the Bissett Creek graphite property of Industrial Minerals Canada: NI 43-101 technical report, prepared for Industrial Minerals Canada Inc.: Montreal, Canada, Systèmes Gèostat International Inc., November, 121 p.
- Taylor, H.A., 2006, Graphite, in Kogel, J.E., Trivedi, N.C., Barker, J.M., and Krukowski, S.T., eds., Industrial minerals and rocks (7th ed.): Littleton, Colo., Society for Mining, Metallurgy, and Exploration Inc., p. 507–518.
- Tichy, L., and Turnovec, I., 1978, On possible geochemical identification of graphite in south Bohemia [in Czech]: Geologicky Pruzkum, v. 20, p. 73–75.
- Touzain, P., Balasooriya, N., Bandaranayake, K., and Descolas-Gros, C., 2010, Vein graphite from the Bogala and Kahatagaha-Kolongaha Mines, Sri Lanka—A possible origin: The Canadian Mineralogist, v. 48, no. 6, p. 1373–1384.

- Uragoda, C.G., 1997, A cohort study of graphite workers in Sri Lanka: Occupational Medicine, v. 47, no. 5, p. 269–272.
- U.S. Geological Survey, 1996, Global 30 arc-second elevation (GTOPO30): Reston, Va., U.S Geological Survey dataset (digital elevation model), accessed February 12, 2014, at https://lta.cr.usgs.gov/GTOPO30.
- U.S. Geological Survey, 2012, Mineral Resources Data System: U.S. Geological Survey database, accessed April 4, 2012, at http://mrdata.usgs.gov/mrds/.
- Vine, J.D., and Tourtelot, E.B., 1970, Geochemistry of black shale deposits—A summary report: Economic Geology, v. 65, p. 253–272.
- Weis, P.L., 1973, Graphite, in Brobst, D.A., and Pratt, W.P., eds., United States mineral resources: U.S. Geological Survey Professional Paper 820, p. 277-283. [Also available at http://pubs.er.usgs.gov/publication/pp820.]

- Wilde, S.A., Dorsett-Bain, H.L., and Lennon, R.G., 1999, Geological setting and controls on the development of graphite, sillimanite and phosphate mineralization within the Jiasmusi Massif—An exotic fragment of Gondwanaland located in north-eastern China?: Gondwana Research, v. 2, no. 1, p. 21-46.
- Xu, A., Indala, S., Hertwig, T.A., Pike, R.W., Knopf, F.C., Yaws, C.L., and Hopper, J.R., 2005, Development and integration of new processes consuming carbon dioxide in multi-plant chemical production complexes: Clean Technology Environmental Policy, v. 7, p. 97–115.
- Zavalyevskiy Graphite Ltd., 2013, Home page: Zavalyevskiy Graphite Ltd. Web site, accessed September 19, 2015, at http://zvgraphit.com.ua/en/.
- Zeitler, P.K., Barreiro, B., Chamberlain, C.P., and Rumble, D., III, 1990, Ion-microprobe dating of zircon from quartz-graphite veins at the Bristol, New Hampshire, metamorphic hot spot: Geology, v. 18, p. 626-629.

For more information concerning this report, please contact:

Mineral Resources Program Coordinator

U.S. Geological Survey 913 National Center Reston, VA 20192

Telephone: 703-648-6100

Fax: 703–648–6057

Email: minerals@usgs.gov

Home page: https://minerals.usgs.gov

Prepared by the USGS Science Publishing Network

Reston Publishing Service Center

Edited by J.C. Ishee

Illustrations by Caryl J. Wipperfurth

Layout by Caryl J. Wipperfurth and Cathy Y. Knutson

Posting by Angela E. Hall

#### **GRAPHITE (NATURAL)**

(Data in metric tons unless otherwise noted)

<u>Domestic Production and Use:</u> In 2020, natural graphite was not produced in the United States; however, approximately 95 U.S. firms, primarily in the Great Lakes and Northeastern regions and Alabama and Tennessee, consumed 35,000 tons valued at an estimated \$21 million. The major uses of natural graphite were batteries, brake linings, lubricants, powdered metals, refractory applications, and steelmaking. During 2020, U.S. natural graphite imports were an estimated 41,000 tons, which were about 71% flake and high-purity, 28% amorphous, and 1% lump and chip graphite.

Salient Statistics—United States:	<u>2016</u>	<u> 2017</u>	<u>2018</u>	<u>2019</u>	2020 <sup>e</sup>
Production, mine	_	_			
Imports for consumption	38,900	51,900	70,700	50,300	41,000
Exports	14,300	13,900	9,950	5,880	5,600
Consumption, apparent <sup>1</sup>	24,700	38,000	60,800	44,400	35,000
Price, imports (average dollars per ton at foreign ports):					
Flake	1,920	1,390	1,520	1,350	1,400
Lump and chip (Sri Lanka)	1,880	1,900	1,890	2,390	3,400
Amorphous	571	451	319	496	570
Net import reliance <sup>1</sup> as a percentage					
of apparent consumption	100	100	100	100	100

<u>Recycling</u>: Refractory brick and linings, alumina-graphite refractories for continuous metal castings, magnesia-graphite refractory brick for basic oxygen and electric arc furnaces, and insulation brick led the way in the recycling of graphite products. The market for recycled refractory graphite material is expanding, with material being recycled into products such as brake linings and thermal insulation. Recovering high-quality flake graphite from steelmaking kish is technically feasible, but currently not practiced. The abundance of graphite in the world market inhibits increased recycling efforts. Information on the quantity and value of recycled graphite is not available.

Import Sources (2016-19): China, 33%; Mexico, 23%; Canada, 17%; India, 9%; and other, 18%.

Number	Normal Trade Relations
	<u>12–31–20</u>
2504.10.1000	Free.
2504.10.5000	Free.
2504.90.0000	Free.
	2504.10.1000 2504.10.5000

Depletion Allowance: 22% (domestic lump and amorphous), 14% (domestic flake), and 14% (foreign).

Government Stockpile: None.

Events, Trends, and Issues: U.S. natural graphite exports decreased each year from 2016 to 2020, with an overall 61% decline over the 5-year period. U.S. imports for consumption and apparent consumption increased each year from 2016 to 2018, when imports and consumption peaked, and declined each year during 2019 and 2020. Restrictions put in place in response to the COVID-19 pandemic caused the 2020 U.S. imports to decrease by 18%, which in turn caused a 21% decrease in U.S. apparent consumption.

In 2020, principal United States import sources of natural graphite were, in descending order of tonnage, China, Mexico, Canada, Madagascar, Mozambique, Brazil, the United Kingdom, Hong Kong, Austria, and Belgium, which combined accounted for 99% of the tonnage and 96% of the value of total United States imports. China and Mexico provided most of the amorphous graphite, and Sri Lanka provided all the lump and chip dust variety.

During 2020, China was the world's leading graphite producer, producing an estimated 62% of total world output. Approximately 40% of production in China was amorphous graphite and about 60% was flake. China produced some large flake graphite, but much of its flake graphite production is very small, in the +200-mesh range. China also processed most of the world's spherical graphite. Globally, during the first 6 months of 2020, the COVID-19 pandemic had some effect on graphite supplies, but mostly to operations outside of China. Most areas in China important for natural graphite flake production were far from the initial coronavirus occurrences. The impact was limited in these areas and the recovery was quick, which was demonstrated by China's pattern of exports. Chinese producers quickly increased production after a few months of closures in 2020. This allowed China to gain a more dominant position in the market and slow down the diversification of the supply chain.

#### **GRAPHITE (NATURAL)**

North America produced only 2% of the world's graphite supply with production in Canada and Mexico. No production of natural graphite was reported in the United States, but two companies were developing graphite projects—one in Alabama and one in Alaska.

Large graphite deposits were being developed in Madagascar, northern Mozambique, Namibia, and south-central Tanzania. A graphite mine in Mozambique in a high-grade graphite deposit was reportedly the largest natural graphite mine globally. The mine was expected to operate for about 50 years.

A U.S. automaker continued building a large plant to manufacture lithium-ion electric vehicle batteries. The automaker reported that the plant was about 30% completed. The completed portion of the plant was operational, and it produced battery cells, battery packs, drive units, and energy storage products. At full capacity, the plant was expected to require 35,200 tons per year of spherical graphite for use as anode material for lithium-ion batteries.

New thermal technology and acid-leaching techniques have enabled the production of higher purity graphite powders that are likely to lead to development of new applications for graphite in high-technology fields. Innovative refining techniques have made the use of graphite possible in carbon-graphite composites, electronics, foils, friction materials, and specialty lubricant applications. Flexible graphite product lines are likely to be the fastest growing market. Large-scale fuel-cell applications are being developed that could consume as much graphite as all other uses combined.

<u>World Mine Production and Reserves</u>: Reserves for Brazil, Madagascar, Sri Lanka, and Tanzania were revised based on information reported by graphite-producing companies and the Governments of those countries.

	Mine production		Reserves <sup>2</sup>
	<u>2019</u>	2020e	
United States			(3)
Austria	1,000	1,000	(3)
Brazil	96,000	95,000	70,000,000
Canada	11,000	10,000	(3)
China	700,000	650,000	73,000,000
Germany	800	800	(3)
India	35,000	34,000	8,000,000
Korea, North	6,000	5,000	2,000,000
Madagascar	48,000	47,000	26,000,000
Mexico	9,000	8,000	3,100,000
Mozambique	107,000	120,000	25,000,000
Norway	16,000	15,000	600,000
Pakistan	14,000	13,000	(3)
Russia	25,100	24,000	(3)
Sri Lanka	4,000	3,500	1,500,000
Tanzania	150	150	17,000,000
Turkey	2,000	1,500	90,000,000
Ukraine	20,000	19,000	(3)
Uzbekistan	100	100	7,600,000
Vietnam	5,000	4,500	(3)
World total (rounded)	1,100,000	1,100,000	320,000,000

<u>World Resources</u>: Domestic resources of graphite are relatively small, but the rest of the world's inferred resources exceed 800 million tons of recoverable graphite.

<u>Substitutes</u>: Synthetic graphite powder, scrap from discarded machined shapes, and calcined petroleum coke compete for use in iron and steel production. Synthetic graphite powder and secondary synthetic graphite from machining graphite shapes compete for use in battery applications. Finely ground coke with olivine is a potential competitor in foundry-facing applications. Molybdenum disulfide competes as a dry lubricant but is more sensitive to oxidizing conditions.

<sup>&</sup>lt;sup>e</sup>Estimated. — Zero.

<sup>&</sup>lt;sup>1</sup>Defined as imports – exports.

<sup>&</sup>lt;sup>2</sup>See Appendix C for resource and reserve definitions and information concerning data sources.

<sup>&</sup>lt;sup>3</sup>Included with "World total."